

TABLE OF WOVEN GEOGRID VALUES											
PROPERTY	REQUIRED TEST METHOD	Raugrid 3/3	Raugrid 4/2	Raugrid 6/3	Raugrid 8/3	Raugrid 10/3					
UV Stability (Retained 50% Strength Min. @ 500 hr.)	ASTM D 4355	95%	95%	95%	95%	95%					
Tensile Strength (kN/m)	ASTM D 4595	Ultimate	32.6	41.5	63.5	77.2	96.2				
		2% Ultimate	5.8	8.1	14.0	14.4	19.0				
		5% Ultimate	10.4	11.2	16.7	17.0	29.8				
		Machine Direction	Ultimate	32.3	21.3	28.6	30.5	32.0			
			2% Ultimate	5.5	4.0	4.9	5.7	5.7			
			5% Ultimate	7.9	5.2	6.6	7.8	7.8			
Cross Direction	Ultimate	10.8	11.8	13.1	12.2	11.2					
	2% Ultimate	—	—	—	—	—					
	5% Ultimate	—	—	—	—	—					
Strain @ Ultimate Tensile Strength	ASTM D 4595	2% strain	—	—	—	—	—				
		5% strain	—	—	—	—	—				
		10% strain	—	—	—	—	—				
Junction Strength (kN/m)	GRI # GG2	N/A	108	199	168	146					
Soil-Geosynthetic Friction	GRI # GG5, GT7	0.9	0.9	0.9	0.9	0.9					
Creep Resistance- T_{creep} (kN/m)	ASTM D 5262	21.4	27.3	41.7	50.8	63.3					
Creep Reduction Factor (T_{ult}/T_{creep})	GRI # GG3 & GT5	1.52	1.52	1.52	1.52	1.52					
Installation Damage (RF _C)	Sand	1.10	1.10	1.10	1.10	1.10					
	Limestone	1.14	1.14	1.14	1.14	1.14					
Durability (RF _D)	Chemical	1.15	1.15	1.15	1.15	1.15					
	Biological	1.15	1.15	1.15	1.15	1.15					
Joint Strength (RF _J)	Mechanical	—	—	—	—	—					
	Overlap	—	—	—	—	—					
Approved Application Usage		3	3	3	3	3					

Approved Application Usage: 1 = Steepened Slopes
 2 = Reinforcement of Foundations over Soft Soils
 3 = Both Steepened Slopes & Reinforcement of Foundations over Soft Soils

THE SEALED RECORD OF THIS STANDARD IS ON FILE IN THE ROADWAY DESIGN OFFICE.

APPROVED GEOSYNTHETIC PRODUCTS (WOVEN GEOGRIDS) APPLICATION AND PROPERTIES

STATE OF FLORIDA DEPARTMENT OF TRANSPORTATION ROAD DESIGN			
GEOSYNTHETIC REINFORCED SOILS			
INTERIM STANDARD	APPROVED BY		
THIS SHEET IS A SUPPLEMENT TO THE INTERIM INDEX NO 501 SHEET 6 OF 8 OF THE ROADWAY AND TRAFFIC DESIGN STANDARDS, BOOKLET IN METRIC UNITS, DATED JANUARY 2000.			
REVISION NO.	SHEET NO.	INDEX NO.	DATE
01	1 of 1	0501	