

STANDARD CRITERIA

CLASS	TYPE (1)	APPLICATION DESCRIPTION	INDEX NO.	PERMITTIVITY SEC ⁻¹	ADS SIEVE#	MIN. GRAB TENSILE STRENGTH	MIN. SEWN STRENGTH	MIN. PUNCTURE	MIN. TRAPEZOIDAL TEAR	MIN. WIDE WIDTH TENSILE STRENGTH	UV RESISTANCE (Min. Allowed)		COMMENTS
						kN	kN/m	kN	kN	kN/m	%	Time (Hrs.)	
DRAINAGE (D)	D-1	Revetment (Special)		(See D-2)	(See D-2)	1.40	1.26	0.50	0.50		50	500	Woven Monofilament Geotextiles only (Elongation <50%) Provide 12" thick bedding stone layer.
	D-2	Revetment (Standard)		% SOIL PASSING No. 200 SIEVE	% SOIL PASSING No. 200 SIEVE	Woven Monofilament 1.10	Woven Monofilament 0.99	Woven Monofilament 0.40	Woven Monofilament 0.25		50	500	Woven Geotextiles only. No Slit Film Geotextiles allowed. Provide 12" thick bedding stone layer for revetment (standard). The bedding layer may be omitted if a D-1 fabric is used with revetment (standard). ***Bedding Stone not required for Articulating Block. *For cohesive soils with a plasticity index >7, maximum average role value for ADS is number 50 sieve.
		Articulating Block****		<15% 0.7	<15% 40	Other Geotextiles: Elongation <50% 1.40	Other Geotextiles: Elongation <50% 1.20	Other Geotextiles: Elongation <50% 0.50	Other Geotextiles: Elongation <50% 0.50				
		Gabions	281	15% to 50% 0.2	15% to 50% 60	>50% 0.1	>50% 70*	>50% 0.90	>50% 0.81	>50% 0.35			
	D-3	Underdrain ***	286	% SOIL PASSING No. 200 SIEVE	% SOIL PASSING No. 200 SIEVE	Elongation	Elongation	Elongation	Elongation		50	500	No woven slit film fabrics allowed. *For cohesive soils with a plasticity index >7, maximum average role value for ADS is number 50 sieve. **Required Trapezoidal tear for woven monofilament is 250. ***See Index No. 286 for the permittivity and ADS values of the internal filter fabric of Type V Underdrain.
		French Drain	285	<15% 0.5	<15% 40	<50% 1.10	<50% 0.99	<50% 0.40	<50% 0.40**				
		Sheet Piling Filter		15% to 50% 0.2	15% to 50% 60	>50% 0.70	>50% 0.63	>50% 0.25	>50% 0.25				
		Filter Fabric Jacket (Culvert)	280	>50% 0.1	>50% 70*								
	D-4	Slope Pavement (Sand-Cement)		0.5	40	0.80	0.72	0.22	0.155		50	500	Non-woven, needle-punch only. Elongation ≥50%
		Ditch Pavement (Sand-Cement)	281										
D-5	Mechanical Stabilized Retaining Wall		0.5	40	0.40	0.36	0.22	0.175		50	500		
	Cast-In-Place Retaining Wall												
D-6	Slope Pavement (Concrete)		0.5	40	0.80	0.72	0.22	0.155		50	500	Non-woven, needle-punch only. Elongation ≥50%	
	Ditch Pavement (Concrete)	281											
EROSION (E)	E-1	Staked Silt Fence	102	0.05	NA	0.40	0.36	NA	0.155		80	500	Min. Filtration Efficiency of 75% & min. flow rate of 0.3 gal.
	E-2	Wind Screen		0.05	NA	0.40	0.36	NA	NA		80	150	
	E-3	Plastic Erosion Mat (Turf Reinforcement Mat) (Type 1)	NA	NA	NA	NA	NA	NA	NA	2 x 1	80	500	Use where design shear stress is ≤100 Pa
	E-4	Plastic Erosion Mat (Turf Reinforcement Mat) (Type 2)	NA	NA	NA	NA	NA	NA	NA	4 x 2	80	500	Use where design shear stress is ≤170 Pa
	E-5	Plastic Erosion Mat (Turf Reinforcement Mat) (Type 3)	NA	NA	NA	NA	NA	NA	NA	8 x 4	80	500	Use where design shear stress is ≤240 Pa

(1) Type refers to FDOT class and application.

TABLE I

Test	Unit	Test Method
Permittivity	sec ⁻¹	ASTM-D-4491
ADS	mm	ASTM-D-4751
Elongation	%	ASTM-D-4632
Grab Tensile Strength	kN	ASTM-D-4632
Wide With Tensile Strength	kN/m	ASTM-D-4595
Maximum Design Velocity	M/sec	See Design Note 3
Sewn Strength	kN/m	ASTM-D-4884
Puncture	kN	ASTM-D-4833
Trapezoidal Tear	kN	ASTM-D-4533
Ultraviolet Resistance	% Retained In Strength	ASTM-D-4355
Filtration Efficiency	%	ASTM-D-5141
Flow Rate	L ³ /min.	ASTM-D-5141

GENERAL NOTES

- Specifications for geotextiles are in Section 985. Physical criteria for each application is provided by this standard, in conjunction with those sections.
- All values except ADS are MINIMUM AVERAGE ROLL values in the weakest principal direction. Values for ADS are MAXIMUM AVERAGE ROLL values.
- Test soil or fill material adjacent to the geotextile for gradation to select values for permittivity and ADS.
- Unless specifically restricted in COMMENTS column, any type of material meeting specification 985 may be used.
- Wide width tensile strength is expressed in units of measure of kN/m, in machine direction and cross direction, as MD x CD.

DESIGN NOTES

- The Designer shall review this criteria and adjust the values as necessary to satisfy project requirements. These adjustments shall be called for in the plans or contained in the project special provisions.
- UV Resistance: The value represents the percent minimum textile strength retained (ASTM-D-4632) after weathering per ASTM-D-4355 for the test period (hours).
- Shear stress limits for plastic erosion mats determined by 30 minutes sustained flow in unvegetated state as determined by tests performed by Utah State University, Texas Transportation Institute or an independent testing laboratory approved by the State Drainage Engineer.



2008 FDOT Design Standards

GEOTEXTILE CRITERIA

Last Revision 07/01/07
Sheet No. 1 of 1
Index No. 199