STANDARD CRITERIA

CLASS	TYPE (1)	APPLICATION DESCRIPTION	INDEX NO.	PERMITTIVITY (sec^{-1})	AOS SIEVE#	MIN. GRAB TENSILE STRENGTH (lb)	MIN. SEWN STRENGTH (lb/in)	MIN. PUNCTURE (lb)	MIN. TRAPEZOIDAL TEAR (lb)	MIN. WIDE WIDTH TENSILE STRENGTH (lb/in)	UV RESISTANCE (Min. Allowed) %	UV RESISTANCE (Min. Allowed) Time (Hrs.)	COMMENTS
DRAINAGE (D)	D-1	Revetment (Special)		(See D-2)	(See D-2)	315	7.2	113	113		50	500	Woven Monofilament Geotextiles only (Elongation <50%) Provide 12" thick bedding stone layer.
	D-2	Revetment (Standard) Articulating Block**** Gabions Rock, Rubble, Broken Concrete	281	% SOIL PASSING No. 200 SIEVE <15% 0.7 15% to 50% 0.2 >50% 0.1	% SOIL PASSING No. 200 SIEVE <15% 40 15% to 50% 60 >50% 70*	Woven Monofilament 248 Other Geotextiles: Elongation <50% 315 ≥50% 203	Woven Monofilament 5.7 Other Geotextiles: Elongation <50% 6.9 ≥50% 4.7	Woven Monofilament 90 Other Geotextiles: Elongation <50% 113 ≥50% 79	Woven Monofilament 57 Other Geotextiles: Elongation <50% 113 ≥50% 79		50	500	Woven Geotextiles only. No Slit Film Geotextiles allowed. Provide 12" thick bedding stone layer for revetment (standard). The bedding layer may be omitted if a D-1 fabric is used with revetment (standard). ****Bedding Stone not required for Articulating Block. *For cohesive soils with a plasticity index >7, maximum average role value for AOS is number 50 sieve.
	D-3	Underdrain *** French Drain Sheet Piling Filter Filter Fabric Jacket (Culvert) Concrete Pavement Subdrainage	286 285 280 287	% SOIL PASSING No. 200 SIEVE <15% 0.5 15% to 50% 0.2 >50% 0.1	% SOIL PASSING No. 200 SIEVE <15% 40 15% to 50% 60 >50% 70*	Elongation <50% 248 ≥50% 158	Elongation <50% 5.7 ≥50% 3.6	Elongation <50% 90 ≥50% 57	Elongation <50% 90** ≥50% 57		50	500	No woven slit film fabrics allowed. *For cohesive soils with a plasticity index >7, maximum average role value for AOS is number 50 sieve. **Required Trapezoidal tear for woven monofilament is 250. ***See Index No. 286 for the permittivity and AOS values of the internal filter fabric of Type V Underdrain.
	D-4	Slope Pavement (Sand-Cement) Ditch Pavement (Sand-Cement)	 281	0.5	40	180	4.2	50	35		50	500	Non-woven, needle-punch only. Elongation ≥50%
	D-5	Mechanical Stabilized Retaining Wall Cast-In-Place Retaining Wall		0.5	40	90	2.1	50	40		50	500	
	D-6	Slope Pavement (Concrete) Ditch Pavement (Concrete)	 281	0.5	40	180	4.2	50	35		50	500	Non-woven, needle-punch only. Elongation ≥50%
EROSION (E)	E-1	Staked Silt Fence		0.05	NA	90	2.1	NA	35		80	500	Min. Filtration Efficiency of 75% & min. flow rate of 0.3 gal.
	E-2	Wind Screen		0.05	NA	90	2.1	NA	NA		80	150	
	E-3	Plastic Erosion Mat (Turf Reinforcement Mat) (Type 1)		NA	NA	NA	NA	NA	NA	12 x 6	80	500	Use where design shear stress is ≤2.1 psf
	E-4	Plastic Erosion Mat (Turf Reinforcement Mat) (Type 2)		NA	NA	NA	NA	NA	NA	23 x 12	80	500	Use where design shear stress is ≤3.6 psf
	E-5	Plastic Erosion Mat (Turf Reinforcement Mat) (Type 3)		NA	NA	NA	NA	NA	NA	46 x 23	80	500	Use where design shear stress is ≤5.0 psf

(1) Type refers to FDOT class and application.

TABLE I

Test	Unit	Test Method
Permittivity	sec^{-1}	ASTM-D-4491
AOS	US Sieve No.	ASTM-D-4751
Elongation	%	ASTM-D-4632
Grab Tensile Strength	lb	ASTM-D-4632
Wide Width Tensile Strength	lb/in	ASTM-D-4595
Maximum Design Velocity	fps	See Design Note 3
Sewn Strength	lb/in	ASTM-D-4884
Puncture	lb	ASTM-D-4833
Trapezoidal Tear	lb	ASTM-D-4533
Ultraviolet Resistance	% Retained In Strength	ASTM-D-4355
Filtration Efficiency	%	ASTM-D-5141
Flow Rate	gal^3/min	ASTM-D-5141

GENERAL NOTES

1. Specifications for geotextiles are in Section 985. Physical criteria for each application is provided by this standard, in conjunction with those sections.
2. All values except AOS are MINIMUM AVERAGE ROLL values in the weakest principal direction. Values for AOS are MAXIMUM AVERAGE ROLL values.
3. Test soil or fill material adjacent to the geotextile for gradation to select values for permittivity and AOS.
4. Unless specifically restricted in COMMENTS column, any type of material meeting specification 985 may be used.
5. Wide width tensile strength is expressed in units of measure of lb./in., in machine direction and cross direction, as MD x CD.
6. The Manufacturer shall provide results in English Units.

DESIGN NOTES

1. The Designer shall review this criteria and adjust the values as necessary to satisfy project requirements. These adjustments shall be called for in the plans or contained in the project special provisions.
2. UV Resistance: The value represents the percent minimum textile strength retained (ASTM-D-4632) after weathering per ASTM-D-4355 for the test period (hours).
3. Shear stress limits for plastic erosion mats determined by 30 minutes sustained flow in unvegetated state as determined by tests performed by Utah State University, Texas Transportation Institute or an independent testing laboratory approved by the State Drainage Engineer.

LAST REVISION	REVISION	DESCRIPTION:				
07/01/12			FDOT DESIGN STANDARDS 2013	GEOTEXTILE CRITERIA	INDEX NO. 199	SHEET NO. 1

C:\d\projects\standards\roadway\00200-s\00199-01.dgn
6/28/2012 7:12:22 AM rd960rh