

SECTION 943
CORRUGATED STEEL PIPE AND PIPE ARCH
(Including Underdrain)

943-1 General Requirements.

Corrugated steel pipe, including round culvert pipe, pipe arch and underdrain and coupling bands for each type shall conform to AASHTO M 36 [AASHTO M 36M].

In addition, except for underdrain corrugated steel pipe including pipe arch shall be fabricated with helical corrugations with a minimum of two annular corrugations formed on each end of each pipe to accommodate a coupling band. Annular fabrication is not permitted unless specifically called for in the plans or specifications.

943-2 Round Culvert Pipe.

For round culvert pipe used as sidedrain, unless shown otherwise in the plans the minimum thickness of the metal (including galvanizing - AASHTO M 218, or aluminum coating - AASHTO M 274), shall be as specified below.

NON SI UNITS		
TABLE I		
THICKNESS OF METAL FOR SIDEDRAIN PIPE		
Nominal Diameter (Inches)	Metal Sheet Gauge No.	Mean Thickness Metal (Inches)
6	18	0.0516
8	16	0.0635
10	16	0.0635
12	16	0.0635
15	16	0.0635
18	16	0.0635
21	16	0.0635
24	16	0.0635
30	14	0.0785
36	14	0.0785
42	12	0.1084
48	12	0.1084
54	12	0.1084
60	10	0.1382
66	10	0.1382
72	10	0.1382
78	8	0.1681
84	8	0.1681
90	8	0.1681
96 and over	8	0.1681

SI UNITS	
TABLE I	
THICKNESS OF METAL FOR SIDEDRAIN PIPE	
Nominal Diameter (mm)	Mean Thickness Metal (mm)
150	1.32
200	1.63
250	1.63
300	1.63
375	1.63
450	1.63
525	1.63
600	1.63
750	2.01
900	2.01
1,050	2.77
1,200	2.77
1,350	2.77
1,500	3.51
1,650	3.51
1,800	3.51
1,950	4.27
2,100	4.27
2,250	4.27
2,400 and over	4.27

NON SI UNITS		
TABLE II		
PERMISSIBLE VARIATION IN THICKNESS OF METAL FOR PIPE AND CONNECTING BANDS		
Metal Sheet Gauge No	Mean Thickness of Metal (Inches)	Permissible Variation (Inches)
18	0.0516	0.007
16	0.0635	0.007
14	0.0785	0.008
12	0.1084	0.009
10	0.1382	0.009
8	0.1681	0.009

SI UNITS	
TABLE II	
PERMISSIBLE VARIATION IN THICKNESS OF METAL FOR PIPE AND CONNECTING BANDS	
Mean Thickness of Metal (mm)	Permissible Variation (mm)
1.32	0.18
1.63	0.18
2.01	0.20
2.77	0.23
3.51	0.23
4.27	0.23

943-3 Pipe Arch.

For corrugated metal pipe arch, in addition to the requirements shown in AASHTO M 36 [AASHTO M 36M], thickness of the metal shall be as shown for the equivalent size round pipe in Tables I and II, above, and the fabrication of the pipe arch sections shall be such as to insure a substantially flat invert.

943-4 Alternate Connecting Bands.

In addition to the connecting bands as specified in AASHTO M 36 [AASHTO M 36M], alternate types of connecting bands are specified in 430-8.1.3, for use with the types of installations as shown.

943-5 Bituminous Coating and Paved Invert.

When bituminous coating is specified, the pipe, or pipe arch, shall be coated in accordance with the requirements of AASHTO M 190, for Type A (Fully Bituminous Coated).

When bituminous coated and paved invert are specified the pipe or pipe arch shall be coated and paved in accordance with AASHTO M 190, for Type C (Fully Bituminous Coated and Paved). The temperature of the asphalt at the time of coating and the duration of the pipe submerged time shall be optimized such that excess coating does not adhere to the pipe. Excess coating is deemed to exist when generalized plugging is present on 50% or more of the pipe circumference.

943-6 Paved Interior.

When bituminous coated and paved interior are called for, the coating and paving shall meet the requirements specified above for bituminous and paved invert (Type C), with the following additions and exceptions:

- (a) The smooth pavement formed by the asphalt cement shall extend over the entire interior of the pipe.
- (b) The exterior coating and the interior paving shall be applied.
- (c) No markings will be required on the outside of the pipe to designate the center line of the top of the pipe.
- (d) Lifting lugs shall be attached to the pipe, and shall be suitably placed to facilitate moving the pipe without damage to the exterior or interior bituminous material.

943-7 Basis of Acceptance of Bituminous Coating and Paving.

The acceptance of the bituminous coating, paved invert, and paved interior will be based on the manufacturer's certified mill tests.

943-8 Underdrain Pipe.

Corrugated metal pipe for underdrain shall conform to the requirements of AASHTO M 36 [AASHTO M 36M] except that Class IV pipe, as specified in Article 18.1.1.4 therein, shall not be used.