

SECTION 948 MISCELLANEOUS TYPES OF PIPE

948-1 Polyvinyl-Chloride Pipe, or Acrylonitrile-Butadiene-Styrene Plastics Pipe.

948-1.1 For Bridge Drains: Polyvinyl-chloride pipe, for use in bridge drains which will be exposed shall conform to the requirements of ASTM D 1785, for Type II, Grade 1, Schedule 40 PVC pipe. For the portion of bridge drains encased in concrete, the pipe may be as specified in 948-1.4.

948-1.2 Pressure Pipe: Pressure pipe for direct burial under pavement shall conform to the requirements of ASTM D 1785, for Type I, Grade I, Schedule 40, for sizes up to and including 2 1/2 inches [60 mm], and Schedule 80 for sizes up to 4 inches [100 mm]. Pressure pipe 4 inches [100 mm] in diameter and larger shall conform to the requirements of AWWA C900-75, DR18, and ASTM D 1785, Type I, Grade I or other types as may be specifically called for in the plans or special provisions.

948-1.3 Pipe Marking: All polyvinyl-chloride pipe shall be marked as required by Article 8 of ASTM D 1785, and acceptance of the pipe may be based on this data.

948-1.4 Nonpressure Pipe: Polyvinyl-chloride pipe and Acrylonitrile-butadiene-styrene pipe, intended for direct-burial or concrete encasement, shall meet the following requirements:

(a) PVC Pipe: ASTM D 3034, SDR-35, or ASTM F 949, profile wall without perforations.

(b) ABS Pipe: ASTM D 2680.

The manufacturer of the PVC or ABS pipe shall furnish to the Engineer six copies of mill analysis covering chemical and physical test results.

948-1.5 Underdrain: Polyvinyl-chloride pipe for use as underdrain shall conform to the requirements of ASTM F 758 or ASTM F 949. Also, PVC underdrain manufactured from PVC pipe meeting ASTM D 3034, perforated in accordance with the perforation requirements given in AASHTO M 36 or AASHTO M 196 will be permitted.

948-1.6 Edgedrain: Polyvinyl-chloride pipe for use as edgedrain shall conform to the requirements of ASTM F 758, ASTM F 949 or ASTM D 3034 pipe shall be perforated in accordance with the perforation requirements given in AASHTO M 36 or AASHTO M 196. Additional perforations will be required as indicated in the Design Standards, Index No. 286 for pipes designated under ASTM F 758 and ASTM D 3034. Polyvinyl chloride pipe intended for direct burial in asphalt shall meet the following requirements:

(a) ASTM D 3034, SDR-35, or ASTM F 949

(b) NEMA TC-2 (pipe material and compounds) and NEMA TC-3 (pipe fittings) for PVC (90° C electrical conduit pipe) NEMA ECP-40 and NEMA ECP-80. Underwriter Laboratory Specifications referenced under NEMA specifications for electrical conductivity are not required.

(c) Pipe shall withstand asphalt placement temperatures specified without permanent deformation.

(d) Perforations shall be in accordance with AASHTO M 36M or AASHTO M 196M.

948-1.7 Polyvinyl Chloride (PVC) Pipe (12 to 48 Inches [300 to 1,200 mm]): Polyvinyl Chloride (PVC) Pipe for side drain, cross drain, storm drain and other specified applications shall conform to AASHTO M 278 for smooth wall PVC pipe, or AASHTO M 304 or ASTM F 949 for PVC ribbed pipe. Mitered end sections are not to be constructed of polyvinyl chloride. Use only concrete or metal mitered end sections as indicated in the Design Standards.

When rubber gaskets are to be installed in the pipe joint, the gasket shall be the sole element relied on to maintain a tight joint. Test pipe joints at the plant hydrostatically using test methods in ASTM D 3212 [ASTM D 3212M]. Soil tight joints must be watertight to 2 psi [13.8 kPa]. Watertight joints must be watertight to 5 psi [34.5 kPa] unless a higher pressure rating is required in the plans.

Provide certification of the actual mean diameter of pipe shipped to the project. Include in the certification the minimum and maximum diameters used to certify the actual mean diameter. The certification shall be attested to by a person having legal authority to bind the manufacturing company.

948-2 Corrugated Polyethylene Tubing and Pipe.

948-2.1 General: For underdrain, Corrugated Polyethylene Tubing and fittings shall meet the requirements of AASHTO M 252. For edgedrain, Corrugated Polyethylene Tubing and fittings shall meet the requirements of AASHTO M 252, except as modified in 948-2.2. For storm drain side drain, french drain and cross drain. Corrugated Polyethylene Pipe shall meet the requirements of AASHTO M 294 and the additional provisions specified in 948-2.3.

The tubing or pipe shall not be left exposed to sunlight for periods exceeding the manufacturer's recommendation.

948-2.2 Edgedrain (4 to 10 inches [100 to 250 mm]): The requirements for Edgedrain as specified in AASHTO M 252 are modified as follows:

(a) Coiling of tubing 6 inches [150 mm] in diameter or greater is not permitted. Tubing shall have a minimum pipe stiffness of 46 psi [275 kPa] at 5% deflection.

948-2.3 Corrugated Polyethylene Pipe (12 to 48 inches [300 to 1,200 mm]): Corrugated Polyethylene Pipe for side drain, cross drain, storm drain and other specified applications shall conform to AASHTO M 294 with the following exceptions: corrugations may only be annular; pipe conforming to the minimum cell classification 335420E may be used if the combination of color and UV stabilizer provides the same or better UV protection as 335420C. Mitered end sections are not to be constructed of polyethylene. Use only concrete or metal mitered end sections as indicated in the Design Standards.

When rubber gaskets are to be installed in the pipe joint, the gasket shall be the sole element relied on to maintain a tight joint. Test pipe joints at the plant hydrostatically using test methods in ASTM D 3212 [ASTM D 3212M]. Soil tight joints must be watertight to 2 psi [13.8 kPa]. Watertight joints must be watertight to 5 psi [34.5 kPa] unless a higher pressure rating is required in the plans.

Provide certification of the actual mean diameter of pipe shipped to the project. Include in the certification the minimum and maximum diameters used to certify the actual mean diameter. The certification shall be attested to by a person having legal authority to bind the manufacturing company.

948-3 Filter Fabric Sock for Use with Underdrain.

For Type I Underdrain specified in the Design Standards, Index 286, filter sock shall be an approved strong rough porous, polyester or other approved knitted fabric which completely covers and is secured to the perforated plastic tubing underdrain in such a way as to prevent infiltration of trench backfill material.

The knitted fabric sock shall be a continuous one piece material that fits over the tubing like a sleeve. It shall be knitted of continuous 150 denier yarn and shall be free from any chemical treatment or coating that might significantly reduce porosity and permeability.

The knitted fabric sock shall comply with the following physical properties:

| | | |
|-----------------------------------|------------|-----------------------------------|
| Weight, applied (oz./sq. yd.) | 3.5 min | ASTM D 3887 |
| Grab tensile strength (lbs.) | 50 min.* | ASTM D 5034 |
| Equivalent opening size (EOS No.) | 25 min.** | Corps of Engineers CW-02215-77 |
| Burst strength (psi) | 100 min.** | ASTM D 3887 |

*Tested wet.

**Manufacturer's certification to meet test requirement.

The knitted fabric sock shall be applied to the tubing in the shop so as to maintain a uniform applied weight. The tubing with knitted fabric sock shall be delivered to the job site in such manner as to facilitate handling and incorporation into the work without damage. The knitted fabric sock shall be stored in UV-resistant bags until just prior to installation. Torn or punctured knitted fabric sock shall not be used.

948-4 Pipe Liner.

948-4.1 Cured-In-Place Pipe Liner: Cured-in-place pipe liner shall be continuous, resin impregnated, flexible tubing that meets the requirements of ASTM D 5813 and ASTM F 1216.

948-4.2 Deformed Pipe Liner: Deformed pipe liner shall be manufactured in an out of round state, usually collapsed circumferentially and folded on the long axis. After installation in a host pipe, the liner is rounded by means of heat and pressure to fit the host pipe. Deformed pipe liner, when installed, shall extend from one structure to the next in one continuous length with no intermediate joints.

(1) Polyethylene: Deformed polyethylene pipe liner shall meet the requirements of ASTM D 3350 or ASTM F 714 with a minimum cell classification of 335420c.

(2) Polyvinyl Chloride: Deformed polyvinyl chloride pipe liner shall meet the requirements of ASTM F 1504 and shall have a minimum cell classification of 12456b.

948-4.3 Discrete Pipe Liner: Discrete pipe liner shall be round, flexible or semi-rigid liner, manufactured in lengths that may be joined in a manhole or access pit before insertion in a host pipe.

(1) Polyethylene: Discrete polyethylene pipe liner shall meet the requirements of ASTM D 3550 or ASTM F 714 and shall have a minimum of cell classification of 335420c.

(2) High Density Polyethylene Profile Wall: Discrete high density polyethylene pipe liner shall meet the requirements of ASTM F 894 and shall have a minimum cell classification of 335420c.

(3) Polyvinyl Chloride: Discrete polyvinyl chloride pipe liner shall meet the requirements of ASTM F 789, ASTM F 794, or ASTM F 949 and shall have a minimum cell classification of 12456b.

(4) Fiberglass: Discrete fiberglass pipe liner shall meet the requirements of ASTM D 3262.

948-4.4 Spiral Wound Pipe Liner: Spiral wound pipe liner shall consist of coils of profile strips that are wound into a host pipe helically, after which a cementitious grout is injected into the annular space between the liner and the host pipe, forming a rigid composite structure.

(1) Polyvinyl Chloride: Polyvinyl chloride spiral wound pipe liner shall meet the requirements of ASTM F 1697 or ASTM F 1698 and shall have a minimum cell classification of 12454b.

948-4.5 Paneled Pipe Liner: Paneled pipe liner consists of custom-cut flat or curved panels that are formed to the inside circumference of a host pipe.

(1) Polyvinyl Chloride: Polyvinyl chloride paneled pipe liner shall meet the requirements of ASTM F 1698 and shall have a minimum cell classification of 12454b.

948-4.6 Point Pipe Liner: Point pipe liner may consist of any materials covered by this specification when used to repair and rehabilitate an isolated portion of an existing storm drain pipe. Materials which are restricted (as primary components) to point repair are; steel, which shall meet the requirements of AASHTO M 167M, ASTM A 167, or ASTM A 240; aluminum, which shall meet the requirements of AASHTO M 196M, and rubber; which shall meet the requirements of ASTM C 923.

948-4.7 Coated Pipe Liner: Coated pipe liner consists of liquid, slurry, foam or gel that is spread or sprayed over the interior surface of an existing pipe to rehabilitate it. Materials that may be used for coating are hydrophilic urethane gel, epoxy resin, polyester resin, gunite, shotcrete, low density cellular concrete, and cementitious grout.