

SECTION 965
GENERAL PROVISIONS FOR ALUMINUM ITEMS
(Including Welding)

965-1 Surface Appearance and Protection.

The exterior surfaces of aluminum castings, pipes, tubes, formed sheets, and structural shapes shall, when placed in the work, have a clean, uniform silvery appearance, free of dark streaks and discoloration.

Aluminum members (including specifically aluminum light poles and signs poles) which are of such size or shape that the surfaces might be marred during transit and prior to their being installed, shall be appropriately and adequately protected against such damage, by wrapping with paper or by other effective means.

965-2 Tests of Aluminum Materials (Mill-Analysis Reports).

For all aluminum materials proposed for use, six certified copies of mill analysis will be required, with certification by the producer that the parts are of the alloys specified and meet the specifications called for. Such reports shall be forwarded to the Department's State Materials Engineer, at Gainesville.

965-3 Welding Aluminum Sign Structures.

The proportioning of weld details and the operation of welding, for aluminum sign structure, shall be in accordance with Section 5 of the AASHTO Standard Specifications for Structural Supports for Highway Signs, Luminaries and Traffic Signals; ANSI and AWS D1.2 "Structural Welding Code - Aluminum", including the requirements for qualifications of procedures and welders, as specified therein.

(a) Alloys: The aluminum alloys to welded under these specifications may be any of the following alloys:

Wrought Nonheat-treatable Alloys:

Alloy 3003

Alloy Alclad 3004

Alloy 5052

Alloy 5083

Alloy 5086

Alloy 5456

Wrought Heat-treatable Alloys:

Alloy 6061

Alloy 6063

Cast Heat-treated Alloy

Alloy SG-70A (ASTM Designation)

(b) Filler Metals: The filler metals to be used with particular base metals shall be as shown in the table below except that other filler metals may be used if approved by the Engineer.

Base Metal	Filler Metal
3003 to 3003	ER1100
Alclad 3004 to Alclad 3004	ER4043
5052 to 5052	ER5356*
5083 to 5083	ER5183
5086 to 5086	ER5356*
5456 to 5456	ER5556
6061 to 6061	ER5356*
6063 to 6063	ER5356*
SG-70A to 6061	ER4043
SG-70A to 6063	ER4043

*ER5183, ER5356, and ER5556 may be used interchangeably for these base metals.

965-4 Welding Aluminum Structures Other Than Sign Structures.

The welding of aluminum structures, other than sign structures, such as aluminum bridge and railing structures and their aluminum components, shall be in accordance with ANSI and AWS D1.2 "Structures Welding Code - Aluminum", including the requirements for qualifications of procedures and welders, as specified therein.