

**SECTION 914
STABILIZATION MATERIALS**

914-1 General.

This Section governs materials to be used in subgrade stabilization. Meet the following requirements:

Plasticity Index (AASHTO T 90)	Maximum 10
Liquid Limit (AASHTO T 89)	Maximum 40
Passing a 3 1/2 inch screen (AASHTO T 27)	Minimum 97%
LBR	No Requirement

914-2 Materials for Stabilizing (Limerock Bearing Ratio).

914-2.1 Commercial Materials: Materials may be either limerock, shell rock, cemented coquina or shell base sources approved in accordance with 6-3.3.

914-2.2 Local Materials: Local materials used for stabilizing may be soils or recyclable materials such as crushed concrete, roof tiles and asphalt coated base or reclaimed pavement provided the following limits for Organic Content are met.

Average Organic Content* (FM1-T 267)	Maximum 2.5%
Individual Organic Content Sample (FM1-T 267)	Maximum 4%
*Note: A minimum of three samples per source	

Materials that contain hazardous substances or contaminants shall not be used.

If toxic substances, elements or compounds are suspected to exist at concentrations exceeding limits defined by EPA, qualifying tests shall be performed. Test methods for these substances shall be those mandated by EPA and analyzed by a certified laboratory.