



Florida Method of Test  
for  
DUCTILITY OF BITUMINOUS MATERIALS  
Designation: FM 1-T 051

FM 1-T 051 is identical to AASHTO T 51 except for the following provisions.

Replace Section 6.1 of ASTM D 113 (which AASHTO T 51 refers to) with the following:

- 6.1 A normal test is one in which the material between the two clips pulls out to a point or thread until rupture occurs at the point where the thread has practically no cross-sectional area or until the capacity of the machine is reached. Only one normal test will be performed for routine testing. If after comparison with the applicable specification, a normal test is less than the minimum allowable or does not exceed the minimum allowable by more than twenty centimeters, report the average of three normal tests as the ductility of the sample.

Obsolete January 2021 - Supersceded by AASHTO T51