FLORIDA DEPARTMENT OF TRANSPORTATION
State Materials Office
5007 NE 39th Avenue
Gainesville, Florida 32609

July 1, 2020

Florida Method of Test
For
Reducing Samples of Aggregate to Testing Size

Designation: FM 1-R 076

FM 1-R 076 is identical to AASHTO R 76 except for the following provisions:

1. Replace all occurrences of “R 76” with “FM 1-R 076.”

   Replace all occurrences of “T 84” in with “FM 1-T 084.”

2. Add at the following to the end of Section 5.1.2:

   > “Alternately, the sample need not be dried to at least the surface-dry condition. Smaller particles adhering to the chutes or splitting bar should be brushed downwards into the containers.“