

State Materials Office 5007 NE 39th Avenue Gainesville, Florida 32609

July 1, 2020

Florida Method of Test For Reducing Samples of Aggregate to Testing Size

Designation: FM 1-R 076

FM 1-R 076 is identical to AASHTO R 76 except for the following provisions:

1. Replace all occurrences of "R 76" with "FM 1-R 076."

Replace all occurrences of "T 84" in with "FM 1-T 084."

2. Add at the following to the end of Section 5.1.2:

"Alternately, the sample need not be dried to at least the surface-dry condition. Smaller particles adhering to the chutes or splitting bar should be brushed downwards into the containers."

FM 1-R 076