

Equipment Checklist AASHTO T 21 Organic Impurities in Fine Aggregate for Concrete

		P	F	N/A
1	Clear glass bottles capacity approx. 8 – 16oz			
2	Water tight stoppers or caps which do not discolor NaOH solution n 24 hours			
3	Fine aggregate level graduation line at 4 ½ oz			
4	Solution level graduation line at 7oz			
5	Sodium Hydroxide solution 3 percent – dissolve 3 parts by weight of NaOH in 97 parts of water			
6	Glass Color Standard – Gardner Color Standard No. 11			

Remarks:

Date: _____ Technician: _____ IA Observer: _____

Technician's E-mail Address: _____

Employer's/Supervisor's E-mail Address: _____