

**State of Florida Department of Transportation
PAVEMENT EVALUATION AND CONDITION DATA SHEET**

Project No.: 441562-1					Cored By: Ardaman									Date: 6/3/2019				Page No.: 1 of 9			
County: Arcadia					Section No.: 04040000									From: Peace River				To: SE Baker Street			
Road No.: SR 70																					
Core No.	MP	Distance from left edge of lane (ft.)	Lane	Wheel Path	Pavement Layers (in.)								Base		Crack				Pavt Cond.	Comments	
					FC-3	FC-9.5	FC-12.5	Type SP-9.5	Type SP-12.5	Type S	Binder	SAHM/Type II	Core Length (in)	Type	Thickness (in)	Depth (in)	Type	Class			Extent
1	14.180	6.0	L2	No				1.5		1.7			3.2	SC	8.8	---	---	---	---	G	Patch Area (new)
29	12.496	3.0	L1	Yes	1.3					2.5			3.8	SC	9.7	---	---	---	---	F	Side St. N. Baldwin Ave.
30	12.416	9.5	L1	No	0.9					2.5			3.4	SC	9.6	---	---	---	---	P	Side St. S Parker Ave.
31	12.386	6.0	L2	No	1.5					2.6			4.1	SC	10.6	4.1	SL	III	S	P	Patch Area
32	12.386	5.5	OL	---	1.5					1.5			3.0	SC	10.0	0.3	SL	I	L	P	Patch Area
33	12.326	8.5	L2	Yes		1.4				1.7			3.1	SC	8.9	---	---	---	---	G	Patch Area
34	12.326	7.0	OL	---		1.3				1.5			2.8	SC	7.0	---	---	---	---	G	Patch Area
35	12.336	9.0	R2	Yes		0.7				1.3			2.0	SC	10.0	---	---	---	---	G	
36	12.336	7.0	OR	---		1.2				0.9			2.1	SC	7.8	---	---	---	---	G	Raveling
37	12.386	3.5	R2	Yes	0.7					2.8			3.5	SC	11.3	3.5	Br	III	S	P	
38	12.386	7.0	OR	---	1.0					2.9			3.9	SC	9.8	---	---	---	---	P	
39	12.416	10.0	R1	No	0.9					1.6			2.6	SC	10.2	---	---	---	---	P	Side St. S. Parker
40	12.496	6.5	R1	No						3.3			3.3	NB	---	---	---	---	---	P	Side St. Baldwin
41	12.623	16.0	R2	No		1.9				1.5			3.4	SC	8.4	3.4	Br	III	S	P	
42	12.725	12.0	R1	Yes	0.5					2.5			3.0	SC	8.9	0.4	SL	I	L	P	Side St. Baldwin
43	12.754	5.0	L1	No	1.0					3.3			4.3	SC	10.7	---	---	---	---	P	Side St. Singleton St.

Remarks: Crack Depth of "B" indicates full depth crack to the base. EOP = Edge of Pavement
Crack Extent: L= Light; M= Moderate; S= Severe **Pavement Condition:** G= Good; F= Fair; P= Poor **Crack Types:** A= Alligator; Bl= Block; Br= Branch
 SL= Single Longitudinal; ST= Single Transverse; R= Reflective; J= Joint; OGFC= Open-Graded FC Stress Crack
Base Types: LR= Limerock; COQ= Coquina; SC= Soil Cement; ABC= Asphalt Base; SAHM= Sand Asphalt Hot Mix; NB= No Base

State of Florida Department of Transportation
PAVEMENT EVALUATION AND CONDITION DATA SHEET

Project No.: 441562-1					Cored By: Ardaman									Date: 6/3/2019				Page No.: 2 of 9			
County: Arcadia					Section No.: 04040000									From: Peace River				To: SE Baker Street			
Road No.: SR 70																					
Core No.	MP	Distance from left edge of lane (ft.)	Lane	Wheel Path	Pavement Layers (in.)									Base		Crack				Pavt Cond.	Comments
					FC-3	FC-9.5	FC-12.5	Type SP-9.5	Type SP-12.5	Type S	Binder	SAHM/Type II	Core Length (in)	Type	Thickness (in)	Depth (in)	Type	Class	Extent		
44	12.952	2.0	L1	Yes	0.8					1.7			2.5	LR	7.5	---	---	---	---	F	Side St. S Lee St.
45	13.000	8.5	R2	Yes			1.0			8.5			9.5	LR	8.5	9.5	Br	III	S	P	
46	13.060	2.5	R2	Yes		1.5				1.5			3.0	LR	9.0	3.0	J	III	S	P	Cored on Joint, half LR Base and half ABC Base
47	13.090	8.0	R1	No	1.2					1.3			2.5	SC	7.4	2.5	Br	III	S	P	Side ST. S Manatee
48	13.158	7.0	R1	No	1.0					1.1			2.1	LR	6.2	---	---	---	---	P	Side St. S Orange
49	13.229	7.0	R1	Yes	0.6					2.1			2.7	LR	5.0	---	---	---	---	F	Side St. S. Monroe
50	13.296	2.5	R1	Yes	0.6					2.9			3.5	SC	5.3	---	---	---	---	P	Side St. Polk
51	13.363	7.5	RRTL	Yes	1.1					3.1			4.2	SHEL	10.4	4.2	SL	III	S	P	Base with Shell and Rocks
52	13.387	7.0	L1	Yes		1.5		1.3		1.7			4.5	SC	12.0	---	---	---	---	G	Side St. Desoto, Patch Area
53	13.466	8.0	R1	Yes		0.8		1.0		3.2	0.9		5.9	LR	12.1	B	Br	II	S	F	Side St. Brevard (Patch Area)
54	13.524	5.5	R2	No		0.9		2.1				2.3	5.3	SC	8.7	5.3	A	III	S	P	Severe Alligator Cracking and Rutting
55	13.534	2.0	R1	Yes		1.4		1.9					3.3	SC	10.7	---	---	---	---	F	Side St. S. Volusia
56	13.610	5.0	R1	No		0.7		2.2					2.9	SC	7.1	2.9	ST	III	S	P	Side St. S. Hillborough
57	13.670	2.0	R1	Yes	1.0					1.5			2.5	SC	5.2	---	---	---	---	F	Side St. S. Hernando
58	13.709	2.5	R2	Yes	1.8			1.5				2.0	5.3	SC	5.7	5.3	A	III	S	P	
59	13.739	2.5	R1	Yes	0.5					1.7			2.2	SC	5.8	---	---	---	---	P	Side St. S. Osceola Ave.

Remarks: Crack Depth of "B" indicates full depth crack to the base. EOP = Edge of Pavement
Crack Extent: L= Light; M= Moderate; S= Severe **Pavement Condition:** G= Good; F= Fair; P= Poor **Crack Types:** A= Alligator; Bl= Block; Br= Branch
 SL= Single Longitudinal; ST= Single Transverse; R= Reflective; J= Joint; OGFC= Open-Graded FC Stress Crack
Base Types: LR= Limerock; COQ= Coquina; SC= Soil Cement; ABC= Asphalt Base; SAHM= Sand Asphalt Hot Mix; NB= No Base

**State of Florida Department of Transportation
PAVEMENT EVALUATION AND CONDITION DATA SHEET**

Project No.: 441562-1					Cored By: Ardaman									Date: 6/3/2019				Page No.: 3 of 9			
County: Arcadia					Section No.: 04040000									From: Peace River				To: SE Baker Street			
Road No.: SR 70																					
Core No.	MP	Distance from left edge of lane (ft.)	Lane	Wheel Path	Pavement Layers (in.)									Base		Crack				Pavt Cond.	Comments
					FC-3	FC-9.5	FC-12.5	Type SP-9.5	Type SP-12.5	Type S	Binder	SAHM/Type II	Core Length (in)	Type	Thickness (in)	Depth (in)	Type	Class	Extent		
60	13.807	2.0	R1	Yes	0.9					2.4			3.3	SC	5.4	---	---	---	---	P	Side St. S. Pasco Ave.
61	13.887	4.0	R1	No	1.1					1.6			2.7	SC	6.3	---	---	---	---	P	Side St. S. Sumter Ave.
62	13.890	6.0	R2	No		1.2				1.5	2.0		4.7	NB	---	---	---	---	G	Patch Area	
63	13.892	3.0	R1	Yes	1.0					2.3			3.3	LR	4.7	---	---	---	---	F	Side St. Mills Ave.
64	13.943	3.0	R2	Yes		1.5		1.3					2.8	NB	---	2.8	A	II	S	P	
65	13.963	4.0	R1	No	1.2					1.6	4.5*		7.3	LR	8.6	---	---	---	---	P	Side St. S. Roberts *RAP layer
66	14.034	3.0	R1	Yes	1.0					2.9			3.9	SC	9.1	---	---	---	---	F	Side St. S.Luther
67	14.098	2.5	R2	Yes				1.6		2.5			4.1	SC	6.8	---	---	---	---	G	Patch Area
68	14.108	4.0	R1	No				1.0					1.0	SC	10.0	---	---	---	---	G	Side St. S Roger
69	14.170	4.0	R2	No				1.3		1.9			3.2	SC	8.3	---	---	---	---	G	Patch Area
70	14.160	2.5	L1	Yes				1.4		1.5			2.9	SC	6.1	---	---	---	---	G	Patch Area
92	12.366	6.5	L1	No		1.2				1.8			3.0	S.C	11.7	3.0	Br	III	S	P	
93	12.366	7.5	LLTL	Yes		1.1				2.6			3.7	LR	9.0	---	---	---	---	F	
94	12.316	5.0	L1	No				1.9		1.6			3.5	S.C	8.4	---	---	---	---	G	Patch Area
95	12.326	2.5	R1	Yes				1.6		2.6			4.2	S.C	7.8	---	---	---	---	G	Patch Area
96	12.386	2.5	R1	Yes	0.9					2.2			3.1	S.C	9.9	---	---	---	---	F	

Remarks: Crack Depth of "B" indicates full depth crack to the base. EOP = Edge of Pavement
Crack Extent: L= Light; M= Moderate; S= Severe **Pavement Condition:** G= Good; F= Fair; P= Poor **Crack Types:** A= Alligator; BI= Block; Br= Branch
 SL= Single Longitudinal; ST= Single Transverse; R= Reflective; J= Joint; OGFC= Open-Graded FC Stress Crack
Base Types: LR= Limerock; COQ= Coquina; SC= Soil Cement; ABC= Asphalt Base; SAHM= Sand Asphalt Hot Mix; NB= No Base

State of Florida Department of Transportation
PAVEMENT EVALUATION AND CONDITION DATA SHEET

Project No.: 441562-1					Cored By: Ardaman								Date: 6/3/2019				Page No.: 4 of 9				
County: Arcadia					Section No.: 04040000								From: Peace River				To: SE Baker Street				
Road No.: SR 70																					
Core No.	MP	Distance from left edge of lane (ft.)	Lane	Wheel Path	Pavement Layers (in.)								Base		Crack				Pavt Cond.	Comments	
					FC-3	FC-9.5	FC-12.5	Type SP-9.5	Type SP-12.5	Type S	Binder	SAHM / Type II	Core Length (in)	Type	Thickness (in)	Depth (in)	Type	Class			Extent
98	12.837	4.5	R1	No	0.9			1.9					2.8	ABC	8.7	---	---	---	---	F	Side St. S. Robinson
99	12.952	3.0	R1	Yes	1.1					2.4			3.5	LR	6.3	---	---	---	---	P	Side St. N. Lee
100	13.020	2.0	R1	Yes	1.0						2.7		3.7	LR	8.3	B	Br	III	S	P	Side St. S. Dade
101	13.060	2.0	R1	Yes		1.8				3.0			4.8	ABC	7.2	---	---	---	---	G	Parch Area
102	13.090	4.0	R1	No		1.6				2.9			4.3	LR	10.3	---	---	---	---	F	Side St.S. Manatee
103	13.158	6.0	R1	No		1.4				2.8			4.2	ABC	6.6	---	---	---	---	F	Side St. S Orange, Lane width 13'-10"
104	13.229	8.0	R1	No		2.0		2.2					4.2	ABC	9.7	---	---	---	---	F	Side St. S.Munroe
105	13.296	6.5	R1	No	0.8					2.3			3.1	SC	1.0	---	---	---	---	P	Side St. S. Polk , Concrete Base 1-2.5"
106	13.387	7.0	L3	No		1.1		0.9	2.4				4.4	S.C	11.5	---	---	---	---	G	Side St. DeSoto, Patch Area
107	13.466	6.5	R2	No	1.3	1.3		1.9	0.7	1.4			6.6	L.R	10.5	---	---	---	---	G	Side St. Bevard, Patch Area
108	13.524	8.5	R1	Yes		1.4			1.1				2.5	SAHM	1.9	2.5	Br	III	S	P	Cracked Base
109	13.534	4.0	R1	No		1.6		1.7					3.4	S.C	7.6	---	---	---	---	F	Side St. S. Volusia
110	13.605	3.5	R1	No	1.0				3.0				4.0	S.C	6.0	---	---	---	---	P	Side St. S. Hillborough
111	13.670	2.5	R1	Yes	0.8				5.7				6.5	NB	---	---	---	---	---	F	Side St. S. Hernando
112	13.709	3.0	R1	Yes	0.8				2.5				3.3	NB	---	1.8	SL	II	M	P	
113	13.739	4.0	R1	No	1.0				3.7				4.7	NB	---	---	---	---	---	F	Side St. S. Osceola, Lane width 8'

Remarks: Crack Depth of "B" indicates full depth crack to the base. EOP = Edge of Pavement
Crack Extent: L= Light; M= Moderate; S= Severe **Pavement Condition:** G= Good; F= Fair; P= Poor **Crack Types:** A= Alligator; Bl= Block; Br= Branch
 _SL= Single Longitudinal; ST= Single Transverse; R= Reflective; J= Joint; OGFC= Open-Graded FC Stress Crack
Base Types: LR= Limerock; COQ= Coquina; SC= Soil Cement; ABC= Asphalt Base; SAHM= Sand Asphalt Hot Mix; NB= No Base

**State of Florida Department of Transportation
PAVEMENT EVALUATION AND CONDITION DATA SHEET**

Project No.: 441562-1					Cored By: Ardaman								Date: 6/3/2019				Page No.: 5 of 9					
County: Arcadia					Section No.: 04040000								From: Peace River				To: SE Baker Street					
Road No.: SR 70																						
Core No.	MP	Distance from left edge of lane (ft.)	Lane	Wheel Path	Pavement Layers (in.)								Base		Crack				Pavt Cond.	Comments		
					FC-3	FC-9.5	FC-12.5	Type SP-9.5	Type SP-12.5	Type S	Binder	SAHM / Type II	Core Length (in)	Type	Thickness (in)	Depth (in)	Type	Class			Extent	
114	13.807	2.0	R1	Yes	1.1					3.6			4.7	NB	---	---	---	---	---	P	Side St. S. Pasco Ave	
115	13.887	4.0	R1	No	1.1					3.1	1.3*		5.5	NB	---	---	---	---	---	F	Side St. S. Sumter Ave. *Rap Layer	
116	13.892	4.0	R1	No	1.0					4.0			5.0	NB	---	---	---	---	---	P	Side St. S. Mills Ave. *Rap Layer	
117	13.963	1.0	R1	Yes	1.7						3.3*		5.0	NB	---	---	---	---	---	F	Side St. S. Roberts. ABC crumbled	
118	14.034	10.0	R1	No	1.0					2.0			3.0	SC	7.8	---	---	---	---	P	Side St.S. Luther	
119	14.180	2.0	R1	Yes				1.5		1.6			3.1	SC	10.7	---	---	---	---	G	New Pavement Area	
120	14.180	2.0	RLTL	Yes				1.5		1.8			3.3	SC	11.5	---	---	---	---	G	New Pavement Area	

Remarks: Crack Depth of "B" indicates full depth crack to the base. EOP = Edge of Pavement
Crack Extent: L= Light; M= Moderate; S= Severe **Pavement Condition:** G= Good; F= Fair; P= Poor **Crack Types:** A= Alligator; Bl= Block; Br= Branch
 SL= Single Longitudinal; ST= Single Transverse; R= Reflective; J= Joint; OGFC= Open-Graded FC Stress Crack
Base Types: LR= Limerock; COQ= Coquina; SC= Soil Cement; ABC= Asphalt Base; SAHM= Sand Asphalt Hot Mix; NB= No Base

**State of Florida Department of Transportation
PAVEMENT EVALUATION AND CONDITION DATA SHEET**

Project No.: 441562-1		Cored By: Ardaman											Date: 6/3/2019				Page No.: 6 of 9				
County: Arcadia		Section No.: 04040101											From: Peace River				To: SE Baker Street				
Road No.: SR 70																					
Core No.	MP	Distance from left edge of lane (ft.)	Lane	Wheel Path	Pavement Layers (in.)								Base		Crack				Pavt Cond.	Comments	
					FC-3	FC-9.5	FC-12.5	Type SP-9.5	Type SP-12.5	Type S	Binder	SAHM / Type II	Core Length (in)	Type	Thickness (in)	Depth (in)	Type	Class			Extent
2	0.008	9.0	R1	Yes				1.5		4.2			5.7	SC	9.3	---	---	---	---	G	Side St. Roger Ave., Patch Area
3	0.068	5.5	L2	No				1.5		2.1			3.6	SC	9.9	---	---	---	---	G	Patch Area (new)
4	0.103	7.5	L1	No				1.9		3.4			5.3	SC	7.0	---	---	---	---	G	Side St. N.E Oak, Patch Area
5	0.133	8.0	R1	No				1.4		4.2			5.5	SC	7.0	---	---	---	---	G	Side St. Luther Ave., Patch Area
6	0.272	14.0	L1	No				2.1		3.1			5.2	SC	7.8	---	---	---	---	G	Side St. Hickory East, Patch Area
7	0.309	8.0	L1	No	0.8					3.6			4.4	SC	8.6	---	---	---	---	F	Side St. Pasco
8	0.329	8.5	L2	Yes				1.8		2.3			4.1	SC	8.9	---	---	---	---	G	Patch Area (new)
9	0.377	6.0	L1	No	0.6					3.9			4.5	LR	7.3	---	---	---	---	F	Side St. N. Osceola
10	0.446	4.0	L1	No	0.6					4.3			4.9	NB	---	---	---	---	---	F	Side St. N. Hernando
11	0.514	5.0	L1	No	0.5					4.5			5.0	LR	6.0	---	---	---	---	P	Side St. Hillborough
12	0.582	4.5	L1	No	1.0					2.5			3.5	NB	---	---	---	---	---	P	Side St. N Volusia Ave.
13	0.622	8.0	L2	Yes	1.6					2.5	1.2		5.3	SC	5.7	---	---	---	---	P	Soil Cement under the SAHM
14	0.651	5.5	R2	No			1.5	2.3		7.3			11.1	SC	7.9	---	---	---	---	G	Side St. Brevard Ave.
15	0.737	3.0	L2	---			1.9			2.0			3.9	LR	14.1	---	---	---	---	G	Side St. Desoto Ave.
16	0.821	8.0	R2	Yes	0.8					2.5			3.3	SAHM	8.4	---	---	---	---	P	Side St. Polk
17	0.889	5.0	L1	No	0.7					3.4			4.1	SC	7.9	---	---	---	---	P	Side St. Monroe Ave.

Remarks: Crack Depth of "B" indicates full depth crack to the base. EOP = Edge of Pavement

Crack Extent: L= Light; M= Moderate; S= Severe **Pavement Condition:** G= Good; F= Fair; P= Poor **Crack Types:** A= Alligator; Bl= Block; Br= Branch

SL= Single Longitudinal; **ST=** Single Transverse; **R=** Reflective; **J=** Joint; **OGFC=** Open-Graded FC Stress Crack

Base Types: LR= Limerock; COQ= Coquina; SC= Soil Cement; ABC= Asphalt Base; SAHM= Sand Asphalt Hot Mix; NB= No Base

State of Florida Department of Transportation
PAVEMENT EVALUATION AND CONDITION DATA SHEET

Project No.: 441562-1		Cored By: Ardaman											Date: 6/3/2019				Page No.: 7 of 9				
County: Arcadia		Section No.: 04040101											From: Peace River				To: SE Baker Street				
Road No.: SR 70																					
Core No.	MP	Distance from left edge of lane (ft.)	Lane	Wheel Path	Pavement Layers (in.)								Base		Crack				Pavt Cond.	Comments	
					FC-3	FC-9.5	FC-12.5	Type SP-9.5	Type SP-12.5	Type S	Binder	SAHM / Type II	Core Length (in)	Type	Thickness (in)	Depth (in)	Type	Class			Extent
18	0.929	5.5	L2	No				2.4		1.7			4.1	SAHM	3.8	---	---	---	---	G	Patch Area (new)
19	0.958	7.0	L1	No			2.5			2.1			4.6	LR	10.4	---	---	---	---	F	Side St. N. Orange
20	0.978	5.5	L2	No			0.8		2.5				3.3	SC	16.6	---	---	---	---	P	
21	1.027	5.5	L1	No			1.2		3.3				4.5	SC	17.5	---	---	---	---	P	Side St. N. Manatee Ave.
22	1.057	1.5	L2	Yes			1.5		2.7				4.2	SC	---	3.5	SL	II	S	P	
23	1.096	4.5	L1	No			2.0		2.4				4.4	SC	15.6	---	---	---	---	F	Side St. Dade Ave.
24	1.166	7.0	L1	Yes			1.1		3.6				4.7	SC	15.3	---	---	---	---	F	Side St. N. Lee
25	1.206	4.5	L2	No				2.0		1.5			3.5	SC	6.5	---	---	---	---	G	
26	1.293	4.5	L2	No				2.0		2.0			4.0	SC	8.0	---	---	---	---	G	
27	1.343	7.0	LRTL	No	0.8					3.0			3.8	SC	9.1	---	---	---	---	G	
28	1.470	2.5	L1	Yes	1.8					3.2			5.0	SC	7.8	---	---	---	---	P	Side St. Yulee Ave
71	0.038	3.0	L1	Yes	0.9								1.0	SC	11.0	0.9	A	III	S	P	Side St. Oak St.
72	0.103	4.0	L1	No	0.8								0.8	SC	11.2	0.8	A	III	S	P	Side St. Luther Rd. /N.E Oak
73	0.209	7.5	L1	No				1.5		3.2			4.7	SC	6.9	---	---	---	---	G	Side St. Robert Ave.
74	0.286	7.0	R1	No				1.8		4.1			5.9	SC	6.6	---	---	---	---	G	Side St. Mills Ave., Patch Area
75	0.309	3.0	L1	Yes				1.3		4.3			5.6	SC	10.4	---	---	---	---	F	Side St. Pasco

Remarks: Crack Depth of "B" indicates full depth crack to the base. EOP = Edge of Pavement
Crack Extent: L= Light; M= Moderate; S= Severe **Pavement Condition:** G= Good; F= Fair; P= Poor **Crack Types:** A= Alligator; Bl= Block; Br= Branch
 _SL= Single Longitudinal; ST= Single Transverse; R= Reflective; J= Joint; OGFC= Open-Graded FC Stress Crack
Base Types: LR= Limerock; COQ= Coquina; SC= Soil Cement; ABC= Asphalt Base; SAHM= Sand Asphalt Hot Mix; NB= No Base

**State of Florida Department of Transportation
PAVEMENT EVALUATION AND CONDITION DATA SHEET**

Project No.: 441562-1		Cored By: Ardaman											Date: 6/3/2019				Page No.: 8 of 9				
County: Arcadia		Section No.: 04040101											From: Peace River				To: SE Baker Street				
Road No.: SR 70																					
Core No.	MP	Distance from left edge of lane (ft.)	Lane	Wheel Path	Pavement Layers (in.)								Base		Crack				Pavt Cond.	Comments	
					FC-3	FC-9.5	FC-12.5	Type SP-9.5	Type SP-12.5	Type S	Binder	SAHM / Type II	Core Length (in)	Type	Thickness (in)	Depth (in)	Type	Class			Extent
76	0.377	2.0	L1	Yes	1.4					2.9			4.3	SC	8.2	2.5	SL	II	S	P	Side St. N. Osceola
77	0.446	2.0	L1	Yes						6.1			6.1	NB	---	1.0	SL	II	S	P	Side St. N. Hernando
78	0.514	4.0	R1	No	1.2					3.9			5.1	NB	---	---	---	---	---	P	Side St. N. Hillborough
79	0.524	2.0	L1	Yes				2.0		6.2			8.2	NB	---	---	---	---	---	G	Patch Area
80	0.582	7.0	L1	No	1.1					4.5			5.6	SC	8.4	---	---	---	---	P	Side St. N. Volusia
81	0.622	2.0	L1	Yes	0.9					6.6			7.5	SHEL	4.3	---	---	---	---	P	
82	0.651	5.0	R1	No		1.2				9.2			10.4	SC	8.1	---	---	---	---	G	Core on Brevard Ave. approx 100' S of Intersection
83	0.737	4.5	L1	No		0.9		1.0		1.9			3.8	SC	12.2	---	---	---	---	G	Core on Desoto Ave. approx. 100' between Oak and E. Hickory St.
84	0.821	8.0	R1	No		2.4				1.1		1.3	4.8	SAHM	1.3	---	---	---	---	G	Side St. Polk
85	0.889	7.5	L1	Yes		1.0				1.1		4.1	6.5	SAHM	4.1	1.3	SL	II	L	P	Side St. Monroe
86	0.958	4.0	R1	No	0.8					4.2			5.0	SC	2.0	---	---	---	---	P	Side St. N. Orange
87	1.027	2.5	R1	Yes		1.8				3.5			5.3	NB	---	---	---	---	---	F	Side St. N. Manatee
88	1.057	4.5	L1	No		1.5				3.0		1.5	6.0	SAHM	1.5	---	---	---	---	G	Patch Area
89	1.096	9.0	R1	Yes		1.8				3.7			5.5	LR	3.3	---	---	---	---	F	Side St. Dade
90	1.166	9.0	R1	Yes		2.0				4.3			6.3	NB	---	---	---	---	---	F	Side St. N. Lee,
91	1.313	4.5	L1	No				2.1		1.4	1.9		5.4	NB	---	---	---	---	---	G	

Remarks: Crack Depth of "B" indicates full depth crack to the base. EOP = Edge of Pavement
Crack Extent: L= Light; M= Moderate; S= Severe Pavement Condition: G= Good; F= Fair; P= Poor Crack Types: A= Alligator; Bl= Block; Br= Branch
SL= Single Longitudinal; ST= Single Transverse; R= Reflective; J= Joint; OGFC= Open-Graded FC Stress Crack
Base Types: LR= Limerock; COQ= Coquina; SC= Soil Cement; ABC= Asphalt Base; SAHM= Sand Asphalt Hot Mix; NB= No Base

