

06/20/16

FLORIDA DEPARTMENT OF TRANSPORTATION  
PAVEMENT CORING REPORTING

PCRPJ03  
PCRO103

PAVEMENT EVALUATION CORING AND CONDITION DATA

FIN PROJ: 439431-1-31-01

TYP SECT: 01

FA PROJ:

COUNTY: HENDRY

SR NUMBER: SR 80

MEDIAN: 08 VEGETATION

CURBED: NO

NAME: SR 80

FROM: LEE C/L

TO: GRANDMAS GROVE RV

BEG MP: .00

END MP: 6.26 LENGTH: 6.26

PROJECT MEASUREMENT: ENGLISH

CORED BY: TIM

DATE: 2016-06-13

LANES: 4 @ 12 FEET

SHOULDER TYPE

INSIDE: 1 PAVED

OUTSIDE: 1 PAVED

CURB & GUTTER: NO



06/20/16

FLORIDA DEPARTMENT OF TRANSPORTATION  
PAVEMENT CORING REPORTING

PCRPJ03  
PCRO303

PAVEMENT EVALUATION CORING AND CONDITION DATA

COMMENTS

SEQ

---

-----

NO DATA FOUND FOR REPORT

06/20/16

FLORIDA DEPARTMENT OF TRANSPORTATION  
PAVEMENT CORING REPORTING

PCRPJ03  
PCRO403

CODE DESCRIPTIONS

CRACK TYPE TYPE DESCRIPTION  
=====

A ALLIGATORING IN WHEELPATH

B BLOCK CRACKING

C COMBINATION OF TYPES

CRACK EXTNT EXTENT DESCRIPTION  
=====

L LIGHT

M MEDIUM

S SEVERE

CRACK CLASS CLASS DESCRIPTION  
=====

IB UNKNOWN

II UNKNOWN

III UNKNOWN

FLORIDA DEPARTMENT OF TRANSPORTATION  
PAVEMENT CORING REPORTING

CODE DESCRIPTIONS

SURFACE LAYER CODE =====	DESCRIPTION =====
ARMI	ASPHALT RUBBER MEMBRANE INTERL
BIND	ASPHALT BINDER COURSE
BRCK	BRICK PAVERS
CONC	PORTLAND CEMENT CONCRETE
CRL	CRACK RELIEF LAYER
FAB	PAVEMENT OVERLAY FABRIC
FC	FRICTION COURSE
FC1	FRICTION COURSE 1
FC2	FRICTION COURSE 2
FC3	FRICTION COURSE 3
FC4	FRICTION COURSE 4
FC5	FRICTION COURSE 5
FC5B	FRICTION COURSE 5 BONDED
FC6	FRICTION COURSE 6
F12M	FRIC. COURSE 12.5 MODIFIED
F125	FRICTION COURSE 12.5
F95	FRICTION COURSE 9.5
F95M	FRIC. COURSE 9.5 MODIFIED
S	TYPE S ASPHALTIC CONCRETE
SAHM	SAND ASPHALT HOT MIX
SP1C	9.5 SUPERPAVE COARSE GRADED
SP1F	9.5 SUPERPAVE FINE GRADED
SP2C	12.5 SUPERPAVE COARSE GRADED
SP2F	12.5 SUPERPAVE FINE GRADED
SP3C	19.0 SUPERPAVE COARSE GRADED
SP3F	19.0 SUPERPAVE FINE GRADED
ST	SURFACE TREATMENT
S1	TYPE S-I ASPHALTIC CONCRETE
S2	TYPE S-II ASPHALTIC CONCRETE
S3	TYPE S-III ASPHALTIC CONCRETE
T1	TYPE I ASPHALTIC CONCRETE
T2	TYPE II ASPHALTIC CONCRETE
T3	TYPE III ASPHALTIC CONCRETE
UNIM	UNIMPROVED SURFACE
UNKW	UNKNOWN
WC	WEARING COURSE
WC1	WEARING COURSE 1
WC2	WEARING COURSE 2
WC3	WEARING COURSE 3
WC4	WEARING COURSE 4
WC5	WEARING COURSE 5
WC6	WEARING COURSE 6
WC7	WEARING COURSE 7
WC8	WEARING COURSE 8

11/07/17

FLORIDA DEPARTMENT OF TRANSPORTATION  
PAVEMENT CORING REPORTING

PCRPJ03  
PCRO103

PAVEMENT EVALUATION CORING AND CONDITION DATA

FIN PROJ: 439431-1-31-01

TYP SECT: 01

FA PROJ:

COUNTY: HENDRY

SR NUMBER: SR 80

MEDIAN: 08 VEGETATION

CURBED: NO

NAME:

FROM: LEE C/L

TO: GRANDMAS GROVE RV

BEG MP: .00

END MP: 6.53 LENGTH: 6.53

PROJECT MEASUREMENT: ENGLISH

CORED BY: TIM

DATE: 2017-11-06

LANES: 4 @ 12 FEET

SHOULDER TYPE

INSIDE: 1 PAVED

OUTSIDE: 1 PAVED

CURB & GUTTER: NO

PAVEMENT EVALUATION CORING AND CONDITION DATA

CORE NO.	MILE POST	VFY	W LN	P	PAVEMENT LAYER			CORE			CRACK			PMT CND	COMMENTS
					--TOP	FC5	SP2F	LNGLTH	BASE	SUB	DEPTH	TYP	CLSS		
1	.564	N	R2	Y	.70	FC5	SP2F	3.20	12.0	12.0		C	IB	L	F
2	1.000	N	R1	Y	1.20			4.20	12.0	12.0	1.20	C	IB	L	F
3	1.500	N	R2	N	.60			3.40	12.0	12.0	.70	C	IB	L	F
4	2.000	N	R1	N	.60			2.80	12.0	12.0		C	IB	L	F
5	2.500	N	R2	N	1.20			4.00	12.0	12.0	1.20	C	IB	L	F
6	3.000	N	R1	N	.70			3.20	12.0	12.0	.70	C	IB	L	F
7	3.590	N	R2	Y	1.00			4.80	12.0	12.0		C	IB	L	F
8	4.000	N	R1	Y	1.00			4.80	12.0	12.0	2.20	C	IB	L	F
9	4.350	N	R2	N	.70			4.60	12.0	12.0	2.30	C	IB	M	P
10	5.000	N	R1	N	.60			4.70	12.0	12.0	2.60	C	IB	S	P
11	5.500	N	R2	N	.80			4.60	12.0	12.0	2.70	C	IB	M	P
12	6.022	N	R1	N	1.30			4.60	12.0	12.0	1.30	C	IB	L	P
13	.564	N	L2	Y	.50			3.30	12.0	12.0		C	IB	L	F
14	1.000	N	L1	Y	1.00			3.20	12.0	12.0					F
15	1.500	N	L2	N	.70			2.70	12.0	12.0		C	IB	L	F
16	2.000	N	L1	N	.70			3.70	12.0	12.0					F
17	2.500	N	L2	N	.90			3.60	12.0	12.0		C	IB	L	F
18	3.000	N	L1	N	.80			3.40	12.0	12.0		C	IB	L	F
19	3.747	N	L2	Y	.70			4.30	12.0	12.0	1.70	C	IB	M	P
20	4.047	N	L1	Y	.90			4.50	12.0	12.0	2.00	C	IB	M	P
21	4.431	N	L2	N	.90			5.00	12.0	12.0	2.50	C	IB	M	P
22	5.000	N	L1	N	1.10			4.50	12.0	12.0	2.00	C	IB	L	P
23	5.490	N	L2	N	.70			3.50	12.0	12.0	2.00	C	IB	M	P
24	6.000	N	L1	N	1.00			4.70	12.0	12.0	1.80	C	IB	L	P
						FC5	SP2F								
25	.564	N	OR	N	.90			2.90	4.0	12.0					F
26	1.500	N	OR	N	.80			2.50	4.3	12.0					F
27	2.500	N	OR	N	1.20			3.20	3.8	12.0					F
						FC5	SP2F								
28	3.590	N	OR	N	1.10			2.30	6.0	12.0					F
29	4.350	N	OR	N	.70			2.70	12.0	12.0					F
30	5.500	N	OR	N	1.40			2.80	8.0	12.0					F
						FC5	SP2F								
31	5.490	N	OL	N	1.10			2.80	4.5	12.0					F
32	4.431	N	OL	N	1.30			2.80	3.3	12.0					F
33	3.747	N	OL	N	1.30			2.80	5.0	12.0					F
34	2.500	N	OL	N	.80			2.50	4.1	12.0					F
35	1.500	N	OL	N	.70			2.40	4.8	12.0					F
36	.564	N	OL	N	.80			2.80	4.2	12.0					F
						FC5	SP2F								
37	1.690	N	R2	N	.70			4.10	12.0	12.0					F
38	4.350	N	R2	N	.80			4.30	12.0	12.0					F
39	5.174	N	L2	N	1.00			3.50	12.0	12.0					F
40	3.115	N	L2	N	.80			3.30	12.0	12.0					F
41	.140	N	R1	N	1.00			4.30	12.0	12.0					F
42	1.423	N	R1	N	.90			4.20	12.0	12.0					F
43	4.000	N	R1	N	1.00			4.70	12.0	12.0					F
44	5.632	N	L1	N	.70			4.90	12.0	12.0					F
	.000														

RT TURN  
RT TURN  
RT TURN  
RT TURN  
LT TURN  
LT TURN  
LT TURN  
LT TURN

11/07/17

FLORIDA DEPARTMENT OF TRANSPORTATION  
PAVEMENT CORING REPORTING

PCRPJ03  
PCRO303

PAVEMENT EVALUATION CORING AND CONDITION DATA

COMMENTS

SEQ

-----

NO DATA FOUND FOR REPORT



## CODE DESCRIPTIONS

CRACK TYPE	TYPE DESCRIPTION
=====	=====

A	ALLIGATORING IN WHEELPATH
---	---------------------------

B	BLOCK CRACKING
---	----------------

C	COMBINATION OF TYPES
---	----------------------

CRACK EXTNT	EXTENT DESCRIPTION
=====	=====

L	LIGHT
---	-------

M	MEDIUM
---	--------

S	SEVERE
---	--------

CRACK CLASS	CLASS DESCRIPTION
=====	=====

IB	UNKNOWN
----	---------

II	UNKNOWN
----	---------

III	UNKNOWN
-----	---------

## CODE DESCRIPTIONS

SURFACE LAYER CODE =====	DESCRIPTION =====
ARMI	ASPHALT RUBBER MEMBRANE INTERL
BIND	ASPHALT BINDER COURSE
BRCK	BRICK PAVERS
CONC	PORTLAND CEMENT CONCRETE
CRL	CRACK RELIEF LAYER
FAB	PAVEMENT OVERLAY FABRIC
FC	FRICTION COURSE
FC1	FRICTION COURSE 1
FC2	FRICTION COURSE 2
FC3	FRICTION COURSE 3
FC4	FRICTION COURSE 4
FC5	FRICTION COURSE 5
FC5B	FRICTION COURSE 5 BONDED
FC6	FRICTION COURSE 6
F12M	FRIC. COURSE 12.5 MODIFIED
F125	FRICTION COURSE 12.5
F95	FRICTION COURSE 9.5
F95M	FRIC. COURSE 9.5 MODIFIED
S	TYPE S ASPHALTIC CONCRETE
SAHM	SAND ASPHALT HOT MIX
SP1C	9.5 SUPERPAVE COARSE GRADED
SP1F	9.5 SUPERPAVE FINE GRADED
SP2C	12.5 SUPERPAVE COARSE GRADED
SP2F	12.5 SUPERPAVE FINE GRADED
SP3C	19.0 SUPERPAVE COARSE GRADED
SP3F	19.0 SUPERPAVE FINE GRADED
ST	SURFACE TREATMENT
S1	TYPE S-I ASPHALTIC CONCRETE
S2	TYPE S-II ASPHALTIC CONCRETE
S3	TYPE S-III ASPHALTIC CONCRETE
T1	TYPE I ASPHALTIC CONCRETE
T2	TYPE II ASPHALTIC CONCRETE
T3	TYPE III ASPHALTIC CONCRETE
UNIM	UNIMPROVED SURFACE
UNKW	UNKNOWN
WC	WEARING COURSE
WC1	WEARING COURSE 1
WC2	WEARING COURSE 2
WC3	WEARING COURSE 3
WC4	WEARING COURSE 4
WC5	WEARING COURSE 5
WC6	WEARING COURSE 6
WC7	WEARING COURSE 7
WC8	WEARING COURSE 8