

STATE OF FLORIDA DEPARTMENT OF TRANSPORTATION
PAVEMENT EVALUATION CORING AND CONDITION DATA

Cored By: District Materials Office

Coring Completion Date: 2/5/2025

Typical Section: 1

W.P.I. No.:	Name: SR 82	Lanes: 2 Lanes
Fin. Proj. ID: 455785-1	From: AT ALABAMA RD. S., NEW SIGNAL	Shoulder Type and Condition:
F.A. Project No.:	To:	Inside: Paved
County: Lee	Beg MP: 14.552	End MP: 14.805
Roadway ID: 12070000	Length: 0.253	Outside: Paved
SR No.: 82	Median Curbed Y/N	Curb & Gutter (Y/N): N
Overall Pavement Condition (from DMO field review): Fair		

All Cores

CORE NO.	MILE POST ²	LANE TYPE	LANE	WP (Y/N)	PAVEMENT LAYER (IN.)								TOTAL ASPHALT THICKNESS (IN.)	BASE			STABILIZED SUBGRADE ³	CRACK				PAVEMENT CONDITION	COMMENTS	
					FC9.5	SP9.5	WC									LR				DEPTH (IN.)	TYPE			CLASS
1	14.696	ML	L1	Y	1.7	0.4	0.4						2.5	6.5			12.0					F	ALABAMA RD S., LLTL / L1	
2	14.696	ML	L1	N	1.2	3.2							4.4	13.0			12.0					F	ALABAMA RD S., LLTL / L1	
3	14.696	TL	LR	Y	1.0	2.5							3.5	11.0			12.0					F	ALABAMA RD S.	
4	14.696	TL	LR	Y	0.9	2.9							3.8	13.5			12.0					F	ALABAMA RD S.	
5	14.696	S	OL	N	0.9	2.5							3.4	13.0			12.0					F	ALABAMA RD S.	
6	14.696	ML	R1	Y	1.4	2.0	0.5						3.9	7.0			12.0	3.9	C	I	S	P	ALABAMA RD S., BASE CRACK	
7	14.696	ML	L1	N	1.4	1.0							2.4	7.0			12.0					F	ALABAMA RD S.	
8	14.696	S	OL	N	1.0	0.9							1.9	7.0			12.0					F	ALABAMA RD S.	
AVERAGE					1.19	1.93	0.45						3.23	9.75			12.00	3.90						
MAX					1.70	3.20	0.50						4.40	13.50			12.00	3.90						
MIN					0.90	0.40	0.40						1.90	6.50			12.00	3.90						
LAYER COEF.					0.25	0.25	UNKW							0.18			0.08							

Notes:

1. The data presented on this table is specific only at the locations cored at the time of the investigation. Should questions arise regarding the pavement composition, it is incumbent upon those raising the question to perform additional exploration as necessary.
2. Mile posts are approximate based on field recorded measurements using a Distance Measuring Instrument (DMI) or a GPS unit.
3. Stabilization thickness was checked on 10% of the coring locations. For pavement design, assume 12 inches of thickness for stabilization.
4. The cross slope is approximate and measured in the center of the lane.
5. A blank cell indicates measurement was not recorded.
6. A value of "UNK" indicates material was encountered but the total thickness was not determined.

<u>Lane Designations - Decreasing MP</u> OL/IL - Outside/Inside Shoulder L1 - 1st Lane Left of Centerline LL/LR - Left/Right Turn Lane	<u>Lane Designations - Increasing MP</u> OR/IR - Outside/Inside Shoulder R1 - 1st Lane Right of Centerline RL/RR - Left/Right Turn Lane	<u>Lane Type</u> ML - Mainline TL - Turn Lane CO - Crossover	<u>Crack Type</u> A - Alligator B - Block C - Combination	<u>Crack Rating</u> Class IB - Hairline cracks that are ≤ 1/8 inch wide Class II - Cracks > than 1/8 inch and ≤ 1/4 inch Class III - Cracks > 1/4 inch	<u>Extent</u> L - Light M - Moderate S - Severe	<u>Pavement Condition</u> G - Good F - Fair P - Poor
---	--	---	--	---	--	---