

STATE OF FLORIDA DEPARTMENT OF TRANSPORTATION  
**PAVEMENT EVALUATION CORING AND CONDITION DATA**

Cored By: Intertek - PSI

Coring Completion Date: 3/29/2023

Typical Section: \_\_\_\_\_

W.P.I. No.:		Name: SR 62				Lanes: 2 Lane Rural Minor Arterial Roadway	
Fin. Proj. ID: 449118-1		From: E of SR 37				Shoulder Type and Condition: Fair	
F.A. Project No.:		Roadway ID: 13060000		To: HARDEE COUNTY LINE		Inside: None	
County: MANATEE		SR No.: 62		Beg MP: 23.215	End MP: 19.376	Length: 3.839	
Overall Pavement Condition (from DMO field review): Fair		Median Curbed (Y/N): N	Paved	Lawn	Other:	Curb & Gutter (Y/N): N	

**All Cores**

CORE NO.	MILE POST <sup>2</sup>	LANE TYPE	LANE	WP (Y/N)	PAVEMENT LAYER (IN.)								TOTAL ASPHALT THICKNESS (IN.)	BASE			STABILIZED SUBGRADE <sup>3</sup>	CRACK				PAVEMENT CONDITION	COMMENTS	
					FC3	S	WC	SAHM								LR		ABC-2	SAHM	DEPTH (IN.)	TYPE			CLASS
1	19.399	S	OR	N	1.0	2.6							3.6		2.8							F		
2	19.586	ML	R1	N	0.9	5.3							6.2			2.8		7.0	6.2	B	III	S	P	
3	19.866	S	OR	N	0.9	1.1							2.0		3.0								F	
4	20.151	TL	RR	N	1.4	4.6							6.0		8.0				2.0	B	IB	L	P	Slippage in LWP
5	20.158	S	OR	N	1.1								1.1		2.8			5.0					P	
6	20.174	SS	NA	N	1.1								1.1		2.9			9.0					P	Duette Rd. Patches near core.
7	20.270	ML	R1	N	1.0	1.6							2.6			UNK			2.6	B	II	M	F	SAHM-base not delivered. Measured delivered core.
8	20.456	S	OR	N	0.9	3.3							4.2		2.8								F	
9	20.801	ML	R1	Y	1.2	3.3							4.5	8.0					4.5	B	IB	M	F	
10	21.087	S	OR	N	1.0	1.1							2.1		3.4				2.1	B	IB	L	F	Base crack
11	21.273	ML	R1	Y	0.9	1.4							2.3		10.7				0.9	A	IB	M	F	
12	21.446	S	OR	N	0.9	1.1							2.0		2.9			5.0	0.2	B	IB	L	F	
13	21.539	ML	R1	N	1.0	5.6							6.6	10.0					6.6	B	II	M	F	Box culvert
14	21.677	ML	R1	Y	1.0	3.5							4.5			UNK			4.5	B	IB	L	F	SAHM-base not delivered. Measured delivered core.
15	21.943	S	OR	N	1.0	1.4							2.4		4.2				2.4	B	II	L	F	
16	22.233	ML	R1	Y	0.9	4.2	0.7						5.8			8.0			5.8	B	II	M	F	Base fell apart, base crack
17	22.516	S	OR	N	0.9	1.4							2.3		4.1								F	
18	22.719	ML	R1	Y	0.9	5.0	0.5						6.4			8.0			6.4	B	III	M	F	Base fell apart, base crack
19	22.970	S	OR	N	0.9	1.6							2.5		3.3								F	
20	23.151	ML	R1	Y	0.9	5.5	0.4						6.8			5.0		6.0	6.8	B	II	M	F	Base fell apart, base crack
21	23.195	S	OL	N	1.3	1.2							2.5		3.5				0.8	B	IB	L	F	
22	23.079	ML	L1	N	1.1	3.9	0.5						5.5			8.0			5.5	B	II	M	P	Base fell apart, base crack
23	22.844	S	OL	N	0.8	1.7							2.5		3.5				2.5	B	III	M	P	Base crack
24	22.618	ML	L1	Y	1.0	3.7	0.5						5.2			7.8		3.0	5.2	B	II	M	F	Base fell apart, base crack
25	22.300	S	OL	N	1.1	1.9							3.0		3.7								F	
26	22.084	ML	L1	Y	0.9	4.0	0.4	3.3					8.6	8.0					8.6	B	II	M	F	Base crack
27	21.826	S	OL	N	0.8	2.2							3.0		3.0								F	
28	21.576	ML	L1	N	1.0	4.1	0.4	3.1					8.6	8.0					8.6	B	II	M	F	Base crack
29	21.314	S	OL	N	1.1	2.4							3.5		3.1				1.1	B	IB	L	F	
30	21.166	ML	L1	Y	0.9	4.0	0.6	3.5					9.0	8.0					9.0	B	II	S	F	SAHM fell apart.
31	20.970	S	OL	N	1.0	3.6							4.6		4.5								F	
32	20.783	ML	L1	Y	0.9	4.1							5.0	11.0					5.0	B	II	M	F	

STATE OF FLORIDA DEPARTMENT OF TRANSPORTATION  
**PAVEMENT EVALUATION CORING AND CONDITION DATA**

Cored By: Intertek - PSI

Coring Completion Date: 3/29/2023

Typical Section: \_\_\_\_\_

W.P.I. No.:		Name: SR 62		Lanes: 2 Lane Rural Minor Arterial Roadway	
Fin. Proj. ID: 449118-1		From: E of SR 37		Shoulder Type and Condition: Fair	
F.A. Project No.:		Roadway ID: 13060000	To: HARDEE COUNTY LINE		Inside: None
County: MANATEE	SR No.: 62	Beg MP: 23.215	End MP: 19.376	Length: 3.839	Outside: Paved
Overall Pavement Condition (from DMO field review): Fair		Median Curbed (Y/N): N	Paved	Lawn	Other:
					Curb & Gutter (Y/N): N

**All Cores**

CORE NO.	MILE POST <sup>2</sup>	LANE TYPE	LANE	WP (Y/N)	PAVEMENT LAYER (IN.)								TOTAL ASPHALT THICKNESS (IN.)	BASE			STABILIZED SUBGRADE <sup>3</sup>	CRACK				PAVEMENT CONDITION	COMMENTS	
					FC3	S	WC	SAHM								LR		ABC-2	SAHM	DEPTH (IN.)	TYPE			CLASS
33	20.655	ML	L1	Y	1.0	3.5							4.5	11.5				1.0	B	IB	L	F	Box culvert	
34	20.216	S	OL	N	1.0	2.1							3.1		2.0			3.1	B	II	M	F	Base crack	
35	19.954	ML	L1	Y	1.0	5.7	0.5	3.3					10.5	5.5				10.5	B	II	S	P	SAHM fell apart.	
36	19.704	S	OL	N	0.8	2.2							3.0		3.6			3.0	B	II	M	F	Base crack	
37	19.481	ML	L1	Y	0.6	3.9	0.7	3.1					8.3	8.0				3.7	B	IB	L	F	SAHM fell apart.	
<b>AVERAGE</b>					<b>0.98</b>	<b>3.08</b>	<b>0.52</b>	<b>3.26</b>					<b>4.47</b>	<b>8.67</b>	<b>3.89</b>	<b>6.60</b>		<b>5.83</b>	<b>4.39</b>					
<b>MAX</b>					<b>1.40</b>	<b>5.70</b>	<b>0.70</b>	<b>3.50</b>					<b>10.50</b>	<b>11.50</b>	<b>10.70</b>	<b>8.00</b>		<b>9.00</b>	<b>10.50</b>					
<b>MIN</b>					<b>0.60</b>	<b>1.10</b>	<b>0.40</b>	<b>3.10</b>					<b>1.10</b>	<b>5.50</b>	<b>2.00</b>	<b>2.80</b>		<b>3.00</b>	<b>0.20</b>					
<b>LAYER COEF.</b>					<b>0.17</b>	<b>0.25</b>	<b>UNKW</b>	<b>0.11</b>						<b>0.18</b>	<b>0.16</b>	<b>0.11</b>		<b>0.08</b>						

Notes:

1. The data presented on this table is specific only at the locations cored at the time of the investigation. Should questions arise regarding the pavement composition, it is incumbent upon those raising the question to perform additional exploration as necessary.
2. Mile posts are approximate based on field recorded measurements using a Distance Measuring Instrument (DMI) or a GPS unit.
3. Stabilization thickness was checked on 10% of the coring locations. For pavement design, assume 12 inches of thickness for stabilization.
4. The cross slope is approximate and measured in the center of the lane.
5. A blank cell indicates measurement was not recorded.
6. A value of "UNK" indicates material was encountered but the total thickness was not determined.

<u>Lane Designations - Decreasing MP</u>	<u>Lane Designations - Increasing MP</u>	<u>Lane Type</u>		<u>Crack Type</u>	<u>Crack Rating</u>	<u>Extent</u>	<u>Pavement Condition</u>
OL/IL - Outside/Inside Shoulder	OR/IR - Outside/Inside Shoulder	ML - Mainline	S - Shoulder	A - Alligator	Class IB - Hairline cracks that are ≤ 1/8 inch wide	L - Light	G - Good
L1 - 1st Lane Left of Centerline	R1 - 1st Lane Right of Centerline	TL - Turn Lane	SS - Side Street	B - Block	Class II - Cracks > than 1/8 inch and ≤ 1/4 inch	M - Moderate	F - Fair
LL/LR - Left/Right Turn Lane	RL/RR - Left/Right Turn Lane	CO - Crossover	BR - Bridge Approach/Departure	C - Combination	Class III - Cracks > 1/4 inch	S - Severe	P - Poor