

STATE OF FLORIDA DEPARTMENT OF TRANSPORTATION
PAVEMENT EVALUATION CORING AND CONDITION DATA

Cored By: Brent Grubbs Date: 11/20/2019 Page: 1 of 1 Typical Section: 01

W.P.I. No.:				Name:	Davenport Complete Streets				Lanes:	2 @ 12 feet	
Fin. Proj. ID:	435094-1-31-01			From:	NA				Shoulder Type and Condition:		
F.A. Project No.:	D118116B			To:	NA				Inside:	NA	
County:	Polk	SR No.:	Not Found	Beg MP:	0.000	End MP:	0.000	Length:	0.000	Outside:	Paved
Median Curbed (Y/N):	N	Paved		Lawn		Other:		Curb & Gutter	No	No	

US 92/US 17/SR 600

CORE NO.	MILE POST	LANE	WP (Y/N)	PAVEMENT LAYER (IN.)					TOTAL ASPHALT THICKNESS (IN.)	BASE				STABILIZED SUBGRADE	CRACK				PAVEMENT CONDITION	COMMENTS	
				F-9.5	FC-2	SP1F	S	WC		LR	CONC	ABC	SAHM		DEPTH (IN.)	TYPE	CLASS	EXTENT			
1	3.856	L1	N	1.20		1.70			2.90		7.0			12.0	1.20	C	IB	L	F	Gore area, sheet piling between concrete	
2	3.833	L1	Y	1.20		1.30			2.50		6.9			12.0	2.50	C	IB	S	F	Left turn lane	
3	3.845	L1	Y	1.10			3.10	0.50	4.70	7.0				12.0	4.70	B	IB	S	P	Cracked base	
4	3.845	R1	Y	1.00		1.00	0.80		2.80		7.8			12.0	2.80	C	IB	M	F	Sheet piling between concrete	
5	3.843	R1	N	1.30			0.20	0.50	2.00	7.0				12.0					F	Entrance to business	
AVERAGE				1.16		1.33	1.37	0.50	2.98	7.00	7.23			12.00	2.80						

W BAY STREET

CORE NO.	MILE POST	LANE	WP (Y/N)	PAVEMENT LAYER (IN.)					TOTAL ASPHALT THICKNESS (IN.)	BASE				STABILIZED SUBGRADE	CRACK				PAVEMENT CONDITION	COMMENTS	
				F-9.5	FC-2	SP1F	S	WC		LR	CONC	ABC	SAHM		DEPTH (IN.)	TYPE	CLASS	EXTENT			
6	3.814	R1	N	1.00			0.70	0.50	2.20	6.0				12.0					F		
7	3.814	R1	Y		0.80			0.40	1.20	5.0				12.0	1.20	C	IB	S	P	Parallel parking, base crack	
8	3.814	R1	N		1.00		1.40	0.50	2.90	6.5				12.0					F		
9	3.814	L1	N		1.10		0.90	0.40	2.40	5.5				12.0	2.40	C	IB	S	P	Parallel parking, base crack	
10	3.814	L1	N		1.10		0.70	0.30	2.10	4.5				12.0	3.50	C	IB	S	F	Transverse crack from concrete	
11	3.814	L1	Y		1.10		0.80	0.50	2.40	5.0				12.0	2.40	C	IB	S	F	Transverse crack, base crack	
12	3.814	L1	Y	1.00					1.00	5.0				12.0					F	Left turn lane	
13	3.814	L1	N	1.30					1.30	5.5				12.0					F		
AVERAGE				1.10	1.02		0.90	0.43	1.94	5.38				12.00	2.38						

ESCAMBIA STREET

CORE NO.	MILE POST	LANE	WP (Y/N)	PAVEMENT LAYER (IN.)					TOTAL ASPHALT THICKNESS (IN.)	BASE				STABILIZED SUBGRADE	CRACK				PAVEMENT CONDITION	COMMENTS	
				F-9.5	FC-2	SP1F	S	WC		LR	CONC	ABC	SAHM		DEPTH (IN.)	TYPE	CLASS	EXTENT			
14	3.986	R1	Y			0.30	2.20		2.50	4.0				12.0	2.50	C	IB	S	F	Transverse crack, base crack	
15	3.986	L1	Y			0.40	0.80	0.30	1.50	5.0				12.0					F	Longitudinal crack, base crack	
AVERAGE						0.35	1.50	0.30	2.00	4.50				12.00	2.50						

STATE OF FLORIDA DEPARTMENT OF TRANSPORTATION
PAVEMENT EVALUATION CORING AND CONDITION DATA

Cored By: Brent Grubbs Date: 11/20/2019 Page: 1 of 1 Typical Section: 01

W.P.I. No.:				Name:	Davenport Complete Streets			Lanes:	2 @ 12 feet		
Fin. Proj. ID:	435094-1-31-01			From:	NA			Shoulder Type and Condition:			
F.A. Project No.:	D118116B			To:	NA			Inside:	NA		
County:	Polk	SR No.:	Not Found	Beg MP:	0.000	End MP:	0.000	Length:	0.000	Outside:	Paved
Median Curbed (Y/N):	N	Paved	Lawn	Other:				Curb & Gutter	No	No	

MARKET STREET																				
CORE NO.	MILE POST	LANE	WP (Y/N)	PAVEMENT LAYER (IN.)					TOTAL ASPHALT THICKNESS (IN.)	BASE				STABILIZED SUBGRADE	CRACK				PAVEMENT CONDITION	COMMENTS
				FC-5	FC-2	SP1F	S	WC		LR	CONC	ABC	SAHM		DEPTH (IN.)	TYPE	CLASS	EXTENT		
16	3.865	L1	Y			0.40	0.80	0.40	1.60	4.0				12.0	1.80	C	IB	S	F	Transverse crack
17	3.865	L1	N			0.50	0.80	0.70	2.00	3.0				12.0	2.00	C	IB	S	P	Parking area
18	3.865	R1	N			0.40	0.30	0.50	1.20	2.5				12.0	1.20	C	IB	S	P	Parking area
19	3.865	L1	N			0.60	0.40	0.50	1.50	5.0				12.0	1.50	C	IB	M	P	Circle area at businesses
AVERAGE						0.48	0.58	0.53	1.58	3.63				12.00	1.63					