

STATE OF FLORIDA DEPARTMENT OF TRANSPORTATION
PAVEMENT EVALUATION CORING AND CONDITION DATA

Cored By: MADRID CPWG

Coring Completion Date: 6/19/2025

Typical Section: 8 Lane Urban Principal Arterial Roadway

W.P.I. No.:		Name:	SR 35 (US 98)				Lanes:	Various						
Fin. Proj. ID:	451481-1-32-01	From:	Sharon Dr.				Shoulder Type and Condition:							
F.A. Project No.:		Roadway ID:	16210000				To: N of Norton Rd.							
County:	Polk	SR No.:	35		Beg MP:	3.569	End MP:	5.982	Length:	2.413	Outside:	Paved		
Overall Pavement Condition (from DMO field review):				Fair		Median Curbed (Y/N):		Y	Y	Lawn	Other:		Curb & Gutter (Y/N):	Y

All Cores

CORE NO.	MILE POST ²	LANE TYPE	LANE	WP (Y/N)	PAVEMENT LAYER (IN.)										TOTAL ASPHALT THICKNESS (IN.)	BASE				STABILIZED SUBGRADE ³	CRACK				PAVEMENT CONDITION	COMMENTS		
					FC12.5	FC9.5	SP12.5	SP9.5	ARMI	SP9.5								LR					DEPTH (IN.)	TYPE			CLASS	EXTENT
61	4.331	S	OL	N		1.5		3.5							5.0	14.0								P				
62	3.909	S	OL	N		1.5		3.6							5.1	14.0						2.6	B	II	M	P		
63	3.675	S	OL	N		1.4		2.6							4.0	14.0									F			
64	3.596	TL	RL	Y		0.9		2.8							3.7	14.0				16.0						P		
65	3.796	TL	RL	Y		0.8		2.9							3.7	20.0						3.7	B	II	S	P		
66	3.831	TL	RL	N		1.3		2.7							4.0	14.0										P		
67	4.060	TL	RL	N		1.2		2.7							3.9	14.5										P		
68	4.163	TL	RL	N		1.2		2.8							4.0	14.0										P		
69	4.693	TL	RL	N		1.2		2.4							3.6	20.0										F		
70	4.856	TL	LL	N		1.4		3.1							4.5	14.0										F		
71	5.067	TL	RL	N		1.2		2.5							3.7	20.0										F		
72	5.380	TL	RL	N		1.0		6.1							7.1	20.0										F		
73	5.567	TL	RR	N		0.9		3.3							4.2	14.0						0.2	B	IB	L	P		
74	5.598	TL	RL	N		1.2		2.3							3.5	14.0										P		
75	5.651	TL	LR	N		1.5		2.9							4.4	14.0										P		
76	5.686	TL	LL	N		1.9		2.8							4.7	13.0										P		
77	4.483	TL	LL	N		1.6		2.5							4.1	14.0										P		
78	4.383	TL	LL	N		1.9		2.3							4.2	14.0				13.0						P		
79	4.233	TL	LL	N		1.4		2.9							4.3	20.0										P		
80	3.948	TL	LL	N		1.4		2.9							4.3	14.0										P		
81	3.893	TL	LL	N		1.5		3.0							4.5	14.0										P		
82	3.712	TL	LL	N		1.1		2.9							4.0	14.0				20.0		4.0	B	II	M	P		
83	3.651	TL	LL	N		1.1		2.9							4.0	14.0										P		
84	4.435	CO	CO	N		1.4		3.1							4.5	14.0										F		
85	4.714	CO	CO	N		1.4		1.9							3.3	20.0										F		
86	5.784	CO	CO	N		1.5		2.4							3.9	20.0										F		
AVERAGE						1.57	1.31	3.30	2.75	0.60	3.00				4.11	14.57					15.78	3.30						
MAX						1.70	2.00	3.30	6.70	0.60	3.00				7.90	20.00					20.00	4.20						
MIN						1.30	0.50	3.30	1.50	0.60	3.00				2.30	10.50					13.00	0.20						
LAYER COEF.						0.25	0.25	0.25	0.25	0.00	0.25					0.18					0.08							