PAVEMENT EVALUATION CORING AND CONDITION DATA

Cored By: RCS Coring Completion Date: 8/24/2023 Typical Section: 1

	Corea By:	NUS									Coning C	Jonipiello	•	8/24/2023							i ypicai (
	W.P.I. No.:													SR 70/700 (U										es each direction and center Lane)
	in. Proj. ID:	448971	-1											West of US 98							Shoulde		nd Conditi	on:
F.A. F	Project No.:					Roa		9107000	00					East of NW 5t								Inside:		
	County:							70/700					Beg MP:			End MP:	9.225	Length:	0.962			Outside:		
	Overall F	Pavemer	nt Conditio	n (from [OMO field	d review):	Fair				Med	dian Curbe	d (Y/N):	N	Paved		Lawn	Other:			Cu	rb & Gut	ter (Y/N):	,Υ
													Main	line Core	es (ML	.)								
								PA	VEMENT	LAYER (IN.)					T (BA	SE			CRA	CK			
CORE NO.	MILE POST ²	LANE TYPE	LANE	WP (Y/N)	FC3	FC9.5	s	wc						TOTAL ASPHALT THICKNESS (IN.)	SHEL	LR	ABC-2	STABILIZED SUBGRADE ³	DEPTH (IN.)	ТҮРЕ	CLASS	EXTENT	PAVEMENT CONDITION	COMMENTS
36	8.291	ML	R2	Υ	1.6		3.1							4.7		11.7			2.9	С	II	S	F	
62	8.292	ML	L2	Υ	1.1		3.4							4.5	10.9								F	
33	8.337	ML	R2	Υ	1.5		3.0							4.5		10.5			3.5	С	III	S	Р	
61	8.376	ML	L2	N	1.2		3.6							4.8	11.2			12.0					F	
38	8.391	ML	R1	N	1.3		3.1							4.4	11.8								F	
60	8.415	ML	L1	Υ	1.5		2.5							4.0	10.0				4.0	С	III	S	Р	
31	8.435	ML	R1	Υ	1.3		2.4							3.7	10.3				3.7	С	III	S	F	
41	8.501	ML	R2	Υ	1.3		2.7							4.0		13.1			1.8	С	III	S	F	
58	8.508	ML	L2	Υ	1.4		3.1							4.5	11.6				2.5	С	II	S	F	
57	8.556	ML	L1	Υ	1.7		4.1							5.8	9.9				0.3	С	ΙB	L	F	
40	8.581	ML	R1	Υ	1.1		2.9							4.0	11.0								F	
35	8.671	ML	L1	Υ	1.5		2.7							4.2	9.5			12.0	4.2	С	П	S	F	
55	8.739	ML	L2	Υ	1.3		3.5							4.8	6.2				2.8	С	≡	S	F	
44	8.743	ML	R2	Υ	1.4		2.8							4.2		9.0		12.0	3.0	С	≡	S	F	
46	8.808	ML	R1	Υ	1.3		2.7							4.0		12.4			3.3	С	≡	S	F	
54	8.821	ML	L1	Υ	1.4		3.1							4.5	9.7								F	
64	8.970	ML	L2	Υ	1.3		3.7							5.0	5.0				5.0	С	Ш	S	Р	
48	9.030	ML	R2	Υ	1.0		3.0							4.0		11.1			2.8	С	Ш	S	F	
52	9.034	ML	L1	N	1.6		2.8							4.4	10.8				0.3	С	IB	L	F	
50	9.100	ML	R1	Υ	1.2		1.0	0.6						2.8	9.2			12.0	2.8	С	III	L	F	
51	9.105	ML	L2	N	0.9		0.3	0.6						1.8		8.2							F	
34	9.133	ML	R2	N	1.2		1.4	0.4						3.0		10.0			3.0	С	Ш	S	Р	
32	9.178	ML	R1	Υ		1.0	3.7							4.7	8.8				4.7	С	Ш	S	Р	
65	9.229	ML	L1	N	1.4		1.1	0.4						2.9		12.0			0.2	С	ΙB	L	F	1
AVERAGE					1.33	1.00	2.74	0.50						4.13	9.73	10.89		12.00	2.82					
MAX					1.70	1.00	4.10	0.60						5.80	11.80	13.10		12.00	5.00					
MIN					0.90	1.00	0.30	0.40						1.80	5.00	8.20		12.00	0.20					
LAYER COEF.					0.17	0.25	0.25	UNKW							0.18	0.18	0.16	0.08						-

Notes

- 1. The data presented on this table is specific only at the locations cored at the time of the investigation. Should questions arise regarding the pavement composition, it is incumbent upon those raising the question to perform additional exploration as necessary.
- 2. Mile posts are approximate based on field recorded measurements using a Distance Measuring Instrument (DMI) or a GPS unit.
- 3. Stabilization thickness was checked on 10% of the coring locations. For pavement design, assume 12 inches of thickness for stabilization.
- 4. The cross slope is approximate and measured in the center of the lane.
- 5. A blank cell indicates measurement was not recorded.
- 6. A value of "UNK" indicates material was encountered but the total thickness was not determined.

_	or a raide or or are maioatee material mae en							
ĺ	Lane Designations - Decreasing MP	Lane Designations - Increasing MP		Lane Type	Crack Type	Crack Rating	<u>Extent</u>	Pavement Condition
	OL/IL - Outside/Inside Shoulder	OR/IR - Outside/Inside Shoulder	ML - Mainline	S - Shoulder	A - Alligator	Class IB - Hairline cracks that are ≤ 1/8 inch wide	L - Light	G - Good
	L1 - 1st Lane Left of Centerline	R1 - 1st Lane Right of Centerline	TL - Turn Lane	SS - Side Street	B - Block	Class II - Cracks > than 1/8 inch and ≤ 1/4 inch	M - Moderate	F - Fair
	LL/LR - Left/Right Turn Lane	RL/RR - Left/Right Turn Lane	CO - Crossover	BR - Bridge Approach/Departure	C - Combination	Class III - Cracks > 1/4 inch	S - Severe	P - Poor

PAVEMENT EVALUATION CORING AND CONDITION DATA

Cored By: RCS Coring Completion Date: 8/24/2023 Typical Section: 1

,	Cored by.	NOS									(John G Col	inpletion Date.	0/24/2023							•	i ypicai	Section.		
	W.P.I. No.:												Name:	SR 70/700 (U	S 98)								Lanes:	4 (2 Lane	es each direction and center Lane)
Fi	in. Proj. ID:	448971-	1										From:	West of US 98	3							Shoulde	r Type ar	nd Conditi	on:
F.A. P	Project No.:					Roa	dway ID:	9107000	00				To:	East of NW 5t	h Avenue								Inside:		
	County:	Okeecho	bee				SR No.:	70/700					Beg MP:	8.263		End MP:	9.225		Length:	0.962			Outside:		
	Overall F			on (from I	DMO field	review):						Mediai	n Curbed (Y/N):		Paved		Lawn		Other:					ter (Y/N):	ıY
														ulder Co				<u> </u>						\ /	
								P/	VEMENT L	LAYER (IN	l.)				(0)	,	SE				CR/	<i>ICK</i>			
CORE NO.	MILE POST ²	LANE TYPE	LANE	WP (Y/N)	FC3	FC9.5	s	wc						TOTAL ASPHALT THICKNESS (IN.)	SHEL	LR	ABC-2		STABILIZED SUBGRADE ³	DEPTH (IN.)	TYPE	CLASS	EXTENT	PAVEMENT CONDITION	COMMENTS
37	8.291	S	OR	N	1.3		3.7							5.0	10.7									F	
63	8.292	S	OL	N	1.2		3.3							4.5	9.1									F	
42	8.501	S	OR	N	1.6		2.6							4.2		10.8								F	
59	8.508	S	OL	N	1.5		3.3							4.8	11.4									F	
56	8.739		OL	N	1.3		3.7							5.0	11.0				12.0					F	
45	8.743		OR	N	1.9		2.6							4.5		10.6								F	
53	8.970		OL	N	1.6		3.4							5.0	6.1									F	
49	9.030		OR	N	1.3		3.4				<u> </u>			4.7	5	9.3								F	
AVERAGE					1.46		3.25							4.71	9.66	10.23			12.00						
MAX					1.90		3.70							5.00	11.40	10.80			12.00						
MIN					1.20		2.60							4.20	6.10	9.30			12.00						
LAYER COEF.					0.17	0.25	0.25	UNKW							0.18	0.18	0.16		0.08						

Notes:

- 1. The data presented on this table is specific only at the locations cored at the time of the investigation. Should questions arise regarding the pavement composition, it is incumbent upon those raising the question to perform additional exploration as necessary.
- 2. Mile posts are approximate based on field recorded measurements using a Distance Measuring Instrument (DMI) or a GPS unit.
- 3. Stabilization thickness was checked on 10% of the coring locations. For pavement design, assume 12 inches of thickness for stabilization.
- 4. The cross slope is approximate and measured in the center of the lane.
- 5. A blank cell indicates measurement was not recorded.
- 6. A value of "UNK" indicates material was encountered but the total thickness was not determined.

6. A value of "UNK" indicates material was en	countered but the total thickness was not determined						
Lane Designations - Decreasing MP	Lane Designations - Increasing MP		<u>Lane Type</u>	Crack Type	Crack Rating	<u>Extent</u>	Pavement Condition
OL/IL - Outside/Inside Shoulder	OR/IR - Outside/Inside Shoulder	ML - Mainline	S - Shoulder	A - Alligator	Class IB - Hairline cracks that are ≤ 1/8 inch wide	L - Light	G - Good
L1 - 1st Lane Left of Centerline	R1 - 1st Lane Right of Centerline	TL - Turn Lane	SS - Side Street	B - Block	Class II - Cracks > than 1/8 inch and ≤ 1/4 inch	M - Moderate	F - Fair
LL/LR - Left/Right Turn Lane	RL/RR - Left/Right Turn Lane	CO - Crossover	BR - Bridge Approach/Departure	C - Combination	Class III - Cracks > 1/4 inch	S - Severe	P - Poor

PAVEMENT EVALUATION CORING AND CONDITION DATA

Cored By: RCS Coring Completion Date: 8/24/2023 Typical Section: 1

	V.P.I. No.:											ooming complete		SR 70/700 (U	C 00)						Lanes: 4 (2 Lanes each direction and center Lane)			
	. Proj. ID: 4	110071 1								-				West of US 98							Shoulder			
	oject No.:	44097 1-1				Poo	dway ID:	9107000	<u>.</u>	-				East of NW 5t							Shoulder	Inside:	u Conditi	011.
Г.А. ГІ	County:	Okooobo	hoo			Nua	SR No.:	70/700	0	-		-	Beg MP:			End MP:	0.225	Length:	0.062			Outside:		
	Overall P			n /fram [MO fold			10/100				Median Curbe			Paved		Lawn	Other:	0.302				er (Y/N):	V
	Overall P	avement	Conditio	n (nom L	JIVIO IIEIU	review).	ган										Lawn	Other.			Cui	D & Guil	er (T/N).	
												'	<u>Turn</u>	Lane Co	res (TI									
								PA	VEMENT L	AYER (IN	V.)			BASE			SE	CR			CK			
CORE NO.	POST ²	LANE TYPE	LANE	WP (Y/N)		FC9.5	s	wc						TOTAL ASPHALT THICKNESS (IN.)	SHEL	LR	ABC-2	STABILIZED SUBGRADE ³	DEPTH (IN.)	ТҮРЕ	CLASS	EXTENT	PAVEMENT CONDITION	COMMENTS
2	8.289	TL	RL	N	1.5		3.6							5.1	11.2								F	
3	8.344	TL	LL	N	1.5		2.9							4.4	11.1								F	
1	8.358	TL	LR	Υ	1.4		3.1							4.5	9.2				3.2	С	II	S	F	
39	8.405	TL	С	Ν	1.4		3.1							4.5	10.6			12.0					F	
43	8.618	TL	С	Υ	1.6		2.7							4.3	10.9								F	
47	8.846	TL	С	N	1.7		3.4							5.1	10.2								F	
11	8.978	TL	RL	Υ	1.4		2.1							3.5	10.6								F	
10	9.009	TL	LL	N	1.2		2.0							3.2	11.3								F	
9	9.045	TL	RL	Υ	1.5		3.4							4.9	9.8								F	
8	9.083	TL	LL	N	1.5		1.5	0.5						3.5		9.0							F	
7	9.123	TL	RL	N	1.6		1.4							3.0	10.6								F	
6	9.154	TL	LL	N	1.4		1.6							3.0		10.5		12.0					F	
5	9.189	TL	RL	N	1.2		1.5							2.7		9.8			1.9	С	II	L	F	
4	9.228	TL	LL	N		1.0	1.1	0.4						2.5		12.3				-			F	
AVERAGE					1.45	1.00	2.39	0.45						3.87	10.55	10.40		12.00	2.55				-	
MAX					1.70	1.00	3.60	0.50						5.10	11.30	12.30		12.00	3.20					
MIN					1.20	1.00	1.10	0.40						2.50	9.20	9.00		12.00	1.90					
LAYER COEF.					0.17	0.25	0.25	UNKW							0.18	0.18	0.16	0.08						

Notes:

- 1. The data presented on this table is specific only at the locations cored at the time of the investigation. Should questions arise regarding the pavement composition, it is incumbent upon those raising the question to perform additional exploration as necessary.
- 2. Mile posts are approximate based on field recorded measurements using a Distance Measuring Instrument (DMI) or a GPS unit.
- 3. Stabilization thickness was checked on 10% of the coring locations. For pavement design, assume 12 inches of thickness for stabilization.
- 4. The cross slope is approximate and measured in the center of the lane.
- 5. A blank cell indicates measurement was not recorded.
- 6. A value of "UNK" indicates material was encountered but the total thickness was not determined.

o. / value of or it indicates material was one	countered but the total thickness was not determined.						
Lane Designations - Decreasing MP	Lane Designations - Increasing MP		Lane Type	Crack Type	Crack Rating	<u>Extent</u>	Pavement Condition
OL/IL - Outside/Inside Shoulder	OR/IR - Outside/Inside Shoulder	ML - Mainline	S - Shoulder	A - Alligator	Class IB - Hairline cracks that are ≤ 1/8 inch wide	L - Light	G - Good
L1 - 1st Lane Left of Centerline	R1 - 1st Lane Right of Centerline	TL - Turn Lane	SS - Side Street	B - Block	Class II - Cracks > than 1/8 inch and ≤ 1/4 inch	M - Moderate	F - Fair
LL/LR - Left/Right Turn Lane	RL/RR - Left/Right Turn Lane	CO - Crossover	BR - Bridge Approach/Departure	C - Combination	Class III - Cracks > 1/4 inch	S - Severe	P - Poor

PAVEMENT EVALUATION CORING AND CONDITION DATA

Cored By: RCS Coring Completion Date: 8/24/2023 Typical Section: 1

1	W.P.I. No.:												Name:	SR 70/700 (U	S 98)							Lanes:	4 (2 Lane	s each direction and center Lane)
Fi	n. Proj. ID:	448971-	1										From:	West of US 98	3						Shoulde		nd Condition	
F.A. P	roject No.:					Roa	dway ID:	91070000 70/700)					East of NW 5t								Inside:		
	County:						SR No.:	70/700				В	Beg MP:	8.263		End MP:		Length:	0.962			Outside:		
	Overall F	Pavemen	t Condition	on (from [OMO field	l review):	Fair				Me	dian Curbe	d (Y/N):	N	Paved		Lawn	Other:			Cı	ırb & Gut	ter (Y/N): \	Y
												S	Side S	Street Co	res (S	S)								
								PAV	/EMENT LA	YER (IN	V.)				`		SE			CRA	<i>ICK</i>			
CORE NO.	MILE POST ²	LANE TYPE	LANE	WP (Y/N)	FC3	FC9.5	s	wc						TOTAL ASPHALT THICKNESS (IN.)	SHEL	LR	ABC-2	STABILIZED SUBGRADE ³	DEPTH (IN.)	TYPE	CLASS	EXTENT	PAVEMENT CONDITION	COMMENTS
12	8.319	SS	NA	Υ	1.6		2.4							4.0			7.0						F	
13	8.378	SS	NA	Υ	1.6		3.4							5.0	7.5								F	
14	8.437	SS	NA	Υ	1.5		4.0							5.5	7.6								F	
15	8.567	SS	NA	Υ	1.3		6.2							7.5	8.5								F	
16	8.601	SS	NA	Υ	1.3		2.8							4.1	11.3								F	
17	8.673	SS	NA	Υ	1.5		3.7							5.2	10.3								F	
18	8.678	SS	NA	Υ	1.3		4.8							6.1	9.8								F	
19	8.783	SS	NA	Υ	1.5		5.0							6.5	13.5								F	
20	8.786	SS	NA	Υ	1.6		4.1							5.7	8.8								F	
21	8.923	SS	NA	Υ	1.5		3.9							5.4	10.9								F	
22	8.926	SS	NA	Υ	1.5		2.8							4.3	10.7								F	
23	8.993	SS	NA	Υ	2.0		3.7							5.7	10.8								F	
24	8.996	SS	NA	N	1.9		3.2							5.1	6.1								F	
25	9.065	SS	NA	Υ	1.3		1.2							2.5		7.7							F	
26	9.069	SS	NA	Υ	1.2		1.1							2.3		11.1							F	
27	9.138	SS	NA	N	0.7									0.7		12.3							F	
28	9.142	SS	NA	Υ	1.7									1.7		7.9							F	
29	9.208	SS	NA	Υ	1.9									1.9		10.4							F	
30	9.212		NA	Y	1.5		1.8							3.3		7.7							F	
AVERAGE					1.49		3.38							4.34	9.65	9.52	7.00							
MAX					2.00		6.20							7.50	13.50	12.30	7.00							
MIN					0.70		1.10							0.70	6.10	7.70	7.00							
LAYER COEF.					0.17	0.25	0.25	UNKW						_	0.18	0.18	0.16	0.08						
Notes:																								

- 1. The data presented on this table is specific only at the locations cored at the time of the investigation. Should questions arise regarding the pavement composition, it is incumbent upon those raising the question to perform additional exploration as necessary.
- 2. Mile posts are approximate based on field recorded measurements using a Distance Measuring Instrument (DMI) or a GPS unit.
- 3. Stabilization thickness was checked on 10% of the coring locations. For pavement design, assume 12 inches of thickness for stabilization.
- 4. The cross slope is approximate and measured in the center of the lane.
- 5. A blank cell indicates measurement was not recorded.
- 6. A value of "UNK" indicates material was encountered but the total thickness was not determined.

Lane Designations - Decreasing MP	Lane Designations - Increasing MP		<u>Lane Type</u>	Crack Type	Crack Rating	<u>Extent</u>	Pavement Condition
OL/IL - Outside/Inside Shoulder	OR/IR - Outside/Inside Shoulder	ML - Mainline	S - Shoulder	A - Alligator	Class IB - Hairline cracks that are ≤ 1/8 inch wide	L - Light	G - Good
L1 - 1st Lane Left of Centerline	R1 - 1st Lane Right of Centerline	TL - Turn Lane	SS - Side Street	B - Block	Class II - Cracks > than 1/8 inch and ≤ 1/4 inch	M - Moderate	F - Fair
LL/LR - Left/Right Turn Lane	RL/RR - Left/Right Turn Lane	CO - Crossover	BR - Bridge Approach/Departure	C - Combination	Class III - Cracks > 1/4 inch	S - Severe	P - Poor