Pavement Evaluation Coring and Condition Data

Cored By:	D2 Materials	Date:	07/25/22	Page 1 of 1	Typical Section: 1 of 1		
Project No.:	443239-1	Name:	I-10 (SR 8) @ SR 51 (US 129)			Lanes:	4
State Road No.:	SR 8 @ SR 51	From:	South of I-10			Shoulders	
County:	Suwannee	To:	North of I-10			Inside:	N/A
Section No:	37120	Beg MP:	14.345	End MP: 14.803	Length: 0.458	Outside:	4-10'

Core Number	Mile Post	Lane	Wheel Path	Pavement Layer (top) FC 6	SP 12.5	T1	Binder			Core Length	Base Type	Crack Depth	Type	Class	Extent	Pavement Condition	Rut Depth (inches)	Cross Slope (%)	Slope Direction (in / out)	Comments:
SR 51 (US 129) from MP 27.087 to MP 27.976																				
1	27.415	R1	I	1.3	0.9	0.9	1.0			4.1	LR	4.1	B	II	M	P				Raveling, Spalling
2	27.461	OR	N	1.8	1.4					3.2	LR					G				
3	27.556	R1	O	1.7	1.8					3.5	LR	1.7	BR	II	L	P				Spalling, Seperated at 1.7
4	27.635	LLTTL	N	1.3	1.6	0.9				3.8	LR					F				IN-1.6% Out-3.2%
5	27.520	L1	N	1.5	0.9		2.1			4.5	LR	2.3	B	IB	M	P				Raveling
6	27.388	L2	O	1.5	0.9		0.8			3.2	LR	3.2	B	II	M	P				Raveling, Spalling
7	27.388	OL	N	1.6	6.2					7.8	LR	1.6				F				

Remarks:

Pavement Evaluation Coring and Condition Data

Cored By:	D2 Materials	Date:	07/25/22	Page 1 of 1	Typical Section: 1 of 1		
Project No.:	443239-1	Name:	I-10 (SR 8) @ SR 51 (US 129)			Lanes:	4
State Road No.:	SR 8 @ SR 51	From:	WB Ramps				
County:	Suwannee	To:	EB Ramps			Inside:	
Section No:	37120	Beg MP:	14.345	End MP: 14.803	Length: 0.458	Outside:	

Core Number	Mile Post	Lane	Wheel Path	Pavement Layer (top) FC 5	SP	T1	Binder			Core Length	Base Type	Crack Depth	Type	Class	Extent	Pavement Condition	Rut Depth (inches)	Cross Slope (%)	Slope Direction (in / out)	Comments:
I-10 Ramps																				
1	Off Rmp	WB	N		1.6	1.3	0.9			3.8	LR	1.7	B	IB	L	P				Severe Raveling
2	Off RMP	WB	Y	1.0	6.2					7.2	LR 10.8	7.2	STR	II	L	P				
3	On Rmp	WB	N	0.7	2.6	1.8	1.0			6.5	LR	2.8	B	II	M	P				Severe Raveling, Spalling to SP
4	ON RMP	WB	Y	0.7	1.6	1.4	0.5			4.2	LR 10.8	4.2	B	II	L	P				Severe Raveling
5	Off Rmp	EB	N	0.9	1.0	3.0	0.5			5.4	LR					F				Severe Raveling
6	Off OS	EB	N		2.2	0.7				2.9	ABC 7.5	10.4	STR	IB	L	F				
7	On Rmp	EB	N	0.8	2.4	2.0				5.2	LR 9.8	1.9	STR	IB	M	P				Severe Raveling
8	ON OS	EB	N		3.2	2.6				5.8	ABC 4.7					F				

Remarks: STR= Single Transverse Crack