

TABLE 1
STATE OF FLORIDA DEPARTMENT OF TRANSPORTATION
PAVEMENT EVALUATION CORING AND CONDITION DATA

675-030-09
Materials
3/13

Cored by: E. PUCKETT, ENVIRONMENTAL AND GEOTECHNICAL SPECIALISTS, INC. (EGS) Date: 4/1/2020 Page: 1 of 3 Typical Section No.: 1

Roadway Section: 72140000	Name: SR 200 (US 301) AT 1-10 IMPROVEMENTS	Lanes: 4
Fin. Proj. ID: 428865-2-52-01	From:	Shoulder Type and Condition:
F. A. Proj. No.:	To:	Inside: PAVED
County: DUVAL	SR No.: SR 200 (US 301)	Beg MP: 6.702
		End MP: 7.287
		Lgth: 0.585
Median Curbed (Y/N): N	Paved	(X) Lawn
		Other:
		Curb & Gutter (Y/N): N

Core No.	Milepost	Lane	Wheel Path	Pavement Layer (in.)								Base (in.) ¹		Crack				Pvmt Cond	Rut Depth (in.)	Cross Slope (%)	Cross Slope Direct.	PROJECT COMMENTS
				Top FC5	Top FC12.5	SP12.5	S1	ARMI	T1	BIND	Core Lgth. (in.)	LR	RAP	Depth (in.)	Type	Class	Extent					
1	6.796	R1	I		1.3	1.4				2.5	1.4	6.6	--					P				LIGHT RAVELING, SPALLING
2	7.015	R1	N		1.3	1.8				0.9	1.5	5.5	--					P				LIGHT RAVELING
3	7.150	R1	I		1.5	1.1				0.7	1.1	4.4	--					P				LIGHT RAVELING, SPALLING
4	7.198	R1	I		1.3	1.4				1.3	0.5	4.5	--					P				LIGHT RAVELING, SPALLING
5	6.715	R2	O	0.6		3.1		0.5			2.1	6.3	--					P				LIGHT RAVELING, SPALLING
6	6.952	R2	O		1.5	1.5					1.2	4.2	--					P				LIGHT RAVELING
7	7.074	R2	N		1.7	1.9					0.7	4.3	--		0.90	B	IB	L	P			LIGHT RAVELING, LONGITUDINAL CRACK, SUPERELEVATED CURVE
8	7.194	R2	O		1.3	2.0					0.6	3.9	--					P				LIGHT RAVELING
9	6.728	L1	I	0.7		1.5	2.2	0.5	1.0	1.4	7.3	10.7		1.00	B	II	L	P				LIGHT RAVELING, SPALLING
10	6.963	L1	I		1.5	1.5	0.5			0.9	1.1	5.5	--					F				LIGHT RAVELING
11	7.088	L1	N		1.4	2.1				1.0	0.8	5.3	--					F				LIGHT RAVELING
12	7.200	L1	N		1.1	2.0	0.5				1.0	4.6	--					P				LIGHT RAVELING, SPALLING
13	7.020	L2	O		1.2	1.7				1.2	1.0	5.1	--		1.70	B	II	M	P			LIGHT RAVELING, SPALLING, TRANSVERSE CRACK
14	7.176	L2	I		1.3	1.6	0.8				1.0	4.7	--		2.30	B	IB	M	P			LIGHT RAVELING, LONGITUDINAL CRACK
15	7.195	L2	O		1.7	1.5						3.2	--		3.00	B	II	M	P			DELAMINATING, GRINDING, MODERATE RAVELING, SEPARATION AT 1.7 in., SPALLING
16	7.209	L2	O		1.4	1.5					0.5	3.4	--		3.40	B	IB	L	P			LIGHT RAVELING, LONGITUDINAL CRACK
17	6.796	IR	N		1.2					4.4		5.6	--					F				LIGHT RAVELING
19	6.715	OR	N	0.8				2.0		1.1		3.9	--					F				LIGHT RAVELING

NOTES: 1. DASHES INDICATE BASE WAS ENCOUNTERED BUT THICKNESS WAS NOT MEASURED.
2. CORE 15: 192" FROM EDGE OF PAVEMENT.
3. CORE 18: CHANGED TO CORE: GA.

4. CORE 43: 219" FROM EDGE OF PAVEMENT.
5. MP 6.773: PAVEMENT CHANGE.

TABLE 1
STATE OF FLORIDA DEPARTMENT OF TRANSPORTATION
PAVEMENT EVALUATION CORING AND CONDITION DATA

675-030-09
Materials
3/13

Cored by: E. PUCKETT, ENVIRONMENTAL AND GEOTECHNICAL SPECIALISTS, INC. (EGS)

Date: 4/1/2020

Page: 2 of 3

Typical Section No.: 1

Roadway Section: 72140000				Name: SR 200 (US 301) AT 1-10 IMPROVEMENTS				Lanes: 4			
Fin. Proj. ID: 428865-2-52-01				From:				Shoulder Type and Condition:			
F. A. Proj. No.:				To:				Inside: PAVED			
County: DUVAL		SR No.: SR 200 (US 301)		Beg MP: 6.702		End MP: 7.287		Lgth: 0.585		Outside: PAVED	
Median Curbed (Y / N): N				Paved		(X) Lawn		Other:		Curb & Gutter (Y / N): N	

Core No.	Milepost	Lane	Wheel Path	Pavement Layer (in.)						Base (in.) ¹			Crack				Pvmt Cond	Rut Depth (in.)	Cross Slope (%)	Cross Slope Direct.	PROJECT COMMENTS	
				Top FC5	Top FC12.5	SP12.5	S1	T1	Core Lgth. (in.)	ABC	LR	RAP	Depth (in.)	Type	Class	Extent						
20	6.952	OR	N		1.5	0.8				2.3			--					F				LIGHT RAVELING
21	7.074	OR	N		1.2	0.6	1.7			3.5	6.7							F				LIGHT RAVELING, SUPERELEVATED CURVE
22	7.194	OR	N		1.2	0.6	1.2			3.0			--					F				LIGHT RAVELING
23	6.728	IL	N	0.9					2.2	3.1			--					F				LIGHT RAVELING
24	6.963	IL	N		1.1	3.9				5.0			--					F				LIGHT RAVELING
25	7.088	IL	N		1.4	4.0				5.4			8.1					F				LIGHT RAVELING
26	6.803	OL	N		1.0		3.5			4.5			--					F				LIGHT RAVELING
27	6.980	OL	N		0.9		1.3			2.2			7.3					F				GORE AREA, LIGHT RAVELING
28	7.066	OL	N		1.3	0.9	2.9			5.1			--					F				GORE AREA, LIGHT RAVELING
29	7.209	OL	N		1.8					1.8			--					F				LIGHT RAVELING
30	6.743	RLTTL	I	0.7		1.4	3.1	5.0	10.2	7.9			2.70	B	III	M	P					RAVELED TO STRUCTURAL, SEVERE RAVELING TRANSVERSE CRACK
31	6.986	RLTTL	I		1.3	3.3		0.8	5.4				--					F				LIGHT RAVELING
32	7.166	RLTTL	O		0.8	4.5			5.3				1.20	B	IB	M	P					LIGHT RAVELING, SPALLING
33	7.198	RLTTL	O		1.3	1.5			2.8	6.7							P					MODERATE RAVELING
34	7.176	LRTTL	N		1.3	3.7			5.0				--					F				LIGHT RAVELING
35	6.837	LLTTL	N		1.2		2.5	1.3	5.0	8.9								F				LIGHT RAVELING
36	7.158	LLTTL	N		1.2	1.5	0.7	0.5	3.9				--					F				LIGHT RAVELING
37	7.075	TO	N		1.4	1.3	2.8		5.5				--					F				LIGHT RAVELING

NOTES: 1. DASHES INDICATE BASE WAS ENCOUNTERED BUT THICKNESS WAS NOT MEASURED.
2. CORE 15: 192" FROM EDGE OF PAVEMENT.
3. CORE 18: CHANGED TO CORE: GA.

4. CORE 43: 219" FROM EDGE OF PAVEMENT.
5. MP 6.773: PAVEMENT CHANGE.

TABLE 1
STATE OF FLORIDA DEPARTMENT OF TRANSPORTATION
PAVEMENT EVALUATION CORING AND CONDITION DATA

675-030-09
Materials
3/13

Cored by: E. PUCKETT, ENVIRONMENTAL AND GEOTECHNICAL SPECIALISTS, INC. (EGS) Date: 4/1/2020 Page: 3 of 3 Typical Section No.: 1

Roadway Section: 72140000	Name: SR 200 (US 301) AT I-10 IMPROVEMENTS	Lanes: 4
Fin. Proj. ID: 428865-2-52-01	From:	Shoulder Type and Condition:
F. A. Proj. No.:	To:	Inside: PAVED
County: DUVAL SR No.: SR 200 (US 301)	Beg MP: 6.702 End MP: 7.287 Lgth: 0.585	Outside: PAVED
Median Curbed (Y / N): N Paved	(X) Lawn Other:	Curb & Gutter (Y / N): N

Core No.	Milepost	Lane	Wheel Path	Pavement Layer (in.)							Base (in.) ¹		Crack				Pvmt Cond	Rut Depth (in.)	Cross Slope (%)	Cross Slope Direct.	PROJECT COMMENTS
				Top FC12.5	Top SP12.5	S1	ARMI	TI	BIND	Core Lgth. (in.)	LR	Depth (in.)	Type	Class	Extent						
38	6.781	CO	N	1.5				2.0	1.9	5.4	--					P				LIGHT RAVELING, SPALLING	
39	6.968	CO	N	1.1	1.7					2.8	15.2					P				MODERATE RAVELING	
40	7.099	CO	N	1.5	1.6					3.1	--					P				CROSS SLOPE MEASURED FROM R1, DELAMINATING, SEPARATION AT 1.5 in.	
41	6.986	GA	N	1.3	1.5					2.8	10.2					P				LIGHT RAVELING, SPALLING	
42	7.128	CO	N	1.2	2.1					3.3	--					P				CROSS SLOPE MEASURED FROM L1, MODERATE RAVELING	
43	7.195	L2	N	1.6	1.5				0.4	3.5	--	1.70	B	II	M	P				DELAMINATING, GRINDING, MODERATE RAVELING, SEPARATION AT 1.6 in.	
44	6.803	L2	O	1.5	1.1	1.7	0.5		2.1	6.9	7.5					P				LIGHT RAVELING	

NOTES: 1. DASHES INDICATE BASE WAS ENCOUNTERED BUT THICKNESS WAS NOT MEASURED.
2. CORE 15: 192" FROM EDGE OF PAVEMENT.
3. CORE 18: CHANGED TO CORE: GA.

4. CORE 43: 219" FROM EDGE OF PAVEMENT.
5. MP 6.773: PAVEMENT CHANGE.