

TABLE 1
STATE OF FLORIDA DEPARTMENT OF TRANSPORTATION
PAVEMENT EVALUATION CORING AND CONDITION DATA

675-030-09
Materials
3/13

Cored by: E. PUCKETT, ENVIRONMENTAL AND GEOTECHNICAL SPECIALISTS, INC. (EGS) Date: 1/6/2021 Page: 1 of 3 Typical Section No.: 1

Roadway Section: 72028000	Name: SR 152 (BAYMEADOWS ROAD)	Lanes: 4
Fin. Proj. ID: 447123-1-52-01	From: BAYBERRY ROAD	Shoulder Type and Condition:
F. A. Proj. No.:	To: SR 115 (SOUTHSIDE BOULEVARD)	Inside: CURB AND GUTTER
County: DUVAL	SR No.: SR 152	Beg MP: 2.094
		End MP: 3.938
		Lgth: 1.844
Median Curbed (Y / N): Y	Paved	(X) Lawn
		Other:
		Curb & Gutter (Y / N): Y

Core No.	Milepost	Lane	Wheel Path	Pavement Layer (in.)				Base (in.) ¹		Crack				Pvmt Cond	Rut Depth (in.)	Cross Slope (%)	Cross Slope Direct.	PROJECT COMMENTS
				Top FC12.5	Top FC9.5	SP12.5	T1	Core Lgth. (in.)	LR	CONC	Depth (in.)	Type	Class					
1	2.200	R1	O	1.5			0.9	2.4	--						P			MODERATE RAVELING
2	2.500	R1	O	1.5			1.1	2.6	10.3			2.60	B	II	M	P		MODERATE RAVELING
3	2.780	R1	I		0.8	2.5		3.3	--						P			MODERATE RAVELING
4	3.228	R1	I		1.1	1.3		2.4	--			2.40	B	III	S	P		SEVERE RAVELING
5	3.546	R1	O	1.6		1.1		2.7	--						P			MODERATE RAVELING
6	3.800	R1	I		1.2	2.1		3.3	--						F			MODERATE RAVELING
7	2.300	R2	O	1.1		1.0	1.3	3.4	--						F			MODERATE RAVELING
8	2.778	R3	O	1.2		1.7		2.9		--		2.90	B	II	M	P		MODERATE RAVELING, RAVELED TO STRUCTURAL, MULTIPLE SMALL PATCHES
9	2.885	R3	O	1.4		2.5		3.9	11.5			3.90	B	II	M	P		MODERATE RAVELING
10	3.300	R2	I		1.0	2.2		3.2	--			3.20	B	II	M	P		MODERATE RAVELING
11	3.592	R2	O		1.5	1.7	0.6	3.8	14.0			3.80	B	II	M	P		2.1 in. DIP IN OUTSIDE WHEEL PATH, MODERATE RAVELING
12	3.900	R2	O	1.5		1.8	0.3	3.6	--						F			LIGHT RAVELING
13	2.300	L1	I	1.2			0.9	2.1	--						F			MODERATE RAVELING
14	2.626	L1	O	1.1		1.7		2.8	--						F			MODERATE RAVELING
15	2.900	L1	O		1.2	2.1	0.5	3.8	--			3.80	B	II	M	P		MODERATE RAVELING
16	3.300	L1	I		1.3	2.2		3.5	--			3.50	B	II	M	P		MODERATE RAVELING
17	3.600	L1	I		0.9	2.5		3.4	11.0			2.00	B	II	M	P		MODERATE RAVELING
18	3.900	L1	I	1.4		1.7	0.3	3.4	--						F			MODERATE RAVELING

- NOTES:** 1. DASHES INDICATE BASE WAS ENCOUNTERED BUT THICKNESS WAS NOT MEASURED. 5. MP 3.190 TO 3.200: MAINTENANCE PATCH 9. MP 3.832: PAVEMENT CHANGE
 2. MP 2.750: PAVEMENT CHANGE 6. MP 3.393 TO 3.416: MAINTENANCE PATCH 10. C-8: MEASURED 54.5 in FROM BARRIER.
 3. MP 2.944: PAVEMENT CHANGE 7. MP 3.529: PAVEMENT CHANGE 11. C-"A": MEASURED 75 in FROM BARRIER.
 4. MP 3.015: PAVEMENT CHANGE 8. MP 3.531: RAVELING TO STRUCTURAL IN LLTTL

TABLE 1
STATE OF FLORIDA DEPARTMENT OF TRANSPORTATION
PAVEMENT EVALUATION CORING AND CONDITION DATA

675-030-09
Materials
3/13

Cored by: E. PUCKETT, ENVIRONMENTAL AND GEOTECHNICAL SPECIALISTS, INC. (EGS) Date: 1/6/2021 Page: 2 of 3 Typical Section No.: 1

Roadway Section: 72028000	Name: SR 152 (BAYMEADOWS ROAD)	Lanes: 4
Fin. Proj. ID: 447123-1-52-01	From: BAYBERRY ROAD	Shoulder Type and Condition:
F. A. Proj. No.:	To: SR 115 (SOUTHSIDE BOULEVARD)	Inside: CURB AND GUTTER
County: DUVAL	SR No.: SR 152	Beg MP: 2.094
	End MP: 3.938	Lgth: 1.844
Median Curbed (Y / N): Y	Paved	(X) Lawn
	Other:	Curb & Gutter (Y / N): Y

Core No.	Milepost	Lane	Wheel Path	Pavement Layer (in.)							Core Lgth. (in.)	Base (in.) ¹	Crack				Pvmt Cond	Rut Depth (in.)	Cross Slope (%)	Cross Slope Direct.	PROJECT COMMENTS	
				FC12.5	FC9.5	SP12.5	FC3	S	T1	LR			Depth (in.)	Type	Class	Extent						
19	2.200	L2	O	1.7						1.7	3.4	--					F					LIGHT RAVELING
20	2.433	L2	O	1.4						1.6	3.0	22.0					F					
21	2.800	L3	I		1.0	2.1					3.1	12.0	1.80	B	II	M	P					MODERATE RAVELING, SPALLING
22	3.168	L2	I			1.8					1.8	--	1.80	B	III	S	P					GRINDING, RAVELED TO STRUCTURAL, SEVERE RAVELING
23	3.592	L2	I		0.7	2.2					2.9	--					P					GRINDING
24	3.807	L2	I		0.7	2.6					3.3	--	3.30	B	II	M	P					GRINDING, MODERATE RAVELING
25	2.122	LLTTL	I	0.8		0.9					1.7	--					P					MODERATE RAVELING
26	2.537	LR TTL2	N	1.8		2.0					3.8	--					F					MODERATE RAVELING
27	2.650	LL TTL1	O	1.5		1.5					3.0	--					F					LIGHT RAVELING
28	2.688	DEC	O	1.8		2.0					3.8	--					F					I-95 SB ON RAMP, LIGHT RAVELING
29	2.785	RL TTL	I		1.2	2.0					3.2	--	3.20	B	II	M	P					I-95 NB ON RAMP, DELAMINATING AT 1.5 in., MODERATE RAVELING
30	2.892	DEC	O		1.5	1.7					3.2	--	3.20	B	II	M	P					I-95 NB ON RAMP, MODERATE RAVELING, WIDENING
31	2.922	RR TTL	I		1.6	2.1					3.7	--					F					MODERATE RAVELING
32	3.310	RL TTL	O		0.9	3.0					3.9	--					F					MODERATE RAVELING
33	2.469	LTO	N	1.7		3.3					5.0	--					P					MODERATE RAVELING
34	3.011	RTO	N	1.6		1.2					2.8	--					F					MODERATE RAVELING
35	3.504	LTO	N	1.5		2.2					3.7	--					F					LIGHT RAVELING
36	2.527	RTO	N	0.8			1.0	2.0			3.8	--	3.80	B	II	M	P					MODERATE RAVELING

- NOTES:** 1. DASHES INDICATE BASE WAS ENCOUNTERED BUT THICKNESS WAS NOT MEASURED. 5. MP 3.190 TO 3.200: MAINTENANCE PATCH 9. MP 3.832: PAVEMENT CHANGE
2. MP 2.750: PAVEMENT CHANGE 6. MP 3.393 TO 3.416: MAINTENANCE PATCH
3. MP 2.944: PAVEMENT CHANGE 7. MP 3.529: PAVEMENT CHANGE
4. MP 3.015: PAVEMENT CHANGE 8. MP 3.531: RAVELING TO STRUCTURAL IN LLTTL

TABLE 1
STATE OF FLORIDA DEPARTMENT OF TRANSPORTATION
PAVEMENT EVALUATION CORING AND CONDITION DATA

675-030-09
Materials
3/13

Cored by: E. PUCKETT, ENVIRONMENTAL AND GEOTECHNICAL SPECIALISTS, INC. (EGS) Date: 1/6/2021 Page: 3 of 3 Typical Section No.: 1

Roadway Section: 72028000	Name: SR 152 (BAYMEADOWS ROAD)			Lanes: 4
Fin. Proj. ID: 447123-1-52-01	From: BAYBERRY ROAD			Shoulder Type and Condition:
F. A. Proj. No.:	To: SR 115 (SOUTHSIDE BOULEVARD)			Inside: CURB AND GUTTER
County: DUVAL	SR No.: SR 152	Beg MP: 2.094	End MP: 3.938	Lgth: 1.844
Median Curbed (Y / N): Y	Paved	(X) Lawn	Other:	Curb & Gutter (Y / N): Y

Core No.	Milepost	Lane	Wheel Path	Pavement Layer (in.)				Base (in.) ¹	Crack				Pvmt Cond	Rut Depth (in.)	Cross Slope (%)	Cross Slope Direct.	PROJECT COMMENTS
				Top FC9.5	Top FC12.5	SP12.5	Core Lgth. (in.)	LR	Depth (in.)	Type	Class	Extent					
A	2.778	R3	N	1.2		1.7	2.9	--					F				MODERATE RAVELING
B	3.375	L2	O		0.9	1.4	2.3	--					P				GRINDING, RAVELED TO STRUCTURAL, SEVERE RAVELING

- NOTES:**
- | | | |
|---|--|------------------------------|
| 1. DASHES INDICATE BASE WAS ENCOUNTERED BUT THICKNESS WAS NOT MEASURED. | 5. MP 3.190 TO 3.200: MAINTENANCE PATCH | 9. MP 3.832: PAVEMENT CHANGE |
| 2. MP 2.750: PAVEMENT CHANGE | 6. MP 3.393 TO 3.416: MAINTENANCE PATCH | |
| 3. MP 2.944: PAVEMENT CHANGE | 7. MP 3.529: PAVEMENT CHANGE | |
| 4. MP 3.015: PAVEMENT CHANGE | 8. MP 3.531: RAVELING TO STRUCTURAL IN LLTTL | |