

Pavement Evaluation Coring and Condition Data

Cored By: UNIVERSAL	Date: 01/20/21	Page 1 of 3	Typical Section: 1 of 1
Project No.: 445429-1-52-01	Name: SR111 From US90 (Beaver Street) To Old Kings Road		Lanes: 4
State Road No.: SR111	From: US90 (Beaver Street)		Shoulders
County: Duval	To: Old Kings Road		Inside: curb and gutter
Section No: 72291000	Beg MP: 3.500	End MP: 5.860	Length: 2.360 Outside: 6' paved

Core Number	Mile Post	Lane	Wheel Path	Pavement Layer						Core Length	Base Type	Crack				Pavement Condition	Rut Depth (inches)	Cross Slope (%)	Slope Direction (in / out)	Comments:
				← top								Depth	Type	Class	Extent					
				FC125	SP125	S1	FC4	T1	BIND											
1	3.800	R1	O	1.4	2.2				3.6	LR	1.0	B	IB	L	P				light raveling	
2	4.100	R1	N	1.1	3.0				4.1	LR=8.7					P				light raveling	
3	4.400	R1	I	1.5	2.1				3.6	LR	3.6	B	II	M	P				light raveling	
4	4.800	R1	I	1.8	2.2				4.0	LR					F				light raveling	
5	5.100	R1	N	1.6	3.1				4.7	LR					F				light raveling	
6	5.360	R1	I	1.3	2.6				3.9	LR=8.8					F				light raveling	
7	5.800	R1	I	1.6	2.5				4.1	LR					F				light raveling	
8	3.600	R2	I	1.3	2.7				4.0	LR=9.0	1.5	B	IB	M	P				light raveling	
9	3.890	R2	O	1.3	2.7				4.0	LR	4.0	B	II	M	P				light raveling	
10	4.200	R2	N	1.5	2.7				4.2	LR					F				light raveling	
11	4.600	R2	O	1.6	2.3				3.9	LR	1.6	B	IB	M	P				light raveling	
12	4.900	R2	O	1.7	2.3			0.6	4.6	LR=10.0					F				light raveling	
13	5.200	R2	O	1.3	2.5				3.8	LR	3.8	B	II	M	P				light raveling	
14	5.600	R2	O	1.4	2.5				3.9	LR	0.2	B	II	M	P				light raveling	
15	3.600	L1	I	1.3	2.2				3.5	LR=8.5					P				light raveling	
16	3.920	L1	I	1.5	2.5				4.0	LR	2.5	B	II	M	P					
17	4.200	L1	I	1.7	2.5			1.1	5.3	LR	1.8	B	II	M	P				light raveling	
18	4.600	L1	I	1.3	2.9				4.2	LR	2.1	B	II	M	P				light raveling	
19	4.900	L1	I	1.3	2.4				3.7	LR=9.3	1.5	B	IB	M	P				light raveling	
20	5.200	L1	I	1.7	2.3			1.3	5.3	LR	2.3	B	IB	L	P				light raveling	

Remarks: R1/2 pavement change: 3.574 / R2 maintenance patch: 3.900-3.919 / R1/2 maintenance patch: 4.236-4.255 / R2 pavement change: 5.539 / L2 small patch, raveled to structural: 4.181
R1 small patch: 4.030 / pavement change all: 3.532, 5.508, 5.810 / L1/2 pavement change: 5.480

Pavement Evaluation Coring and Condition Data

Cored By: UNIVERSAL Date: 01/20/21 Page 2 of 3 Typical Section 1 of 1

Project No.: 445429-1-52-01 Name: SR111 From US90 (Beaver Street) To Old Kings Road

Core Number	Mile Post	Lane	Wheel Path	Pavement Layer						Core Length	Base Type	Crack				Pavement Condition	Rut Depth (Inches)	Cross Slope (%)	Slope Direction (in / out)	Comments:
				← top								Depth	Type	Class	Extent					
				FC125	SP125	S1	FC4	T1	BIND											
21	5.600	L1	I	1.4	2.7				4.1	LR				F				light raveling		
22	3.800	L2	O	1.4	2.8				4.2	LR				P				light raveling		
23	4.100	L2	N	1.3	3.1				4.4	LR=8.6				F				light raveling		
24	4.400	L2	N	1.6	2.1				3.7	LR	1.6	B	III	M	P			moderate raveling, spalling, grinding, separated 1.6"		
25	4.780	L2	O	1.6	2.7				4.3	LR	4.3	B	II	M	P			light raveling		
26	5.100	L2	O	1.3	3.0				4.3	LR	4.3	B	II	M	P			light raveling		
27	5.400	L2	N	1.3	2.5				3.8	LR=7.5	1.3	B	IB	L	P			light raveling		
28	5.800	L2	O	1.2	3.2				4.4	LR				F				light raveling		
29	3.600	OR	N	1.4	1.6				3.0	LR				F						
30	4.600	OR	N	1.7	2.7				4.4	LR=9.3				F						
31	5.600	OR	N	1.3	2.5				3.8	LR				F						
32	3.800	OL	N	1.8	2.6				4.4	LR				F						
33	4.780	OL	N	1.6	2.8				4.4	LR				F						
34	5.800	OL	N	1.6	2.6				4.2	LR=8.0				F						
35	5.360	RLTTL	O	1.0	1.7				2.7	LR				F				light raveling		
36	3.735	RTO	N	1.7				1.1	4.5	7.3	LR			F				light raveling		
37	4.586	RTO	N	1.5				1.4	2.0	4.9	LR			F				light raveling		
38	5.514	RTO	N	1.3	1.6			1.0	2.7	6.6	LR			F				light raveling		
39	4.198	LRTTL	O	1.3	3.3				4.6	LR				P				light raveling		
40	3.600	LLTTL	O	1.6	2.3				3.9	LR				F				light raveling		

Remarks: _____

Pavement Evaluation Coring and Condition Data

Cored By: UNIVERSAL Date: 01/20/21 Page 3 of 3 Typical Section 1 of 1

Project No.: 445429-1-52-01 Name: SR111 From US90 (Beaver Street) To Old Kings Road

Core Number	Mile Post	Lane	Wheel Path	← top Pavement Layer						Core Length	Base Type	Crack				Pavement Condition	Rut Depth (inches)	Cross Slope (%)	Slope Direction (in / out)	Comments:	
				FC125	SP125	S1	FC4	T1	BIND			Depth	Type	Class	Extent						
41	4.172	LTO	N	1.4	1.8	2.0	0.6	2.8		8.6	LR					F			light raveling		
42	4.931	LTO	N	0.8				1.2	2.0	4.0	LR					P			moderate raveling		
43	5.714	LTO	N	1.2				1.7	1.7	4.6	LR					F			light raveling		
44	4.561	CO	N	1.5	2.5					4.0	LR=10.0					F			light raveling		

Remarks: CC = Center Crown