

Pavement Evaluation Coring and Condition Data

Cored By: CSI Geo, Inc.				Date: 02/19/25		Page 1 of 1				Mainline			
Project No.: 209698-5-52-01				Name: Blanding Blvd				Lanes: 4					
State Road No.: SR-21				From: SR134 (103RD Street)				Shoulders					
County: Duval				To: Wilson Blvd				Inside: N/A					
Section No: 72170000				Beg MP: 4.194		End MP: 5.717		Length: 1.523		Outside: C&G			

Core Number	Mile Post	Lane	Wheel Path	<div style="display: flex; align-items: center;"> ← <div style="border: 1px solid black; padding: 2px 5px;">Top</div> </div> Pavement Layer							Core Length (in.)	Base Type	Crack				Pavement Condition	Rut Depth (in.)	Cross Slope (%)	Slope Direction (in / out)	Comments:
				FC 9.5	SP 9.5	Binder							Depth (in.)	Type	Class	Extent					
1	4.195	R1	Y	1.0	1.2	2.2					4.4	LR	4.4	B	II	M	P				
2	4.669	R1	N	0.8	0.5	1.5					2.8	LR=11"	2.8	B	II	M	P				Raveling
3	5.052	R1	Y	1.1	0.9	2.0					4.0	LR	4.0	B	II	M	P				
5	5.672	R1	Y	0.9	0.7	1.6					3.2	LR	1.5	B	II	M	P				
11	4.257	R2	N	1.2	0.5	1.5					3.2	LR	3.2	B	II	M	P				
12	4.828	R2	Y	0.8	0.8	1.9					3.5	LR	3.5	B	II	M	P				Raveling
13	5.300	R2	Y	1.0	0.7	2.3					4.0	LR	1.0	B	III	M	P				Grinding
14	5.700	R2	Y	1.5	1.1	1.5					4.1	LR=9"	1.3	B	III	S	P				
9	4.250	L1	Y	0.5	1.1	2.0					3.6	LR=10"	3.6	B	II	M	P				
8	4.932	L1	N	1.0	1.0	2.5					4.5	LR	4.5	B	III	S	P				
7	5.391	L1	Y	1.0	1.9	2.0					4.9	LR	4.9	B	III	S	P				Raveled to 1.2"
6	5.654	L1	Y	1.1	1.2	2.4					4.7	LR	4.7	B	III	S	P				
19	4.195	L2	Y	0.9	0.6	1.9					3.4	LR					P				Raveling
18	4.670	L2	Y	0.8	0.7	1.8					3.3	LR	3.3	B	III	S	P				Grinding
17	5.150	L2	Y	1.1	0.7	2.0					3.8	LR=9"	2.7	B	III	S	P				
15	5.542	L2	Y	0.9	0.7	1.8					3.4	LR	1.7	B	II	M	P				
10	4.247	RTO	N	1.8	1.0	2.3					5.1	LR					P				Turnout for Lynnwood Ave
16	5.162	LTO	Y	1.1	3.0	2.2					6.3	LR					P				Turnout for Bartholf Ave
20	4.215	CTL	N	0.8	0.9	2.2					3.9	LR					F				PC
4	5.524	CTL	N	0.7	0.9	1.9					3.5	LR					F				PC

Remarks: PC=Parabolic Crown, Grinding throughout project.