

STATE OF FLORIDA DEPARTMENT OF TRANSPORTATION
PAVEMENT EVALUATION CORING AND CONDITION DATA

675-030-09
 Materials
 3/13

Cored by: E. PUCKETT Date: 01/06/20 Page: 1 of 3 Typical Section No.: --

Roadway Section: 46160000				Name: SR 30A (US 98)				Lanes: 6			
Fin. Proj. ID: 217838-4-32-01				From: EAST OF NAUTILUS STREET				Shoulder Type and Condition: GOOD			
F. A. Proj. No.: --				To: EAST OF RICHARD JACKSON BOULEVARD				Inside: GRASS			
County: BAY		SR No.: 30A		Beg MP: 9.006		End MP: 11.390		Lgth: 2.384		Outside: PAVED	
Median Curbed (Y / N): Y				Paved: Y		Lawn: Y		Other: --		Curb & Gutter (Y / N): N	

Core No.	Mile Post or Sta. No.	Lane	Wheel Path (Y / N)	Pavement Layer (in.)							Core Lgth. (in.)	Base		Crack			Pvmt Cond	Rut Depth (in.)	Cross Slope (%)	PROJECT COMMENTS
				FC-5	FC-12.5	SP-12.5	S	T2						LIMEROCK	SAHM	Depth (in.)				
G-1	9.025	R2	Y	0.70		3.30	0.90	1.10			6.00		6.80	0.00	A	IB	L	F		MOD. RUTTING, MOD LONG CRK, DELAMINATION
G-2	9.025	ROTL	Y	0.80		3.80					4.60		12.00	0.70	A	IB	L	F		MOD RUTTING, MOD LONG CRK
G-3	9.105	CO	N		0.70	0.70	3.10				4.50		9.00	0.00	A	IB	L	F		LIGHT LONGITUDINAL CRACKING
G-4	9.214	L2	Y	1.00		2.90	5.80				9.70		6.30	1.10	A	IB	L	F		MOD RUTTING, LIGHT RAVELING
G-5	9.214	LOTL	N	1.00		4.10					5.10		12.00	0.50	A	IB	L	F		MOD. RUTTING, LIGHT RAVELING
G-6	9.381	OL	N	1.50		1.30	1.60				4.40		7.60	0.30	A	IB	L	G		
G-7	9.381	OR	N	0.70		2.50	1.30				4.50		6.00	0.00	A	IB	L	G		
G-8	9.442	LITL	Y		1.90	1.20	3.80				6.90		8.10	0.00	A	IB	L	F		LIGHT RAVELING, CONCRETE CURB
G-9	9.534	L1	Y	0.90		1.70	2.90				5.50		11.50	0.00	A	IB	L	F		MOD RUTTING, LIGHT LONG CRK, LIGHT RAVELING
G-10	9.534	LITL	Y	1.20		1.30	2.40				4.90		11.10	1.10	A	IB	L	F		LIGHT RUTTING, LIGHT RAVELING
G-11	9.571	LITL	N		1.00	1.00	4.40				6.40		10.60	0.00	A	IB	L	F		MOD RUTTING, CONCRETE CURB
G-12	9.898	RITL	N	1.20		3.20					4.40		12.00	1.20	B	II	M	F		LIGHT RUTTING, MOD LONG CRK AT TL/R1 JOINT
G-13	9.898	R1	Y	1.00		3.90	4.80	0.70			10.40		3.60	0.00	B	II	M	F		MOD LONG CRK AT TL/R1 JOINT, DELAMINATION
G-14	10.117	LOTL	Y	1.20		3.00					4.20		9.80	0.00	A	IB	L	F		MOD. RUTTING, LIGHT RAVELING
G-15	10.117	L2	Y	1.00		2.10	3.10				6.20		10.20	1.10	A	IB	L	P		SEVERE RUTTING, SEV SPALLING
G-16	10.145	R2	Y	1.00		3.90	2.70	0.80			8.40		1.10	1.10	A	IB	L	F		MOD RUTTING, LIGHT RAVELING
G-17	10.145	ROTL	N	0.50		1.00	2.70				4.20		10.80	0.00	A	IB	L	P		SEVERE RUTTING, MODERATE SPALLING
G-18	10.215	LOTL	N	0.90		1.50					2.40		12.00	0.40	A	IB	L	P		SEVERE RUTTING, LIGHT RAVELING
G-19	10.329	RITL	N	1.20		5.10					6.30		6.00	1.20	A	IB	L	F		MOD. RUTTING, LIGHT SPALLING, MOD LONG CRK AT TL/R1 JOINT
G-20	10.329	R1	Y	1.20		3.60	12.40				17.20		6.00	0.00	A	IB	L	F		LIGHT RUTTING, MOD RAVELING, SUPERELEVATED CURVE

STATE OF FLORIDA DEPARTMENT OF TRANSPORTATION
PAVEMENT EVALUATION CORING AND CONDITION DATA

675-030-09
 Materials
 3/13

Cored by: E. PUCKETT Date: 01/06/20 Page: 2 of 3 Typical Section No.: --

Roadway Section: 46160000		Name: SR 30A (US 98)		Lanes: 6	
Fin. Proj. ID: 217838-4-32-01		From: EAST OF NAUTILUS STREET		Shoulder Type and Condition: GOOD	
F. A. Proj. No.: --		To: EAST OF RICHARD JACKSON BOULEVARD		Inside: GRASS	
County: BAY	SR No.: 30A	Beg MP: 9.006	End MP: 11.390	Lgth: 2.384	Outside: PAVED
Median Curbed (Y / N): Y Paved: Y Lawn: Y Other: --					Curb & Gutter (Y / N): N

Core No.	Mile Post or Sta. No.	Lane	Wheel Path (Y / N)	Pavement Layer (in.)							Core Lgth. (in.)	Base		Crack				Pvmt Cond	Rut Depth (in.)	Cross Slope (%)	PROJECT COMMENTS
				FC-5	FC-12.5	SP-12.5	S	T2				LIMEROCK	SAHM	Depth (in.)	Type	Class	Extent				
G-21	10.417	CO	N		1.50	3.30				4.80	12.00		4.80	B	II	M	F			MOD LONG AND TRANS. CRK / CONCRETE CURB	
G-22	10.638	RITL	N	0.80		4.70	4.90			10.40	6.00		0.00	A	IB	L	F			LIGHT RUTTING, LIGHT RAVELING	
G-23	10.638	RITL	Y	1.00		1.40	6.10			8.50	5.00		8.50	B	II	M	P			SEVERE RUTTING, MOD. LONGITUDINAL CRACKING	
G-24	10.798	ROTL	N	1.00		2.00				3.00	12.00		0.00	A	IB	L	F			MODERATE RUTTING, MODERATE RAVELING AND SPALLING	
G-25	10.873	OR	N	1.60		2.40				4.00	12.00		0.40	A	IB	L	G			LIGHT RAVELING	
G-26	10.873	OL	N	1.30		1.30				2.60	7.40		0.40	A	IB	L	G			LIGHT RAVELING	
G-27	11.001	L1	N	1.10		4.10				5.20	12.00		0.00	A	IB	L	F			LIGHT RAVELING	
G-28	11.001	LITL	N	1.30		4.10				5.40	12.00		1.20	A	IB	L	F			MODERATE RUTTING, MODERATE SPALLING	
G-29	11.020	RITL	Y	1.20		2.90				4.10	12.00		0.00	A	IB	L	F			LIGHT RUTTING, MOD. LONG CRK AT TL/R1 JOINT	
G-30	11.020	R1	Y	1.00		3.10	4.90	1.10		10.10		3.90	0.00	A	IB	L	P			SEVERE RUTTING, MOD LONG CRK AT TL/R1 JOINT	
G-31	11.065	OL	N	1.10		1.80				2.90	7.60		0.00	A	IB	L	G				
G-32	11.065	L2	Y	0.90		1.60	3.30			5.80	9.70		0.00	A	IB	L	F			MODERATE RUTTING, LIGHT RAVELING	
G-33	11.071	R2	Y	0.70		4.70	2.00	1.30		8.70		5.30	0.70	A	IB	L	F			MODERATE RUTTING, DELAMINATION	
G-34	11.071	OR	N	1.60		6.60				8.20	6.00		0.00	A	IB	L	G				
G-35	11.118	R3	Y	1.10		8.30				9.40	8.60		0.00	A	IB	L	F			LIGHT RUTTING, SUPERELEVATED CURVE	
G-36	11.118	ROTL	N		1.50	3.10				4.60	6.00		0.00	A	IB	L	F			LIGHT RUTTING	
G-37	11.192	LOTL	N	0.80		3.50				4.30	6.70		0.80	A	IB	L	F			LIGHT RUTTING, LIGHT RAVELING	
G-38	11.192	L3	Y	0.80		3.80				4.60	7.40		0.00	A	IB	L	F			LIGHT RUTTING, LIGHT RAVELING	
G-39	11.384	L1	Y	1.10		4.40				5.50	12.00		0.00	A	IB	L	F			MODERATE RUTTING, LIGHT RAVELING	
G-40	11.384	LITL	N		1.50	2.20				3.70	12.00		0.00	A	IB	L	F			MODERATE RUTTING	

