PCRPJ03

FLORIDA DEPARTMENT OF TRANSPORTATION PAVEMENT CORING REPORTING PCRO003

PAVEMENT EVALUATION CORING AND CONDITION DATA INPUT DATA REPORT

MANDIST	FINPROJ	TYPSECT	MESSAGE
04	445526-1-52-01	01	THE CONTROL CARD IS CORRECT

FLORIDA DEPARTMENT OF TRANSPORTATION PAVEMENT CORING REPORTING

PAVEMENT EVALUATION CORING AND CONDITION DATA

FIN PROJ: 445526-1-52-01 NAME: N 22ND AVE/SW 12TH CORED BY: GCME

TYP SECT: 01 FROM: SHERIDAN ST DATE: 2023-06-23

TO: STIRLING RD LANES: 2 @ FEET

FA PROJ:

MEDIAN:

BEG MP: .00
COUNTY: BROWARD SHOULDER TYPE

END MP: 1.02 LENGTH: 1.02

SR NUMBER: NOTFOUND INSIDE:

PROJECT MEASUREMENT: ENGLISH OUTSIDE:

CURB & GUTTER: NO

CURBED: NO

06/27/23 FLORIDA DEPARTMENT OF TRANSPORTATION PCRPJ03
PAVEMENT CORING REPORTING PCR0203

PAVEMENT EVALUATION CORING AND CONDITION DATA

CORE	MILE			W					CORE								
NO.	POST	VFY	LN	Р	TOP		PAVEMENT	LAYER	 LNGTH	BASE	SUB	DEPTH	TYP	CLSS	EXT	CND	COMMENTS
				-					 								
					FC2	S1				LR	ST40						
1	.000	Y	L1	Y	1.00	1.50			2.50	6.0	11.0	2.50	C	II	S	P	FULLY CRACKED DURING CO
2	.000	Y	R1	Y	1.00	2.00			3.00	6.0	11.0	3.00	C	II	S	P	FULLY CRACKED DURING CO
3	.000	Y	L1	Y	1.00	1.50			2.50	3.0	16.0	2.50	A	II	S	P	
4	.000	Y	R1	Y	1.00	2.00			3.00	9.0	11.0	.50	C	II	M	P	
	.000																

PCRPJ03 PCRO303

FLORIDA DEPARTMENT OF TRANSPORTATION PAVEMENT CORING REPORTING

PAVEMENT EVALUATION CORING AND CONDITION DATA

COMMENTS

1 NO MP AVAILABLE.
2 MILLING RECOMMENDATIONS: MILL 1.50 INCHES AND

3 REPAVE WITH 1.50 INCHES FC-12.5 (FRICTION COURSE).

FLORIDA DEPARTMENT OF TRANSPORTATION PAVEMENT CORING REPORTING

CODE DESCRIPTIONS

	CODE DESCRIPTIONS
	TYPE DESCRIPTION
A	ALLIGATORING IN WHEELPATH
В	BLOCK CRACKING
С	COMBINATION OF TYPES
	EXTENT DESCRIPTION
L	LIGHT
М	MEDIUM
S	SEVERE
	CLASS DESCRIPTION UNKNOWN

UNKNOWN

UNKNOWN

ΙI

III

CODE DESCRIPTIONS

SURFACE LAYER	
CODE	DESCRIPTION
====	=======================================
ARMI	ASPHALT RUBBER MEMBRANE INTERL
BIND	ASPHALT BINDER COURSE
BRCK	BRICK PAVERS
CONC	PORTLAND CEMENT CONCRETE
CRL	CRACK RELIEF LAYER
FAB	PAVEMENT OVERLAY FABRIC
FC FC	FRICTION COURSE
FC1	FRICTION COURSE 1
FC2	FRICTION COURSE 1 FRICTION COURSE 2
	FRICTION COURSE 2 FRICTION COURSE 3
FC3	FRICTION COURSE 4
FC4	
FC5	FRICTION COURSE 5
FC5B	FRICTION COURSE 5 BONDED
FC6 F12M	FRICTION COURSE 6 FRIC. COURSE 12.5 MODIFIED
F12M F125	FRICTION COURSE 12.5
F125 F95	FRICTION COURSE 12.5 FRICTION COURSE 9.5
F95M	FRIC. COURSE 9.5 FRIC. COURSE 9.5 MODIFIED
F95M S	TYPE S ASPHALTIC CONCRETE
	SAND ASPHALT HOT MIX
SAHM SP1C	9.5 SUPERPAVE COARSE GRADED
SPIC SPIF	9.5 SUPERPAVE COARSE GRADED 9.5 SUPERPAVE FINE GRADED
SP1F SP2C	12.5 SUPERPAVE FINE GRADED
SP2F	
SP2F SP3C	12.5 SUPERPAVE FINE GRADED 19.0 SUPERPAVE COARSE GRADED
SP3C SP3F	19.0 SUPERPAVE COARSE GRADED 19.0 SUPERPAVE FINE GRADED
ST	SURFACE TREATMENT
S1	TYPE S-I ASPHALTIC CONCRETE
S2	TYPE S-II ASPHALTIC CONCRETE
S3	TYPE S-II ASPHALTIC CONCRETE
T1	TYPE I ASPHALTIC CONCRETE
T2	
T3	TYPE II ASPHALTIC CONCRETE TYPE III ASPHALTIC CONCRETE
UNIM	
UNKW	UNIMPROVED SURFACE UNKNOWN
WC	WEARING COURSE
WC1	WEARING COURSE 1
WC1 WC2	WEARING COURSE 1 WEARING COURSE 2
WC3	WEARING COURSE 2 WEARING COURSE 3
WC3 WC4	WEARING COURSE 3 WEARING COURSE 4
WC5	WEARING COURSE 4 WEARING COURSE 5
WC5 WC6	WEARING COURSE 5 WEARING COURSE 6
WC7	WEARING COURSE 6 WEARING COURSE 7
WC7 WC8	WEARING COURSE / WEARING COURSE 8
WCO	O BENUUD CHILINGEN