PAVEMENT EVALUATION CORING AND CONDITION DATA INPUT DATA REPORT

MANDIST	FINPROJ	TYPSECT	MESSAGE
04	450867-1-32-01	01	THE CONTROL CARD IS CORRECT

FLORIDA DEPARTMENT OF TRANSPORTATION PAVEMENT CORING REPORTING

PAVEMENT EVALUATION CORING AND CONDITION DATA

.22 LENGTH:

FIN PROJ: 450867-1-32-01 NAME: W LAKE DR @ BRIDGE # CORED BY: GCME

TYP SECT: 01 FROM: E LAKE DRIVE DATE: 2023-08-14

BEG MP: .19

TO: MERCEDES DRIVE LANES: 2 @ FEET

.02

FA PROJ: D423049B

MEDIAN:

COUNTY: BROWARD SHOULDER TYPE END MP:

SR NUMBER: NOTFOUND INSIDE:

PROJECT MEASUREMENT: ENGLISH OUTSIDE:

CURB & GUTTER: NO CURBED: NO

10/10/23 FLORIDA DEPARTMENT OF TRANSPORTATION PCRPJ03
PAVEMENT CORING REPORTING PCR0203

PAVEMENT EVALUATION CORING AND CONDITION DATA

CORE	MILE			W				CORE				CRA	CK		CROSS
NO.	POST	VFY	LN	Ρ	TOP		PAVEMENT LAYER	 LNGTH	BASE	SUB	DEPTH	TYP	CLSS	EXT	SLOPE COMMENTS
				_				 							
					FC2	S1			LR						
1	.200	Y	R1	Y	1.25	2.75		4.00	11.0		.35	С	III	M	.06 NORTHBOUND
2	.219	Y	R1	Y	1.25	1.75		3.00	16.0		.23	С	II	M	.09 NORTHBOUND
	.000														

10/10/23

FLORIDA DEPARTMENT OF TRANSPORTATION PAVEMENT CORING REPORTING

PCRPJ03 PCRO303

PAVEMENT EVALUATION CORING AND CONDITION DATA

COMMENTS

SEQ ---

- 1 MILLING RECOMMENDATIONS: MILL 1.50 INCHES AND
- 2 REPAVE WITH 1.50 INCHES FC-12.5 (FRICTION COURSE).

FLORIDA DEPARTMENT OF TRANSPORTATION PAVEMENT CORING REPORTING

	CODE DESCRIPTIONS
	TYPE DESCRIPTION
A	ALLIGATORING IN WHEELPATH
В	BLOCK CRACKING
С	COMBINATION OF TYPES
-	EXTENT DESCRIPTION
L	LIGHT
М	MEDIUM
S	SEVERE
CRACK CLASS	CLASS DESCRIPTION

UNKNOWN

UNKNOWN

UNKNOWN

ΙB

ΙI

III

CODE DESCRIPTIONS

SURFACE LAYER CODE ====	DESCRIPTION
ARMI BIND BRCK CONC CRL FAB FC FC1	ASPHALT RUBBER MEMBRANE INTERI ASPHALT BINDER COURSE BRICK PAVERS PORTLAND CEMENT CONCRETE CRACK RELIEF LAYER PAVEMENT OVERLAY FABRIC FRICTION COURSE FRICTION COURSE 1 FRICTION COURSE 2
FC3 FC4 FC5 FC5B FC6 F12M F125 F95	FRICTION COURSE 3 FRICTION COURSE 4 FRICTION COURSE 5 FRICTION COURSE 5 BONDED FRICTION COURSE 6 FRIC. COURSE 12.5 MODIFIED FRICTION COURSE 12.5 FRICTION COURSE 9.5 FRIC. COURSE 9.5 MODIFIED
S SAHM SP1C SP1F SP2C SP2F SP3C SP3F ST	TYPE S ASPHALTIC CONCRETE SAND ASPHALT HOT MIX 9.5 SUPERPAVE COARSE GRADED 9.5 SUPERPAVE FINE GRADED 12.5 SUPERPAVE COARSE GRADED 12.5 SUPERPAVE FINE GRADED 19.0 SUPERPAVE COARSE GRADED 19.0 SUPERPAVE FINE GRADED SURFACE TREATMENT TYPE S-I ASPHALTIC CONCRETE
S2 S3 T1 T2 T3 UNIM UNKW WC WC1	TYPE S-II ASPHALTIC CONCRETE TYPE S-III ASPHALTIC CONCRETE TYPE I ASPHALTIC CONCRETE TYPE II ASPHALTIC CONCRETE TYPE III ASPHALTIC CONCRETE UNIMPROVED SURFACE UNKNOWN WEARING COURSE WEARING COURSE
WC2 WC3 WC4 WC5 WC6 WC7 WC8	WEARING COURSE 2 WEARING COURSE 3 WEARING COURSE 4 WEARING COURSE 5 WEARING COURSE 6 WEARING COURSE 7 WEARING COURSE 8