FLORIDA DEPARTMENT OF TRANSPORTATION PAVEMENT CORING REPORTING

PAVEMENT EVALUATION CORING AND CONDITION DATA INPUT DATA REPORT

MANDIST	FINPROJ	TYPSECT	MESSAGE
04	449559-1-32-01	01	THE CONTROL CARD IS CORRECT

MEDIAN:

PCRPJ03 PCRO103

FLORIDA DEPARTMENT OF TRANSPORTATION PAVEMENT CORING REPORTING

.85 LENGTH: .85

PAVEMENT EVALUATION CORING AND CONDITION DATA

FIN PROJ: 449559-1-32-01 NAME: ROYAL PALM BLVD CORED BY: TIERRA SOUTH FLORIDA

.00

TYP SECT: 01 FROM: EAST UNIVERSITY DRIV DATE: 2024-06-18

TO: RIVERSIDE DRIVE LANES: 3 @ FEET

FA PROJ: D423025B BEG MP:

COUNTY: BROWARD SHOULDER TYPE END MP:

SR NUMBER: NOTFOUND INSIDE:

PROJECT MEASUREMENT: ENGLISH OUTSIDE:

CURB & GUTTER: YES CURBED: NO

06/20/24 FLORIDA DEPARTMENT OF TRANSPORTATION PCRPJ03
PAVEMENT CORING REPORTING PCR0203

PAVEMENT EVALUATION CORING AND CONDITION DATA

CORE	MILE		1	W				CORE				CRA	CK		PMT	
NO.	POST	VFY	LN	PTO		PAVEMEN	T LAYER	 LNGTH	BASE	SUB	DEPTH	TYP	CLSS I	EXT	CND	COMMENTS
				F125	S1	S1			LR	STAB						
1	.100	Y	L3 1	N .9	.90	.90		2.70	7.0	10.0					F	
2	.500	Y	L3 1	N .5	1.00	1.40		2.90	9.0	9.0					F	
3	.800	Y	L3 1	N .6	.60	1.50		2.70	7.0	12.0					F	
	.000															

06/20/24

FLORIDA DEPARTMENT OF TRANSPORTATION PCRPJ03 PAVEMENT CORING REPORTING PCR0303

PAVEMENT EVALUATION CORING AND CONDITION DATA

COMMENTS

SEQ

1 MILLING RECOMMENDATIONS: MILL 1.50 INCHES AND
2 REPAVE WITH 1.50 INCHES FC-12.5 (FRICTION COURSE).

FLORIDA DEPARTMENT OF TRANSPORTATION PAVEMENT CORING REPORTING

CODE DESCRIPTIONS

	CODE DESCRIPTIONS
	TYPE DESCRIPTION
A	ALLIGATORING IN WHEELPATH
В	BLOCK CRACKING
С	COMBINATION OF TYPES
	EXTENT DESCRIPTION
L	LIGHT
М	MEDIUM
S	SEVERE
	CLASS DESCRIPTION
IB	UNKNOWN

UNKNOWN

UNKNOWN

ΙI

III

FLORIDA DEPARTMENT OF TRANSPORTATION PAVEMENT CORING REPORTING

CODE DESCRIPTIONS

SURFACE LAYER CODE ====	DESCRIPTION
ARMI BIND BRCK CONC CRL	ASPHALT RUBBER MEMBRANE INTERL ASPHALT BINDER COURSE BRICK PAVERS PORTLAND CEMENT CONCRETE CRACK RELIEF LAYER
FAB FC FC1 FC2 FC3	PAVEMENT OVERLAY FABRIC FRICTION COURSE FRICTION COURSE 1 FRICTION COURSE 2 FRICTION COURSE 3
FC4 FC5 FC5B FC6 F12M F125	FRICTION COURSE 4 FRICTION COURSE 5 FRICTION COURSE 5 BONDED FRICTION COURSE 6 FRIC. COURSE 12.5 MODIFIED FRICTION COURSE 12.5
F125 F95 F95M S SAHM SP1C	FRICTION COURSE 12.5 FRICTION COURSE 9.5 FRIC. COURSE 9.5 MODIFIED TYPE S ASPHALTIC CONCRETE SAND ASPHALT HOT MIX 9.5 SUPERPAVE COARSE GRADED
SP1F SP2C SP2F SP3C SP3F	9.5 SUPERPAVE FINE GRADED 12.5 SUPERPAVE COARSE GRADED 12.5 SUPERPAVE FINE GRADED 19.0 SUPERPAVE COARSE GRADED 19.0 SUPERPAVE FINE GRADED
ST S1 S2 S3 T1 T2	SURFACE TREATMENT TYPE S-I ASPHALTIC CONCRETE TYPE S-II ASPHALTIC CONCRETE TYPE S-III ASPHALTIC CONCRETE TYPE I ASPHALTIC CONCRETE
T3 UNIM UNKW WC WC1	TYPE II ASPHALTIC CONCRETE TYPE III ASPHALTIC CONCRETE UNIMPROVED SURFACE UNKNOWN WEARING COURSE WEARING COURSE 1
WC2 WC3 WC4 WC5 WC6	WEARING COURSE 2 WEARING COURSE 3 WEARING COURSE 4 WEARING COURSE 5 WEARING COURSE 6
WC7 WC8	WEARING COURSE 7 WEARING COURSE 8