

06/30/25

FLORIDA DEPARTMENT OF TRANSPORTATION
PAVEMENT CORING REPORTING

PCRPJ03
PCRO003

PAVEMENT EVALUATION CORING AND CONDITION DATA
INPUT DATA REPORT

| MANDIST | FINPROJ | TYPSECT | MESSAGE |
|---------|----------------|---------|-----------------------------|
| 04 | 453333-2-52-01 | 01 | THE CONTROL CARD IS CORRECT |

06/30/25

FLORIDA DEPARTMENT OF TRANSPORTATION
PAVEMENT CORING REPORTING

PCRPJ03
PCRO103

PAVEMENT EVALUATION CORING AND CONDITION DATA

FIN PROJ: 453333-2-52-01

NAME: SW WARFILED BLVD.

CORED BY: TIERRA SOUTH FLORIDA, INC.

TYP SECT: 01

FROM: SE 126TH BLVD

DATE: 2025-06-03

TO: FPL ACCES RD

LANES: 2 @ FEET

FA PROJ:

BEG MP: .00

SHOULDER TYPE

COUNTY: MARTIN

END MP: 9.73 LENGTH: 9.73

INSIDE:

SR NUMBER: NOTFOUND

PROJECT MEASUREMENT: ENGLISH

OUTSIDE:

MEDIAN:

CURB & GUTTER: NO

CURBED: NO

FLORIDA DEPARTMENT OF TRANSPORTATION
PAVEMENT CORING REPORTING

PAVEMENT EVALUATION CORING AND CONDITION DATA

| CORE NO. | MILE POST | VFY | LN | W P | --TOP | PAVEMENT LAYER | | | | | CORE LENGTH | BASE | SUB | DEPTH | CRACK TYP | CLSS | EXT | PMT CND | COMMENTS |
|----------|-----------|-----|----|-----|-------|----------------|------|------|------|------|-------------|------|------|-------|-----------|------|-----|---------|-------------------------|
| | | | | | F95 | S1 | S1 | S1 | S1 | S1 | LR | STAB | | | | | | | |
| 1 | .254 | Y | L1 | Y | 1.10 | 1.40 | 1.10 | 2.50 | 2.30 | 3.00 | 11.40 | 5.1 | | | | | | F | SG:BROWN SAND |
| 2 | .660 | Y | R1 | Y | .90 | 1.10 | .80 | 1.80 | 1.50 | .90 | 7.00 | 8.0 | | | | | | F | SG:LIGHT GRAY SAND |
| 3 | 1.039 | Y | L1 | Y | 1.60 | 2.20 | 2.00 | 1.60 | 1.20 | 4.00 | 12.60 | 4.8 | | 3.00 | B | II | M | P | SG:BROWN SAND |
| 4 | 1.039 | Y | OL | N | .70 | 1.00 | 1.60 | 1.30 | 1.40 | 6.70 | 12.70 | 4.0 | | | | | | F | SG:LIGHT BROWN SAND |
| 5 | 1.807 | Y | R1 | Y | .70 | 1.40 | 1.00 | 1.20 | 1.10 | 1.20 | 6.60 | 9.0 | | | | | | F | SG:LIGHT GRAY SAND W/SI |
| 6 | 1.807 | Y | OR | N | .70 | 1.00 | .90 | 1.00 | 1.90 | | 5.50 | 6.0 | | | | | | F | SG:LIGHT GRAY SAND W/SI |
| 7 | 2.319 | Y | L1 | Y | .60 | .50 | .70 | 1.00 | | | 2.80 | 17.0 | | | | | | F | SG:BROWN SAND TRACE LR |
| 8 | 2.603 | Y | L1 | Y | 1.30 | 2.10 | 6.20 | 1.70 | 2.40 | 2.10 | 15.80 | 2.0 | | 2.20 | B | II | M | P | SG:LIGHT GRAY SAND |
| 9 | 2.811 | Y | R1 | Y | .90 | .90 | | | | | 1.80 | 17.0 | | | | | | F | SG:LIGHT GRAY SAND |
| 10 | 3.323 | Y | L2 | Y | 1.00 | 1.10 | .60 | | | | 2.70 | 14.0 | | | | | | F | SG:LIGHT GRAY SAND |
| 11 | 3.323 | Y | OL | N | 1.40 | 1.20 | | | | | 2.60 | 9.0 | | | | | | F | SG:LIGHT GRAY SAND |
| 12 | 3.569 | Y | L1 | Y | 1.30 | 1.40 | 1.80 | 1.70 | 1.90 | 3.50 | 11.60 | | | 2.70 | B | II | M | P | SG:LIGHT GRAY SAND |
| 13 | 3.815 | Y | R1 | Y | 1.30 | 1.00 | .90 | .80 | 1.50 | 2.00 | 7.50 | 8.5 | | | | | | F | SG:LIGHT GRAY SAND |
| 14 | 3.815 | Y | OR | N | .80 | .90 | .80 | | | | 2.50 | 12.0 | 9.0 | | | | | F | SG:LIGHT GRAY SAND W/SI |
| 15 | 4.327 | Y | L1 | Y | 1.00 | 1.00 | 2.00 | 6.60 | 2.40 | | 13.00 | 3.8 | | | | | | F | SG:BROWN SAND |
| 16 | 4.819 | Y | R1 | Y | 1.00 | 1.30 | 2.10 | 2.60 | 1.40 | | 8.40 | 8.8 | | | | | | F | SG:LIGHT GRAY SAND W/LR |
| 17 | 5.331 | Y | L1 | Y | 1.20 | 1.60 | 1.70 | 1.80 | .70 | 2.60 | 9.60 | 3.7 | | 2.10 | B | IB | M | P | SG:LIGHT GRAY SAND |
| 18 | 5.331 | Y | OL | N | 1.20 | 1.00 | 1.50 | 1.50 | 1.80 | 2.70 | 9.70 | 3.6 | | | | | | F | SG:DARK BROWN SAND |
| 19 | 5.823 | Y | R1 | Y | .90 | 1.70 | 1.10 | 2.30 | 1.80 | 6.00 | 13.80 | | | | | | | F | SG:LIGHT GRAY SAND |
| 20 | 5.823 | Y | OR | N | .80 | 1.30 | 2.20 | 1.20 | 2.30 | 2.00 | 9.80 | | | | | | | F | SG:LIGHT GRAY SAND |
| 21 | 6.335 | Y | L1 | Y | 1.50 | 1.30 | 2.10 | 5.20 | 5.00 | | 15.10 | | | | | | | F | SG:LIGHT GRAY SAND |
| 22 | 6.826 | Y | R1 | Y | 1.50 | 1.10 | 1.30 | 2.30 | 2.10 | 5.70 | 14.00 | | | 3.20 | B | IB | M | P | SG:LIGHT GRAY SAND |
| 23 | 7.337 | Y | L1 | Y | 1.00 | 1.70 | .70 | 2.90 | 1.20 | 4.30 | 11.80 | 2.9 | | | | | | F | SG:DARK BROWN SAND TRAC |
| 24 | 7.337 | Y | OL | N | 1.60 | 2.10 | 1.30 | 1.40 | 6.60 | | 13.00 | | | | | | | F | SG:BROWN SAND |
| 25 | 7.836 | Y | R1 | Y | 1.10 | 1.60 | 1.10 | 2.40 | 1.90 | 5.20 | 13.30 | 15.0 | | | | | | F | SG:LIGHT GRAY SILTY SAN |
| 26 | 7.836 | Y | OR | N | 1.40 | .80 | 1.90 | 1.00 | 1.60 | 3.00 | 9.70 | 8.0 | | | | | | F | SG:LIGHT GRAY SILTY SAN |
| 27 | 8.341 | Y | L1 | Y | 1.10 | 1.30 | 1.20 | 1.20 | 1.50 | 3.80 | 10.10 | | 13.0 | 2.10 | B | II | S | P | SG:DARK BROWN SAND W/LR |
| 28 | 8.840 | Y | R1 | Y | 1.30 | 1.10 | 1.70 | 2.00 | 1.80 | 5.00 | 12.90 | | | 2.00 | B | III | S | P | SG:DARK BROWN SAND |
| 29 | 9.351 | Y | L1 | Y | 1.60 | 1.20 | .80 | 2.00 | 1.70 | 5.80 | 13.10 | 2.5 | | | | | | F | SG:DARK BROWN SAND W/TR |
| 30 | 9.351 | Y | OL | N | .80 | 1.20 | 1.50 | 1.40 | 1.70 | 3.00 | 9.60 | 9.8 | 16.0 | 9.60 | B | III | S | P | SG:DARK BROWN SAND W/LR |
| 31 | 9.673 | Y | R1 | Y | 1.40 | 1.30 | 2.10 | 1.00 | 1.30 | 6.00 | 13.10 | | | 1.70 | B | III | S | P | SG:BROWN SILTY SAND |
| 32 | 9.673 | Y | OR | Y | 1.10 | 2.10 | .80 | 1.00 | 1.90 | 2.40 | 9.30 | | | 2.80 | B | III | S | P | SG:BROWN SILTY SAND |
| 33 | .000 | Y | R1 | Y | 1.20 | 1.00 | .80 | | | | 3.00 | 2.0 | 5.0 | | | | | F | SG:LIGHT GRAY SAND W/LR |
| 34 | .000 | Y | R1 | Y | .90 | .50 | 1.20 | | | | 2.60 | 2.5 | 4.0 | 2.60 | B | III | S | P | SG:LIGHT GRAY SAND W/LR |
| 35 | .000 | Y | L1 | Y | 1.20 | 1.00 | 1.70 | | | | 3.90 | 5.0 | | | | | | F | SG:LIGHT GRAY SAND |
| 36 | .000 | Y | R1 | Y | .40 | 1.20 | 1.10 | 1.10 | .60 | | 4.40 | 11.0 | 5.0 | | | | | F | SG:LIGHT GRAY SAND W/LR |
| 37 | .000 | Y | L1 | Y | 1.40 | | | | | | 1.40 | 11.0 | 7.0 | | | | | P | SG:LIGHT GRAY SAND W/LR |
| 38 | .000 | Y | R1 | Y | 1.00 | | | | | | 1.00 | 14.0 | 3.0 | | | | | F | SG:LIGHT GRAY SAND W/LR |
| 39 | 9.157 | Y | L1 | Y | .60 | .80 | 7.10 | 3.20 | | | 11.70 | | | 5.20 | A | III | S | P | SG:BROWN SAND |
| 40 | 9.157 | Y | OL | N | .90 | .90 | 1.40 | .80 | 2.10 | 1.60 | 7.70 | | | 7.70 | B | III | S | P | SG:LIGHT BROWN SAND |
| 41 | 9.650 | Y | R1 | Y | .70 | 1.10 | .60 | 1.00 | 1.60 | | 5.00 | 11.0 | | 5.00 | B | III | S | P | SG:LIGHT BROWN SAND |
| 42 | 9.650 | Y | OR | N | 1.30 | 1.80 | 1.00 | 1.30 | 1.90 | 1.30 | 8.60 | 8.0 | | | | | | F | SG:LIGHT BROWN SAND |
| 43 | .000 | Y | L1 | Y | .60 | .90 | .80 | | | | 2.30 | 19.0 | | | | | | F | |
| 44 | .000 | Y | R1 | Y | 1.00 | .90 | .80 | 2.20 | | | 4.90 | 6.0 | 14.0 | 4.90 | B | III | S | P | SG:LIGHT BROWN SAND W/L |

06/30/25

FLORIDA DEPARTMENT OF TRANSPORTATION
PAVEMENT CORING REPORTING

PCRPJ03
PCRO303

PAVEMENT EVALUATION CORING AND CONDITION DATA

COMMENTS

SEQ

- 1 MILLING RECOMMENDATIONS: MILL 2.50 INCHES AND
- 2 REPAVE WITH 1.25 INCHES SP-9.5 (STRUCTURAL COURSE)
- 3 AND 1.25 INCHES FC-9.5 (FRICTION COURSE).

CODE DESCRIPTIONS

| CRACK TYPE | TYPE DESCRIPTION |
|------------|------------------|
| ===== | ===== |

| | |
|---|---------------------------|
| A | ALLIGATORING IN WHEELPATH |
|---|---------------------------|

| | |
|---|----------------|
| B | BLOCK CRACKING |
|---|----------------|

| | |
|---|----------------------|
| C | COMBINATION OF TYPES |
|---|----------------------|

| CRACK EXTNT | EXTENT DESCRIPTION |
|-------------|--------------------|
| ===== | ===== |

| | |
|---|-------|
| L | LIGHT |
|---|-------|

| | |
|---|--------|
| M | MEDIUM |
|---|--------|

| | |
|---|--------|
| S | SEVERE |
|---|--------|

| CRACK CLASS | CLASS DESCRIPTION |
|-------------|-------------------|
| ===== | ===== |

| | |
|----|---------|
| IB | UNKNOWN |
|----|---------|

| | |
|----|---------|
| II | UNKNOWN |
|----|---------|

| | |
|-----|---------|
| III | UNKNOWN |
|-----|---------|

FLORIDA DEPARTMENT OF TRANSPORTATION
PAVEMENT CORING REPORTING

CODE DESCRIPTIONS

| SURFACE LAYER CODE ===== | DESCRIPTION ===== |
|-----------------------------------|--------------------------------|
| ARMI | ASPHALT RUBBER MEMBRANE INTERL |
| BIND | ASPHALT BINDER COURSE |
| BRCK | BRICK PAVERS |
| CONC | PORTLAND CEMENT CONCRETE |
| CRL | CRACK RELIEF LAYER |
| FAB | PAVEMENT OVERLAY FABRIC |
| FC | FRICTION COURSE |
| FC1 | FRICTION COURSE 1 |
| FC2 | FRICTION COURSE 2 |
| FC3 | FRICTION COURSE 3 |
| FC4 | FRICTION COURSE 4 |
| FC5 | FRICTION COURSE 5 |
| FC5B | FRICTION COURSE 5 BONDED |
| FC6 | FRICTION COURSE 6 |
| F12M | FRIC. COURSE 12.5 MODIFIED |
| F125 | FRICTION COURSE 12.5 |
| F95 | FRICTION COURSE 9.5 |
| F95M | FRIC. COURSE 9.5 MODIFIED |
| S | TYPE S ASPHALTIC CONCRETE |
| SAHM | SAND ASPHALT HOT MIX |
| SP1C | 9.5 SUPERPAVE COARSE GRADED |
| SP1F | 9.5 SUPERPAVE FINE GRADED |
| SP2C | 12.5 SUPERPAVE COARSE GRADED |
| SP2F | 12.5 SUPERPAVE FINE GRADED |
| SP3C | 19.0 SUPERPAVE COARSE GRADED |
| SP3F | 19.0 SUPERPAVE FINE GRADED |
| ST | SURFACE TREATMENT |
| S1 | TYPE S-I ASPHALTIC CONCRETE |
| S2 | TYPE S-II ASPHALTIC CONCRETE |
| S3 | TYPE S-III ASPHALTIC CONCRETE |
| T1 | TYPE I ASPHALTIC CONCRETE |
| T2 | TYPE II ASPHALTIC CONCRETE |
| T3 | TYPE III ASPHALTIC CONCRETE |
| UNIM | UNIMPROVED SURFACE |
| UNKW | UNKNOWN |
| WC | WEARING COURSE |
| WC1 | WEARING COURSE 1 |
| WC2 | WEARING COURSE 2 |
| WC3 | WEARING COURSE 3 |
| WC4 | WEARING COURSE 4 |
| WC5 | WEARING COURSE 5 |
| WC6 | WEARING COURSE 6 |
| WC7 | WEARING COURSE 7 |
| WC8 | WEARING COURSE 8 |