FLORIDA DEPARTMENT OF TRANSPORTATION PAVEMENT CORING REPORTING

PCRPJ03 PCRO003

PAVEMENT EVALUATION CORING AND CONDITION DATA INPUT DATA REPORT

MANDIST	FINPROJ	TYPSECT	MESSAGE
04	440575-2-52-01	01	THE CONTROL CARD IS CORRECT

FLORIDA DEPARTMENT OF TRANSPORTATION PAVEMENT CORING REPORTING

PCRPJ03 PCRO103

PAVEMENT EVALUATION CORING AND CONDITION DATA

FIN PROJ: 440575-2-52-01	NAME: SR 806 (ATLANTIC BLV	CORED BY: TIERRA SOUTH FLORIDA, INC.
TYP SECT: 01	FROM: EAST OF LYONS RD	DATE: 2023-06-30
	TO: TURNPIKE	LANES: 4 @ 11 FEET
FA PROJ:	BEG MP: 1.27	
COUNTY: PALM BEACH		SHOULDER TYPE
SR NUMBER: SR 806	END MP: 1.56 LENGTH: .29	INSIDE: 1 PAVED
MEDIANI, 17 CURD & MEGERATION	PROJECT MEASUREMENT: ENGLISH	OUTSIDE: 1 PAVED
MEDIAN: 17 CURB & VEGETATION		CURB & GUTTER: YES

CURBED: YES

FLORIDA DEPARTMENT OF TRANSPORTATION PAVEMENT CORING REPORTING

PCRPJ03 PCR0203

PAVEMENT EVALUATION CORING AND CONDITION DATA

CORE	MILE			W								CORE				CRA	CK -		PMT	
NO.	POST	VFY	LN	Ρ	TOP		- PA	AVEM	IENT	LAYER		LNGTH	BASE	SUB	DEPTH	TYP	CLS	S EXI	CND	COMMENTS
				-																
					F125	S2	S2	S	33	S2	S3		LR	STAB						
1	1.569	Y	L2	Ν	1.00				1.40		2.80	5.20	9.0						G	LAT 26.453866 LON -80.1
2	1.375	Y	L1	Ν	1.10	.60		70	.90			3.30	11.0						G	LAT 26.453816 LON -80.1
3	1.271	Y	R2	Ν	1.10				1.00	1.00	.60	3.70	8.0	10.0					G	LAT 26.453650 LON -80.1
4	1.425	Y	R1	Ν	1.60				1.00	1.00		3.60	10.0	8.0					G	LAT 26.453666 LON -80.1
	.000																			

PAVEMENT EVALUATION CORING AND CONDITION DATA

COMMENTS

SEQ

```
----
```

1 ALL SLOPES ARE IN %.

- 2 LAST S3 ENTRY FOR PC-01 IS 2 LAYERS, 1.5"AND 1.3".
- 3 SHELL IN THE MIX.
- 4 SSG=LT BR SA W/TR LIMEROCK OR SHELL.
- 5 MILLING RECOMMENDATIONS: MILL 1.50 INCHES AND
- 6 REPAVE WITH 1.50 INCHES FC-12.5 (FRICTION COURSE).

CODE DESCRIPTIONS

CRACK TYPE	TYPE DESCRIPTION
===========	

- A ALLIGATORING IN WHEELPATH
- B BLOCK CRACKING
- C COMBINATION OF TYPES

CRACK EXTNT EXTENT DESCRIPTION

- L LIGHT
- M MEDIUM

S SEVERE

CRACK CLASS CLASS DESCRIPTION

- IB UNKNOWN
- II UNKNOWN
- III UNKNOWN

CODE DESCRIPTIONS

SURFACE LAYER	
CODE	DESCRIPTION
====	
ARMI	ASPHALT RUBBER MEMBRANE INTERL
BIND	ASPHALT BINDER COURSE
BRCK	BRICK PAVERS
CONC	PORTLAND CEMENT CONCRETE
CRL	CRACK RELIEF LAYER
FAB	PAVEMENT OVERLAY FABRIC
FC	FRICTION COURSE
FC1	FRICTION COURSE 1
FC2	FRICTION COURSE 2
FC3	FRICTION COURSE 3
FC4	FRICTION COURSE 4
FC5	FRICTION COURSE 5
FC5B	FRICTION COURSE 5 BONDED
FC6	FRICTION COURSE 6
F12M	FRIC. COURSE 12.5 MODIFIED
F125	FRICTION COURSE 12.5
F95	FRICTION COURSE 9.5
F95M	FRIC. COURSE 9.5 MODIFIED
S	TYPE S ASPHALTIC CONCRETE
SAHM	SAND ASPHALT HOT MIX
SP1C	9.5 SUPERPAVE COARSE GRADED
SP1F	9.5 SUPERPAVE FINE GRADED
SP2C	12.5 SUPERPAVE COARSE GRADED
SP2F	12.5 SUPERPAVE FINE GRADED
SP3C	19.0 SUPERPAVE COARSE GRADED
SP3F ST	19.0 SUPERPAVE FINE GRADED SURFACE TREATMENT
SI S1	TYPE S-I ASPHALTIC CONCRETE
S1 S2	TYPE S-II ASPHALTIC CONCRETE
52 S3	TYPE S-III ASPHALIIC CONCRETE
55 T1	TYPE I ASPHALTIC CONCRETE
T2	TYPE II ASPHALTIC CONCRETE
T3	TYPE III ASPHALTIC CONCRETE
UNIM	UNIMPROVED SURFACE
UNKW	UNKNOWN
WC	WEARING COURSE
WC1	WEARING COURSE 1
WC1 WC2	WEARING COURSE 2
WC3	WEARING COURSE 3
WC4	WEARING COURSE 4
WC5	WEARING COURSE 5
WC6	WEARING COURSE 6
WC7	WEARING COURSE 7
WC8	WEARING COURSE 8