PCRPJ03

FLORIDA DEPARTMENT OF TRANSPORTATION PAVEMENT CORING REPORTING PCRO003

PAVEMENT EVALUATION CORING AND CONDITION DATA INPUT DATA REPORT

MANDIST	FINPROJ	TYPSECT	MESSAGE
04	449280-1-52-01	01	THE CONTROL CARD IS CORRECT

FLORIDA DEPARTMENT OF TRANSPORTATION PAVEMENT CORING REPORTING

PAVEMENT EVALUATION CORING AND CONDITION DATA

.12 LENGTH: .12

FIN PROJ: 449280-1-52-01 NAME: I-95 LOOP RAMP CORED BY: TIERRA SOUTH FLORIDA

TYP SECT: 01 FROM: NB I-95 DATE: 2024-02-10

BEG MP: .00

TO: WB SR-786 LANES: 1 @ FEET

FA PROJ:

MEDIAN:

COUNTY: PALM BEACH SHOULDER TYPE END MP:

SR NUMBER: SR 9 INSIDE:

PROJECT MEASUREMENT: ENGLISH OUTSIDE:

CURB & GUTTER: NO CURBED: NO

02/21/24 FLORIDA DEPARTMENT OF TRANSPORTATION PCRPJ03
PAVEMENT CORING REPORTING PCR0203

PAVEMENT EVALUATION CORING AND CONDITION DATA

CORE	\mathtt{MILE}			W							CORE				CRAC	CK		PMT					
NO.	POST	VF	Z LN	Ρ	TOP		PAV	EMENT	LAYER		LNGTH	BASE	SUB	DEPTH	TYP	CLSS	EXT	CND]	COM	MENTS		
				_																			
					FC5	S1	S1	S1	S1	S1		LR	STAB										
1	.070	Y	R1	Y	1.20	1.40	1.80	2.30	2.00	3.00	11.70	10.0	3.5					F		SG:	BROWN :	SAND W/	LR
2	.080	Y	OR	N	1.70	1.10	.70	1.70	2.40		7.60	12.0						F		SG:	NOT AP	PARENT	
	.000																						

FLORIDA DEPARTMENT OF TRANSPORTATION PAVEMENT CORING REPORTING

PAVEMENT EVALUATION CORING AND CONDITION DATA

COMMENTS

SEQ	
1	MILLING RECOMMENDATIONS:
2	IF FC-5 IS USED:
3	MILL 2.25 INCHES AND REPAVE WITH 1.50 INCHES
4	SP-12.5 INCHES (STRUCTURAL COURSE) AND 0.75 INCHES
5	FC-5 (FRICTION COURSE).
6	OTHERWISE:
7	MILL 2.00 INCHES AND REPAVE WITH 2.00 INCHES
8	FC-12.5 (FRICTION COURSE).

FLORIDA DEPARTMENT OF TRANSPORTATION PAVEMENT CORING REPORTING

CODE DESCRIPTIONS

	CODE DESCRIPTIONS
	TYPE DESCRIPTION
A	ALLIGATORING IN WHEELPATH
В	BLOCK CRACKING
С	COMBINATION OF TYPES
	EXTENT DESCRIPTION
L	LIGHT
М	MEDIUM
S	SEVERE
	CLASS DESCRIPTION

UNKNOWN

UNKNOWN

ΙI

III

FLORIDA DEPARTMENT OF TRANSPORTATION PAVEMENT CORING REPORTING

CODE DESCRIPTIONS

SURFACE LAYER CODE ====	DESCRIPTION
ARMI BIND BRCK CONC CRL FAB FC FC1	ASPHALT RUBBER MEMBRANE INTERL ASPHALT BINDER COURSE BRICK PAVERS PORTLAND CEMENT CONCRETE CRACK RELIEF LAYER PAVEMENT OVERLAY FABRIC FRICTION COURSE FRICTION COURSE
FC2 FC3 FC4 FC5 FC5B FC6 F12M	FRICTION COURSE 2 FRICTION COURSE 3 FRICTION COURSE 4 FRICTION COURSE 5 FRICTION COURSE 5 BONDED FRICTION COURSE 6 FRIC. COURSE 12.5 MODIFIED
F125 F95 F95M S SAHM SP1C SP1F SP2C	FRICTION COURSE 12.5 FRICTION COURSE 9.5 FRIC. COURSE 9.5 MODIFIED TYPE S ASPHALTIC CONCRETE SAND ASPHALT HOT MIX 9.5 SUPERPAVE COARSE GRADED 9.5 SUPERPAVE FINE GRADED 12.5 SUPERPAVE COARSE GRADED
SP2F SP2F SP3C SP3F ST S1 S2 S3	12.5 SUPERPAVE COARSE GRADED 12.5 SUPERPAVE FINE GRADED 19.0 SUPERPAVE COARSE GRADED 19.0 SUPERPAVE FINE GRADED SURFACE TREATMENT TYPE S-I ASPHALTIC CONCRETE TYPE S-II ASPHALTIC CONCRETE TYPE S-III ASPHALTIC CONCRETE
T1 T2 T3 UNIM UNKW WC	TYPE I ASPHALTIC CONCRETE TYPE II ASPHALTIC CONCRETE TYPE III ASPHALTIC CONCRETE UNIMPROVED SURFACE UNKNOWN WEARING COURSE
WC1 WC2 WC3 WC4 WC5 WC6 WC7 WC8	WEARING COURSE 1 WEARING COURSE 2 WEARING COURSE 3 WEARING COURSE 4 WEARING COURSE 5 WEARING COURSE 6 WEARING COURSE 7 WEARING COURSE 8