# FLORIDA DEPARTMENT OF TRANSPORTATION PAVEMENT CORING REPORTING

# PAVEMENT EVALUATION CORING AND CONDITION DATA INPUT DATA REPORT

MANDIST	FINPROJ	TYPSECT	MESSAGE
04	449832-1-52-01	01	THE CONTROL CARD IS CORRECT

# FLORIDA DEPARTMENT OF TRANSPORTATION PAVEMENT CORING REPORTING

#### PAVEMENT EVALUATION CORING AND CONDITION DATA

FIN PROJ: 449832-1-52-01 NAME: FEDERAL HIGHWAY CORED BY: TIERRA SOUTH FLORIDA INC.

END MP: .77 LENGTH: .77

TYP SECT: 01 FROM: US-1 / NORTH DIXIE H DATE: 2024-04-12

BEG MP: .00

TO: 10 AVE S LANES: 2 @ FEET

FA PROJ:

MEDIAN:

COUNTY: PALM BEACH SHOULDER TYPE

SR NUMBER: SR 5 INSIDE:

PROJECT MEASUREMENT: ENGLISH OUTSIDE:

CURB & GUTTER: YES CURBED: NO

04/29/24 FLORIDA DEPARTMENT OF TRANSPORTATION PCRPJ03
PAVEMENT CORING REPORTING PCR0203

### PAVEMENT EVALUATION CORING AND CONDITION DATA

CORE	MILE			W							CORE				CRAC	CK		PMT	
NO.	POST	VFY	LN	Ρ	TOP		- PAV	EMENT	LAYER		LNGTH	BASE	SUB	DEPTH	TYP	CLSS	EXT	CND	COMMENTS
				_															
					F125	S1	S1	S1	S1	S1		LR	STAB						
1	.232	Y	L1	N	1.00	.80	1.30	1.70	1.40	1.80	8.00	5.0	6.0					G	
2	.605	Y	R1	N	1.00	.80	1.00	2.40	3.00	)	8.20	6.0	12.0					G	
	.000																		

04/29/24

# FLORIDA DEPARTMENT OF TRANSPORTATION PCRPJ03 PAVEMENT CORING REPORTING PCR0303

### PAVEMENT EVALUATION CORING AND CONDITION DATA

#### COMMENTS

SEQ	
1	MILLING RECOMMENDATIONS: MILL 1.50 INCHES AND
2	REPAVE WITH 1.50 INCHES FC-12.5 (FRICTION COURSE).

### FLORIDA DEPARTMENT OF TRANSPORTATION PAVEMENT CORING REPORTING

#### CODE DESCRIPTIONS

	CODE DESCRIPTIONS
	TYPE DESCRIPTION
A	ALLIGATORING IN WHEELPATH
В	BLOCK CRACKING
С	COMBINATION OF TYPES
-	EXTENT DESCRIPTION
L	LIGHT
М	MEDIUM
S	SEVERE
	CLASS DESCRIPTION
IB	UNKNOWN

UNKNOWN

UNKNOWN

ΙI

III

### FLORIDA DEPARTMENT OF TRANSPORTATION PAVEMENT CORING REPORTING

### CODE DESCRIPTIONS

SURFACE LAYER CODE ====	DESCRIPTION
ARMI BIND BRCK CONC CRL FAB FC	ASPHALT RUBBER MEMBRANE INTERL ASPHALT BINDER COURSE BRICK PAVERS PORTLAND CEMENT CONCRETE CRACK RELIEF LAYER PAVEMENT OVERLAY FABRIC FRICTION COURSE
FC1 FC2 FC3 FC4 FC5 FC5B FC6	FRICTION COURSE 1 FRICTION COURSE 2 FRICTION COURSE 3 FRICTION COURSE 4 FRICTION COURSE 5 FRICTION COURSE 5 FRICTION COURSE 6 FRICTION COURSE 6
F12M F125 F95 F95M S SAHM SP1C	FRIC. COURSE 12.5 MODIFIED FRICTION COURSE 12.5 FRICTION COURSE 9.5 FRIC. COURSE 9.5 MODIFIED TYPE S ASPHALTIC CONCRETE SAND ASPHALT HOT MIX 9.5 SUPERPAVE COARSE GRADED
SP1F SP2C SP2F SP3C SP3F ST S1	9.5 SUPERPAVE FINE GRADED 12.5 SUPERPAVE COARSE GRADED 12.5 SUPERPAVE FINE GRADED 19.0 SUPERPAVE COARSE GRADED 19.0 SUPERPAVE FINE GRADED SURFACE TREATMENT TYPE S-I ASPHALTIC CONCRETE
S2 S3 T1 T2 T3 UNIM	TYPE S-II ASPHALTIC CONCRETE TYPE S-III ASPHALTIC CONCRETE TYPE I ASPHALTIC CONCRETE TYPE II ASPHALTIC CONCRETE TYPE III ASPHALTIC CONCRETE TYPE III ASPHALTIC CONCRETE UNIMPROVED SURFACE UNKNOWN
UNKW WC WC1 WC2 WC3 WC4 WC5 WC6 WC7 WC8	WEARING COURSE WEARING COURSE 1 WEARING COURSE 2 WEARING COURSE 3 WEARING COURSE 4 WEARING COURSE 5 WEARING COURSE 6 WEARING COURSE 7 WEARING COURSE 8
WCO	MEWITING COOKSE 0