PCRPJ03 PCRO003

PAVEMENT EVALUATION CORING AND CONDITION DATA INPUT DATA REPORT

MANDIST	FINPROJ	TYPSECT	MESSAGE
04	448449-1-52-01	01	THE CONTROL CARD IS CORRECT

PCRPJ03

FLORIDA DEPARTMENT OF TRANSPORTATION PAVEMENT CORING REPORTING PCRO103

PAVEMENT EVALUATION CORING AND CONDITION DATA

FIN PROJ: 448449-1-52-01

NAME: ST LUCIE BLVD

CORED BY: TIERRA SOUTH FLORIDA

TYP SECT: 01

FA PROJ:

FROM: EAST OF SR-615 / N 2

TO: WEST OF SR-5 / US-1

LANES: 2 @ FEET

DATE: 2022-10-14

BEG MP: .00

SHOULDER TYPE

SR NUMBER: SR 608

COUNTY: ST. LUCIE

END MP: .56 LENGTH: .56

INSIDE:

MEDIAN:

PROJECT MEASUREMENT: ENGLISH

OUTSIDE: CURB & GUTTER: YES

CURBED: NO

PAVEMENT EVALUATION CORING AND CONDITION DATA

CORE	MILE			W						CORE				CRA	CK		PMT	
NO.	POST	VFY	LN	P	TOP		PAV	EMENT :	LAYER	LNGTH	BASE	SUB	DEPTH	TYP	CLSS	EXT	CND	COMMENTS
				_														
					F125	SP2F S	2	BIND			LR	LR						
1	.150	Y	R1	Y	1.50		6.70	.60		8.80	5.0	9.0					P	SG:BROWN SAND W/LR
2	.375	Y	L1	Y	1.40		5.10	.60		7.10	4.0	8.0	.30	A	ΙI	L	P	SG:BROWN SAND W/LR
3	.507	Y	OR	N	1.70	.70		.60		3.00	6.3	12.0	.30	A	II	L	P	SG:BROWN SAND W/LR
4	.045	Y	OL	N	1.50		3.40			4.90	9.5	10.0					P	SG:BROWN SAND W/LR
	.000																	

10/24/22

FLORIDA DEPARTMENT OF TRANSPORTATION PAVEMENT CORING REPORTING

PCRPJ03 PCRO303

PAVEMENT EVALUATION CORING AND CONDITION DATA

COMMENTS

SEQ ---

- 1 MILLING RECOMMNEDATIONS: MILL 1.5 INCHES AND
- 2 REPAVE WITH 1.5 INCHES FC-12.5 (FRICTION COURSE).

FLORIDA DEPARTMENT OF TRANSPORTATION PAVEMENT CORING REPORTING

CODE DESCRIPTIONS

	CODE DESCRIPTIONS
	TYPE DESCRIPTION
A	ALLIGATORING IN WHEELPATH
В	BLOCK CRACKING
С	COMBINATION OF TYPES
	EXTENT DESCRIPTION
L	LIGHT
М	MEDIUM
S	SEVERE
	CLASS DESCRIPTION
IB	UNKNOWN

UNKNOWN

UNKNOWN

ΙI

III

CODE DESCRIPTIONS

SURFACE LAYER CODE ====	DESCRIPTION
ARMI BIND BRCK CONC CRL FAB FC FC1 FC2	ASPHALT RUBBER MEMBRANE INTERI ASPHALT BINDER COURSE BRICK PAVERS PORTLAND CEMENT CONCRETE CRACK RELIEF LAYER PAVEMENT OVERLAY FABRIC FRICTION COURSE FRICTION COURSE 1 FRICTION COURSE 2
FC3 FC4 FC5 FC5B FC6 F12M F125 F95	FRICTION COURSE 3 FRICTION COURSE 4 FRICTION COURSE 5 FRICTION COURSE 5 BONDED FRICTION COURSE 6 FRIC. COURSE 12.5 MODIFIED FRICTION COURSE 12.5 FRICTION COURSE 9.5 FRIC. COURSE 9.5 MODIFIED
S SAHM SP1C SP1F SP2C SP2F SP3C SP3C SP3F ST	TYPE S ASPHALTIC CONCRETE SAND ASPHALT HOT MIX 9.5 SUPERPAVE COARSE GRADED 9.5 SUPERPAVE FINE GRADED 12.5 SUPERPAVE COARSE GRADED 12.5 SUPERPAVE FINE GRADED 19.0 SUPERPAVE COARSE GRADED 19.0 SUPERPAVE FINE GRADED SURFACE TREATMENT TYPE S-I ASPHALTIC CONCRETE
S2 S3 T1 T2 T3 UNIM UNKW WC	TYPE S-II ASPHALTIC CONCRETE TYPE S-III ASPHALTIC CONCRETE TYPE I ASPHALTIC CONCRETE TYPE II ASPHALTIC CONCRETE TYPE III ASPHALTIC CONCRETE UNIMPROVED SURFACE UNKNOWN WEARING COURSE
WC1 WC2 WC3 WC4 WC5 WC6 WC7 WC8	WEARING COURSE 1 WEARING COURSE 2 WEARING COURSE 3 WEARING COURSE 4 WEARING COURSE 5 WEARING COURSE 6 WEARING COURSE 7 WEARING COURSE 8