PCRPJ03 PCRO003

PAVEMENT EVALUATION CORING AND CONDITION DATA INPUT DATA REPORT

MANDIST	FINPROJ	TYPSECT	MESSAGE
04	449281-1-52-01	01	THE CONTROL CARD IS CORRECT

PCRPJ03 PCR0103

PAVEMENT EVALUATION CORING AND CONDITION DATA

FIN PROJ:	449281-1-52-01	NAME :	NB I-95 OFF RAMP WB	CORED BY:	WSP	
TYP SECT:	01	FROM:	SR-9 / I-95	DATE:	2023-04-25	
		то:	SR-68 / ORANGE AVE	LANES:	@ FEE'	г
FA PROJ:		BEG MP:	.00			
COUNTY:	ST. LUCIE	END MP:	.08 LENGTH: .08	SHOULDEF	R TYPE	
SR NUMBER:		END MP.	.00 LENGIR00	INSIDE:		
MEDIAN:		PROJECT	MEASUREMENT: ENGLISH	OUTSIDE:		
CURBED:	NO		C	URB & GUTTER:	NO	
CORDED	110					

PCRPJ03 PCR0203

PAVEMENT EVALUATION CORING AND CONDITION DATA

CORE	MILE			W					CORE				CRA	СК		PMT	
NO.	POST	VFY	LN	Ρ	TOP		PAVEMENT	' LAYER	 LNGTH	BASE	SUB	DEPTH	TYP	CLSS	EXT	CND	COMMENTS
				-					 								
					FC5	SP2C	SP3C			LR							
1	.090	Ν	R1	Ν	.70	3.20	5.00		8.90	12.5		2.00	С	III	L	F	MECHANICAL GOUGING
2	.140	Ν	R1	Y	.90	1.50	5.60		8.00	13.8		2.00	С	II	L	F	MECHANICAL GOUGING
	.000																

PCRPJ03 PCRO303

PAVEMENT EVALUATION CORING AND CONDITION DATA

COMMENTS

SEQ

- 1 MILLING RECOMMDATIONS (2 OPTIONS):
- 2 OPTION 1:
- 3 MILL 2.25 INCHES AND REPAVE WITH 1.50 INCHES
- 4 SP-12.5 (STRUCTURAL COURSE) AND 0.75 INCHES FC-5
- 5 (FRICTION COURSE).
- 6 OPTION 2:
- 7 MILL 1.50 INCHES AND REPAVE WITH 1.50 INCHES
- 8 FC-12.5 (FRICTION COURSE).

CODE DESCRIPTIONS

	CODE DESCRIPTIONS
CRACK TYPE	TYPE DESCRIPTION
A	ALLIGATORING IN WHEELPATH
В	BLOCK CRACKING
С	COMBINATION OF TYPES
CRACK EXTNT	EXTENT DESCRIPTION
L	LIGHT

M MEDIUM

S SEVERE

CRACK CLASS CLASS DESCRIPTION

IB UNKNOWN

II UNKNOWN

III UNKNOWN

CODE DESCRIPTIONS

SURFACE LAYER	
CODE	DESCRIPTION
====	
ARMI	ASPHALT RUBBER MEMBRANE INTERL
BIND	ASPHALT BINDER COURSE
BRCK	BRICK PAVERS
CONC	PORTLAND CEMENT CONCRETE
CRL	CRACK RELIEF LAYER
FAB	PAVEMENT OVERLAY FABRIC
FC	FRICTION COURSE
FC1	FRICTION COURSE 1
FC2	FRICTION COURSE 2
FC3	FRICTION COURSE 3
FC4	FRICTION COURSE 4
FC5	FRICTION COURSE 5
FC5B	FRICTION COURSE 5 BONDED
FC6	FRICTION COURSE 6
F12M	FRIC. COURSE 12.5 MODIFIED
F125	FRICTION COURSE 12.5
F95	FRICTION COURSE 9.5
F95M	FRIC. COURSE 9.5 MODIFIED
S	TYPE S ASPHALTIC CONCRETE
SAHM	SAND ASPHALT HOT MIX
SP1C	9.5 SUPERPAVE COARSE GRADED
SP1F	9.5 SUPERPAVE FINE GRADED
SP2C	12.5 SUPERPAVE COARSE GRADED
SP2F	12.5 SUPERPAVE FINE GRADED
SP3C	19.0 SUPERPAVE COARSE GRADED
SP3F ST	19.0 SUPERPAVE FINE GRADED SURFACE TREATMENT
SI S1	TYPE S-I ASPHALTIC CONCRETE
S1 S2	TYPE S-II ASPHALTIC CONCRETE
52 S3	TYPE S-III ASPHALIIC CONCRETE
55 T1	TYPE I ASPHALTIC CONCRETE
T2	TYPE II ASPHALTIC CONCRETE
T3	TYPE III ASPHALTIC CONCRETE
UNIM	UNIMPROVED SURFACE
UNKW	UNKNOWN
WC	WEARING COURSE
WC1	WEARING COURSE 1
WC1 WC2	WEARING COURSE 2
WC3	WEARING COURSE 3
WC4	WEARING COURSE 4
WC5	WEARING COURSE 5
WC6	WEARING COURSE 6
WC7	WEARING COURSE 7
WC8	WEARING COURSE 8