

**State of Florida Department of Transportation**  
**PAVEMENT EVALUATION AND CONDITION DATA SHEET**

<b>Project No.:</b> 450581-1					<b>Cored By:</b> J. Wilkes & M. Soto (Intertek-PSI)					<b>Date:</b> 2/6/2024 - 2/7/2024					<b>Page No.:</b> 1 of 2								
<b>County:</b> Lake					<b>Highway Sect. No:</b> 11010000					<b>From:</b> Lakeshore Blvd.					<b>To:</b> Lake Eustis Drive								
<b>Road No.:</b> SR 500 (US 441)					<b>Begin MP:</b> 13.966					<b>End MP:</b> 15.280					<b>Length:</b> 1.314 miles								
Core No.	MP	Distance from left edge of lane (ft.)	Lane	Wheel Path	Pavement Layer (in.)							Base		Crack				Pavt Cond.	Rut Depth (in.)	Cross Slope (%)	Comments		
					FC-6	Type SP					Core Length (in.)	Type	Thick-ness (in.)	Depth (in.)	Type	Class	Extent						
1	14.000	3.5	R3	X	1.8	3.5						5.3	LR	10.3	1.8	Br	IB	L	P				
2	14.129	3.5	R3	X	1.1	4.1						5.2	LR	11.1	2.5	Br	IB	L	P				
3	14.551	9.0	R3	X	1.5	4.0						5.5	LR	9.8	2.5	Br	IB	L	P				
4	14.830	4.0	RRTL		1.8	5.9						7.7	LR	8.2	-	-	-	-	F				Eastbound Right turn lane onto N St. Clair Abrams Ave
5	15.197	4.0	R3		1.5	3.5						5.0	LR	9.8	2.5	TR	II	M	P				
6	15.188	7.0	L3	X	1.5	3.8						5.3	LR	10.1	-	-	-	-	F				
8	14.785	2.0	L3	X	1.5	4.2						5.7	LR	9.9	1.5	Br	II	M	F				
10	14.055	7.0	L3	X	1.7	3.8						5.5	LR	10.3	-	-	-	-	F				
11	13.966	5.0	R1		1.3	4.1						5.4	LR	10.4	-	-	-	-	F				
12	13.997	5.0	RLTL		1.8	4.2						6.0	LR	10.1	-	-	-	-	F				Eastbound Left turn lane onto N Lakeshore Blvd
13	14.345	6.0	RLTL		2.1	2.9						5.0	LR	11.0	-	-	-	-	F				Eastbound Left turn lane into Tavares Commerce Center
14	14.600	8.0	R1	X	2.0	3.5						5.5	LR	9.8	2.5	Br	III	S	P				
16	15.126	7.0	R1	X	1.3	3.2						4.5	LR	8.9	2.0	Br	IB	M	P				

**Remarks:** Crack Depth of "B" indicates full depth crack to the base.      EOP = Edge of Pavement      In lieu of MP for Ramp Cores, Location Distance Measured in Feet from Ramp Gore

Crack Extent: L= Light; M= Moderate; S= Severe      Pavement Condition: G= Good; F= Fair; P= Poor

Crack Types: A= Alligator; BI= Block; Br= Branch; SL= Single Longitudinal; ST= Single Transverse; R= Reflective; J= Joint; OGFC= Open-Graded FC Stress Crack

Base Types: LR= Limerock; COQ= Coquina; SC= Soil Cement; ABC= Asphalt Base; SAHM= Sand Asphalt Hot Mix; SBRM= Sand Bituminous Road Mix; NB= No Base

**State of Florida Department of Transportation**  
**PAVEMENT EVALUATION AND CONDITION DATA SHEET**

<b>Project No.:</b>	450581-1	<b>Cored By:</b>	J. Wilkes & M. Soto (Intertek-PSI)	<b>Date:</b>	2/6/2024 - 2/7/2024	<b>Page No.:</b>	2 of 2
<b>County:</b>	Lake	<b>Highway Sect. No:</b>	11010000	<b>From:</b>	Lakeshore Blvd.	<b>To:</b>	Lake Eustis Drive
<b>Road No.:</b>	SR 500 (US 441)	<b>Begin MP:</b>	13.966	<b>End MP:</b>	15.280	<b>Length:</b>	1.314 miles

Core No.	MP	Distance from left edge of lane (ft.)	Lane	Wheel Path	Pavement Layer (in.)							Base		Crack				Pavt Cond.	Rut Depth (in.)	Cross Slope (%)	Comments
					FC-6	Type SP					Core Length (in.)	Type	Thick-ness (in.)	Depth (in.)	Type	Class	Extent				
17	15.170	7.0	RLTL	X	1.8	3.6					5.4	LR	10.1	-	-	-	-	F			Eastbound Left turn onto Lake Eustis Dr. -- RLTL-1 (inside turn lane)
18	15.200	3.5	R1	X	1.5	3.8					5.3	LR	9.8	2.0	Br	II	M	P			
19	15.095	5.0	LLTL		2.0	2.5					8.7	ABC	4.2	-	-	-	-	F			Westbound Left turn into Checker's entrance
21	14.594	3.0	L1	X	1.5	3.5					5.0	LR	11.3	2.0	Br	II	M	P			
22	14.573	5.0	LLTL		2.0	3.1					5.1	LR	10.6	-	-	-	-	F			Westbound Left turn lane onto N Joanna Ave
24	14.271	8.0	LLTL	X	1.2	3.5					18.0	ABC	13.3	-	-	-	-	F			Westbound Left turn lane onto SR 19 (pick the worst of the duals)
25											0.0										

**Remarks:** Crack Depth of "B" indicates full depth crack to the base.      EOP = Edge of Pavement      In lieu of MP for Ramp Cores, Location Distance Measured in Feet from Ramp Gore

Crack Extent: L= Light; M= Moderate; S= Severe      Pavement Condition: G= Good; F= Fair; P= Poor

Crack Types: A= Alligator; Bl= Block; Br= Branch; SL= Single Longitudinal; ST= Single Transverse; R= Reflective; J= Joint; OGFC= Open-Graded FC Stress Crack

Base Types: LR= Limerock; COQ= Coquina; SC= Soil Cement; ABC= Asphalt Base; SAHM= Sand Asphalt Hot Mix; SBRM= Sand Bituminous Road Mix; NB= No Base