

**State of Florida Department of Transportation**  
**PAVEMENT EVALUATION AND CONDITION DATA SHEET**

Project No.:		427273-1		Cored By:		Universal Engineering Sciences		Date:		7/31/2010		Page No.:		1 of 1						
County:		Marion		Highway Sect. No.:		36009		From:		South of 92nd Place		To:		South of Juniper Road						
Road No.:		SR 35		Begin M.P.:		1.600		End M.P.:		3.910		Length:		2.310						
Core No.	MP	Distance from left edge of lane (ft)	Lane	Wheel Path						Base		Crack				Pav. Cond.	Rut Depth (in)	Cross Slope (%)	Comments	
					FC 6	Type S	ARMI	Type II	Type S	Core Length (in)	Type	Thick-ness (in)	Depth (in)	Type	Class					Extent
1	1.653	9.5	R1	X	2.0	5.7				7.7	LR	11.8					F	0.3	2.9	Granite in layers
2	1.653	2	OR		2.5	5.5				8.0	LR	11.0					F	0.0	2.6	Granite in layers
3	1.653	3	CL		1.5	1.6	0.4	0.9		4.4	LR	7.6					F	0.0	2.0/2.4	to L1/ to R1
4	2.078	7	R1		1.4	1.4	0.3	0.4		3.5	LR	9.5	B	SL	I	S	P	0.1	1.6	
5	2.808	7	RRTL		1.5	2.9				4.4	LR	10.1	1.0	SL	I	S	P	0.1	3.1	RRTL to SE 83rd Street
6	2.808	10.5	R1		1.4	1.4	0.5		1.4	4.7	LR	8.3	2.5	SL	I	M	P	0.2	2.4	
7	3.230	2	OR		1.5	2.5				4.0	LR	8.0					F	0.0	7.4	
8	3.233	5	RRTL		1.1	1.9				3.0	LR	9.0					F	0.0	6.2	RRTL to SE 78th Street
9	3.233	8.5	R1	X	1.6	1.1	0.4	1.8		4.9	LR	8.6	B	SL	I	M	P	0.0	3.3/4.2	LWP/RWP
10	3.233	2.5	CL		1.2	2.2		0.5		3.9	LR	8.9					F	0.0	2.4/0.3	to L1/ to R1
11	3.810	2	OR		1.2			1.5		2.7	LR	8.3					F	0.0	5.6	
12	3.805	6.5	R1		1.1	1.7	0.3			3.1	LR	8.4	B	SL	I	M	P	0.1	4.3	ARMI on Limerock.
13	3.805	2	OL		1.5	1.1				2.6	LR	11.9					F	0.0	4.6	
14	3.803	7.5	L1		1.5	2.1				3.6	LR	10.2	B	SL	I	M	P	0.2	2.4	No ARMI in core.
15	3.225	8.5	L1	X	1.7	1.5	0.4			3.6	LR	10.9	B	SL	I	L	P	0.1	5.0	
16	3.225	9	OL	X	2.0	1.3				3.3	LR	7.2					F	0.0	9.2	
17	2.808	2	OL		2.3			1.4		3.7	LR	9.6					F	0.0	5.4	
18	2.808	1	L1		1.7	1.5	0.5			3.7	LR	9.3	B	SL	I	L	F	0.3	0.2/-1.4	
19	2.529	2	OL		1.7	1.8				3.5	LR	6.5					F	0.0	7.9	LWP/RWP, ARMI on Limerock
20	2.529	10	L1	X	1.4	1.3	0.6	1.7		5.0	LR	9.3	B	SL	I	M	P	0.2	3.7	
21	2.078	8	L1	X	1.4	1.4	0.7	1.4		4.9	LR	5.6	B	SL	I	S	P	0.2	4.3	
22	1.824	6	LRTL		1.6	3.7				5.3	LR	12.7					G	0.0	2.6	Granite in layers; LRTL to SE 92nd Place Road
23	1.650	2	OL		1.8	3.5				5.3	LR	14.7					G	0.0	2.8	Granite in layers
24	1.650	9	L1	X	1.6	4.0				5.6	LR	12.9					G	0.2	3.4	Granite in layers
25	2.528	2	OR		1.5	2.1				3.6	LR	17.9					G	0.0	2.4	Granite in layers, New Widening

26	2.528	7	R1		1.6	2.1				3.7	LR	15.6					G	0.0	2.5	New Widening
27	2.528	2	CL		1.4	1.4	0.4	0.5		3.7	LR	9.3					F	0.0	2.7	to R1, Additional Core

**Remarks:** Crack Depth of "B" indicates full depth crack to the base. EOP = Edge of Pavement  
Crack Extent: L= Light; M= Moderate; S= Severe      Pavement Condition: G= Good; F= Fair; P= Poor  
Crack Types: A= Alligator; Bl= Block; Br= Branch; SL= Single Longitudinal; ST= Single Transverse  
Base Types: LR= Limerock; COQ= Coquina; SC= Soil Cement; ABC= Asphalt Base; SAHM= Sand Asphalt Hot Mix