

**State of Florida Department of Transportation
PAVEMENT EVALUATION AND CONDITION DATA SHEET**

Project No.:		429053-1		Cored By:		Ardaman		Date:		7/15/12-7/17/12		Page No.:										
County:		Marion		Highway Sect. No.:		36070		From:		CR 326		To:		CR 225A								
Road No.:		SR 500 (US 27)		Begin MP:		6.555		End MP:		14.448		Length:		7.893 Miles								
Core No.	MP	Distance from left edge of lane (ft.)	Lane	Wheel Path	Base								Crack				Pavt Cond.	Rut Depth (in)	Cross Slope (%)	Comments		
					FC-2	FC-5	SP 12.5	TYPE-S	Type II	ABC	Binder	Core Length (in)	Type	Thickness (in)	Depth (in)	Type					Class	Extent
1	6.732	3.0	L1	X	0.5			3.2				3.7	LR	---	0.5	OGFC	I	L	F			
2	6.731	8.0	RLTL	X	0.5			2.9				3.4	LR	---	0.3	OGFC	I	L	F			
3	6.880	10.0	LLTL	X	0.5			4.0				4.5	LR	10.0	0.2	OGFC	I	L	F			Split Core at 1-inch
4	6.932	2.0	R1	X	0.6			2.8				3.4	LR	---	0.2	OGFC	I	L	F			
5	7.002	2.5	OL		0.6			2.1				2.7	LR	5.0	---	---	---	---	F			
6	7.004	8.0	L2	X	0.5			3.0				3.5	LR	---	0.2	OGFC	I	L	F			
7	6.999	7.5	R2		0.5			2.7				3.2	LR	---	B	Br	II	M	F			
8	6.999	1.5	OR		0.4			1.4				1.8	LR	10.1	0.1	OGFC	I	L	F			
9	7.221	3.0	MXO		0.7			4.1				4.8	LR	10.1	0.2	OGFC	I	L	F			
10	7.288	4.0	L2	X	0.6			3.4				4.0	LR	10.0	0.2	OGFC	I	L	F			
11	7.290	8.5	L1	X	0.6			2.9				3.5	LR	9.8	B	Br	II	L	F			
12	7.433	10.0	R1	X	0.8			3.1				3.9	LR	10.0	1.7	Br	II	M	F			
13	7.425	3.5	R2	X	0.7			3.0				3.7	LR	9.8	1.7	Br	II	M	F			
14	7.760	3.0	OL		0.7			1.7				2.4	LR	---	0.1	OGFC	I	L	F			
15	7.758	9.5	L2	X	0.8			3.0				3.8	LR	---	0.2	OGFC	I	L	F			
16	7.780	3.5	L1	X	0.4			3.5				3.9	LR	---	0.2	OGFC	I	L	F			
17	7.844	4.0	R2	X	0.4			3.6				4.0	LR	---	0.4	OGFC	III	M	F			
18	7.844	1.0	OR		0.5			1.8				2.3	LR	---	0.5	OGFC	I	L	F			
19	7.956	3.5	R1	X	0.9			7.8				8.7	LR	---	0.2	OGFC	I	L	F			Split Core at 1-inch
20	8.182	10.0	L2	X	0.5			2.8				3.3	LR	10.1	1.5	B	I	L	F			
21	8.256	3.0	L1	X	0.5			3.1				3.6	LR	9.8	0.1	OGFC	I	L	F			
22	8.364	5.5	RLTL		0.5			4.0				4.5	LR	10.0	0.5	OGFC	I	L	F			
23	8.363	8.0	R1	X	0.7			3.1				3.8	LR	10.3	0.5	OGFC	II	M	F			
24	8.461	9.0	R2	X	0.6			3.0				3.6	LR	9.8	0.4	OGFC	II	M	F			
25	8.496	7.0	LLT2		0.5			2.8				3.3	LR	9.8	0.5	OGFC	II	M	F			
26	8.675	7.0	L1		0.4			2.7				3.1	LR	---	0.4	OGFC	I	L	F			
27	8.677	7.5	RLTL		0.6			3.2				3.8	LR	---	1.4	Br	II	L	F			
28	8.677	3.5	R1	X	0.9			3.6				4.5	LR	---	1.0	Br	II	L	F			
29	8.847	9.5	LLTL	X	0.8			3.2				4.0	LR	---	0.1	OGFC	I	L	F			
30	8.903	3.0	OL		0.7			2.8				3.5	LR	5.0	0.1	OGFC	I	L	F			
31	8.901	10.0	L2	X	0.7			7.4				8.1	LR	---	0.5	OGFC	I	L	F			
32	8.980	10.0	R2	X	0.5			3.3				3.8	LR	---	0.4	OGFC	I	L	F			
33	8.980	2.5	OR		0.5			2.3				2.8	LR	9.5	0.4	OGFC	I	L	F			
34	9.009	2.0	MXO					3.9				3.9	LR	10.0	---	---	---	---	F			
35	9.156	6.5	R1		0.5			3.3				3.8	LR	10.0	0.5	OGFC	I	L	F			
36	9.205	7.5	L1		0.5			9.7				10.2	LR	10.1	0.2	OGFC	I	L	F			
37	9.273	3.0	L2	X	0.8			2.6				3.4	LR	9.8	0.2	OGFC	I	L	F			
38	9.362	3.0	R2	X	0.5			3.6				4.1	LR	10.1	0.2	OGFC	I	L	F			
39	9.639	3.0	R1	X	0.7			3.9				4.6	LR	---	1.2	Br	III	M	F			
40	9.720	7.5	L1		0.6			3.6				4.2	LR	---	0.2	OGFC	I	L	F			
41	9.851	9.0	LLTL	X	0.7			3.9				4.6	LR	10.1	0.1	OGFC	I	L	F			
42	9.857	8.5	R1	X	0.5			3.1				3.6	LR	---	1.0	Br	I	L	F			
43	9.944	9.0	L1	X	0.5			3.3				3.8	LR	---	0.2	OGFC	I	L	F			
44	10.130	7.0	RLTL		0.4		4.6			4.8		9.8	ABC	4.8	0.2	OGFC	I	L	F			ABC has Granite; Structural course is Limestone.
45	10.152	2.5	MXO	X	0.4		5.7			5.8		11.9	ABC	5.8	0.2	OGFC	I	L	F			ABC has Granite; Structural course is Limestone.
46	10.187	6.0	R2		0.5			3.3				3.8	LR	10.1	0.4	OGFC	I	L	F			
47	10.187	2.5	OR		0.6			1.7				2.3	LR	---	0.3	OGFC	I	L	F			
48	10.279	2.5	OL		0.5			3.3				3.8	LR	---	0.3	OGFC	I	L	F			
49	10.276	3.0	L1	X	0.5			2.5				3.0	LR	10.8	0.1	OGFC	I	L	F			

Core No.	MP	Distance from left edge of lane (ft.)	Lane	Wheel Path									Base		Crack			Pavt Cond.	Rut Depth (in)	Cross Slope (%)	Comments	
					FC-2	FC-5	SP 12.5	TYPE-S	Type II	ABC	Binder	Core Length (ft.)	Type	Thickness (in)	Depth (in)	Type	Class					Extent
50	10.392	3.0	R1	X	0.6			2.9				3.5	LR	---	0.6	OGFC	I	L	F			
51	10.472	8.5	L1	X	0.7			3.2				3.9	LR	10.8	0.4	OGFC	I	L	F			
52	10.713	7.0	L1		0.6			3.3				3.9	LR	---	0.6	OGFC	I	L	F			
53	10.798	9.0	R2	X	0.6			3.9			0.5	5.0	LR	---	B	Br	II	M	F			
54	10.798	3.0	OR		0.5			3.0				3.5	LR	6.0	0.5	OGFC	I	L	F			
55	10.952	3.0	OL		0.7			1.8				2.5	LR	4.7	0.3	OGFC	I	L	F			
56	10.952	2.0	L2	X	0.6			3.1				3.7	LR	---	0.3	OGFC	I	L	F			
57	10.959	8.0	R1	X	0.5			3.4				3.9	LR	---	1.4	Br	I	M	F			
58	11.104	3.5	RLTL	X	0.6			3.5				4.1	LR	9.8	0.3	OGFC	I	L	F			
59	11.293	7.0	L1		0.5			3.5				4.0	LR	10.0	0.2	OGFC	I	L	F			
60	11.293	9.0	LLTL	X	0.6			3.3				3.9	LR	9.8	2.0	Br	II	M	F			
61	11.306	4.0	R2	X	0.4			3.0				3.4	LR	10.1	0.4	OGFC	I	L	F			
62	11.410	7.5	L2		0.6			3.4				4.0	LR	10.5	2.1	Br	II	M	F			
63	11.428	3.5	R1	X	0.5			3.5				4.0	LR	10.1	0.3	OGFC	I	L	F			
64	11.598	9.0	R2	X	0.5			2.4				2.9	LR	---	1.0	Br	I	L	F			
65	11.731	7.5	R1		0.5			5.2				5.7	LR	10.3	0.5	OGFC	I	L	F			
66	11.758	2.5	L2	X	0.8			2.9				3.7	LR	---	1.0	Br	I	L	F			
67	11.835	6.0	MXO		0.6			3.7				4.3	LR	10.8	0.2	OGFC	I	L	F			
68	12.004	7.5	L1		0.5			3.3				3.8	LR	---	0.5	OGFC	I	L	F			
69	12.131	7.5	RLTL		0.5			3.4				3.9	LR	---	0.1	OGFC	I	L	F			
70	12.159	9.0	R2	X	0.4			2.7				3.1	LR	---	0.4	OGFC	I	L	F			
71	12.159	2.0	OR		0.5			1.7				2.2	LR	---	0.1	OGFC	I	L	F			
72	12.159	7.5	LRTL		0.7			3.0				3.7	LR	---	0.2	OGFC	I	L	F			
73	12.338	8.5	R1	X	0.9			3.6				4.5	LR	10.3	0.2	OGFC	I	L	F			
74	12.399	2.5	OL		0.5			2.2				2.7	LR	---	0.4	OGFC	I	L	F			
75	12.402	2.0	L3		0.5			3.3				3.8	LR	10.1	0.5	OGFC	I	L	F			
76	12.404	8.5	L1	X	0.5			3.4				3.9	LR	10.3	0.4	OGFC	I	L	F			
77	12.673	7.5	L1		0.8			2.9				3.7	LR	---	0.4	OGFC	I	L	F			
78	12.852	2.5	OL		0.5			1.9				2.4	LR	6.3	0.3	OGFC	I	L	F			
79	12.855	8.5	L2	X	0.6			3.1				3.7	LR	---	0.5	OGFC	I	L	F			
80	12.910	9.5	R2	X	0.5			2.7				3.2	LR	---	1	Br	II	M	F			
81	12.907	3.0	OR		0.4			1.7				2.1	LR	6.5	0.1	OGFC	I	L	F			
82	13.109	2.5	R1	X	0.5			3.2				3.7	LR	---	1	Br	I	L	F			
83	13.026	3.0	MXO		0.5			4.0				4.5	LR	12.5	0.2	OGFC	I	L	F			
84	13.158	10.0	L2	X	0.5			3.3				3.8	LR	10.3	0.3	OGFC	I	L	F			
85	13.200	1.5	R2		0.6			2.7				3.3	LR	10.3	0.4	OGFC	I	L	F			
86	13.312	7.5	L1		0.6			3.5				4.1	LR	10.3	0.9	OGFC	I	L	F			
87	13.310	3.5	LLTL	X	0.8			4.1				4.9	LR	10.0	---	---	---	---	F			
88	13.453	3.5	RLTL	X		0.8	2.2			6.8		9.8	ABC	9.0	---	---	---	---	F			
89	13.453	8.5	R1	X	0.4			6.6	1.0		0.5	8.5	LR	10.0	0.3	OGFC	I	L	F			
90	13.584	3.0	L1	X	0.4			3.9				4.3	LR	9.8	1.6	Br	II	L	F			
91	13.587	9.0	R1	X	0.8			4.3	1.7		0.5	7.3	LR	9.8	0.6	OGFC	I	L	F			
92	13.768	2.5	OL			0.8	2.2			7.5		10.5	LR	---	---	---	---	---	F			
93	13.766	8.5	LRTL	X		0.5	2.1			7.5		10.1	LR	3.5		OGFC	I	L	F			
94	13.957	2.5	R2	X	0.5			2.2				2.7	LR	10.1	B	Br	III	M	F			
95	13.959	2.5	OR		0.6			2.2				2.8	LR	6.3	0.3	OGFC	I	L	F			
96	14.001	2.5	OL		0.4			2.1				2.5	LR	5.0	0.2	OGFC	I	L	F			
97	14.002	9.5	L2	X	0.5			2.9				3.4	LR	10.9	B	Br	I	L	F			
98	14.073	9.5	R1	X	0.6			3.3				3.9	LR	---	0.2	OGFC	I	L	F			
99	14.075	3.5	R2	X	0.5			2.7				3.2	LR	---	0.3	OGFC	I	L	F			
100	14.155	9.0	L1	X	0.7			3.2				3.9	LR	---	0.2	OGFC	I	L	F			
101	14.403	3.5	L2	X	0.5			2.7				3.2	LR	---	0.1	OGFC	I	L	F			
102	7.959	3.5	R2	X	0.6			7.7				8.3	LR	6.0	0.6	OGFC	II	M	F			