

**State of Florida Department of Transportation  
PAVEMENT EVALUATION AND CONDITION DATA SHEET**

Project No.:		430643-1		Cored By:		Ardaman		Date:		7/15/12-7/17/12		Page No.:											
County:		Marion		Highway Sect. No.:		36210		From:		North of SR 500 (US 27)		To:		Alachua County Line									
Road No.:		SR 93 (I-75)		Begin MP:		18.436		End MP:		38.282		Length:		19.846 Miles									
Core No.	MP	Distance from left edge of lane (ft.)	Lane	Wheel Path	Asphalt								Base		Crack				Pavt Cond.	Rut Depth (in)	Cross Slope (%)	Comments	
					FC-5	Type SP	TYPE-S	ARMI	TYPE-I	TYPE-II	BINDER	ST	Core Length (in)	Type	Thickness (in)	Depth (in)	Type	Class					Extent
1	18.636	9.5	R3	X	0.6		5.4		2.0		2.2		10.2	LR	11.3	---	---	---	---	G			
2	18.636	4.5	OR	---			4.3		1.1			0.6	6.0	LR	6.2	---	---	---	---	F			
3	18.786	2.5	L1	X	0.7		6.6						7.3	LR	12.7	---	---	---	---	G			
4	18.786	5.5	IL	---			1.9						1.9	LR	7.1	B	ST	II	L	F			
5	19.013	6.0	OL	---			4.0		1.0			0.5	5.5	LR	7.5	---	---	---	---	F			
6	19.013	9.5	L3	X	0.7		4.1		3.3		1.6		9.7	LR	12.5	---	---	---	---	G			
7	19.186	6.0	IR	---			2.3						2.3	LR	8.2	---	---	---	---	F			
8	19.186	3.0	R1	X	0.9		5.7						6.6	LR	14.4	---	---	---	---	G			
9	19.690	4.0	L1	X	0.8		6.5						7.3	LR	---	---	---	---	G				
10	19.690	4.0	IL	---			2.0						2.0	LR	---	---	---	---	F				
11	19.790	9.5	R3	X	0.8		5.0	0.4	2.2		2.4		10.8	LR	---	---	---	---	G				ARMI Layer Between Two Layers of Type S
12	19.790	5.0	OR	---			5.0		1.0			0.7	6.7	LR	---	---	---	---	F				
13	19.936	6.0	OL	---			6.6		0.7			0.8	8.1	LR	---	---	---	---	F				
14	19.936	10.0	L3	X	0.8		5.2	0.2	4.8		1.2		12.2	LR	---	---	---	---	G				
15	20.316	6.0	IR	---			1.5						1.5	LR	---	1.1	BR	I	L	F			
16	20.316	3.0	R1	X	0.7		5.3						6.0	LR	---	---	---	---	G				
17	21.306	2.5	L1	X	1.1		5.2						6.3	LR	---	---	---	---	G				
18	21.306	4.0	IL				1.8						1.8	LR	8.0	B	ST	II	L	F			
19	21.306	4.0	IR				1.9						1.9	LR	5.1	---	---	---	---	F			
20	21.306	3.0	R1	X	0.8		6.3						7.1	LR	---	---	---	---	G				
21	21.050	4.0	R3	X	0.6		3.4	0.2	2.5		1.6		8.3	LR	---	---	---	---	G				
22	21.050	8.0	OR				6.3						6.3	LR	13.0	0.1	BR	I	M	F			
23	21.136	7.0	OL				5.0					0.7	5.7	LR	7.2	---	---	---	---	F			
24	21.136	10.0	L3	X	0.8		2.5	0.5	1.4	1.0	2.0		8.2	LR	---	---	---	---	G				
25	22.050	5.0	L3		0.6		3.4	0.5	3.4		2.0		9.9	LR	11.1	---	---	---	---	G			
26	22.050	8.5	L1	X	1.2		5.1						6.3	LR	20.3	---	---	---	---	G			
27	22.000	10.0	R1	X	0.9		6.0						6.9	LR	14.5	---	---	---	---	G			
28	22.000	10.0	R3	X	0.8		3.6				1.5		5.9	LR	12.1	B	BR	III	M	P			
29	22.140	3.5	L3	X	0.5		4.0	0.5	3.5		1.5		10.0	LR	20.3	---	---	---	---	F			
30	22.140	2.5	L1	X	1.1		5.3						6.4	LR	14.6	---	---	---	---	G			
31	22.140	2.5	R1	X	0.9		5.9						6.8	LR	14.2	---	---	---	---	G			
32	22.140	2.0	R3	X	0.8		3.1		4.9		1.9		10.7	LR	12.8	---	---	---	---	G			Split core at 3.5"
33	22.786	4.0	L1	X	0.7		6.4						7.1	LR	---	---	---	---	G				
34	22.786	4.5	IL				2.2						2.2	LR	12.3	---	---	---	---	F			
35	22.850	10.0	R3	X	0.8		3.7	0.5	2.1		2.2		9.3	LR	---	---	---	---	G				
36	22.850	6.0	OR				4.3					0.6	4.9	LR	7.1	---	---	---	---	F			
37	23.086	4.0	OL				4.0		1.0			0.9	5.9	LR	6.5	1.7	BR	II	M	F			
38	23.086	9.5	L3	X	1.0		4.2	0.5	2.3		1.8		9.8	LR	---	---	---	---	G				
39	23.200	6.0	IR				1.2						1.2	LR	6.6	B	ST	II	F	F			
40	23.200	3.0	R1	X	0.6		6.2						6.8	LR	12.4	---	---	---	---	G			
41	24.136	3.0	L1	X	0.9		5.8						6.7	LR	12.5	---	---	---	---	G			

42	24.136	5.5	IL				1.2					1.2	LR	---	---	---	---	---	F			
43	24.150	4.0	R3	X	0.7		3.4	0.2	2.6		2.1		9.0	LR	12.4	2.3	BR	III	S	F		
44	24.150	6.0	OR				7.2						7.2	LR	---	0.1	BR	I	L	F		Horizontal crack at 1"
45	24.250	6.5	OL				7.3						7.3	LR	---	1.3	BR	II	M	F		Horizontal crack at 1.3"
46	24.250	10.0	L3	X	1.0	1.8	1.2	0.4	4.3				8.7	LR	11.6	---	---	---	---	G		
47	24.286	6.5	IR				1.1						1.1	LR	---	---	---	---	---	F		
48	24.286	3.0	R1	X	0.9		5.9						6.8	LR	14.7	---	---	---	---	G		Split core at 4.8"
49	24.586	4.0	OL				4.8		1.0		0.8		6.6	LR	7.4	2.9	BR	III	S	F		
50	24.586	4.0	L3	X	0.5		4.0	0.5	2.5		3.0		10.5	LR	---	4.1	BR	II	S	P		
51	24.850	6.5	IR				1.6						1.6	LR	10.4	---	---	---	---	F		
52	24.850	3.0	R1	X	1.0		6.2						7.2	LR	---	---	---	---	---	G		
53	25.150	4.0	L1	X	0.8		5.8						6.6	LR	---	---	---	---	---	G		
54	25.150	5.5	IL				1.4						1.4	LR	6.6	---	---	---	---	F		
55	25.200	9.0	R3	X	0.9		3.3		3.7		2.1		10.0	LR	---	4.1	ST	II	M	F		Horizontal crack at 4.1"
56	25.200	6.0	OR				6.3		1.4		0.5		8.2	LR	7.1	2.5	BR	II	M	F		
57	26.100	7.0	IR				1.7						1.7	LR	---	---	---	---	---	F		
58	26.100	3.0	R1	X	0.9		6.2						7.1	LR	13.9	---	---	---	---	G		
59	26.100	8.5	R3	X	0.8		3.0	0.4	3.4		2.5		10.1	LR	11.6	---	---	---	---	G		
60	26.100	6.0	OR				7.0						7.0	LR	---	1.2	SL	I	L	F		
61	26.200	5.0	OL				3.4				0.6		4.0	LR	---	2.1	SL	I	L	F		
62	26.200	9.0	L3	X	0.7		3.0	0.5	1.8		2.1		8.1	LR	11.9	---	---	---	---	G		
63	26.200	3.5	L1	X	0.8		6.4						7.2	LR	11.8	---	---	---	---	G		
64	26.200	6.0	IL				1.9						1.9	LR	---	---	---	---	---	F		
65	26.700	3.5	R3	X	0.9		4.3		3.7		2.1		11.0	LR	---	3.7	BR	III	S	F		
66	26.700	6.0	OR				4.6		1.0		0.7		6.3	LR	7.7	2.2	BR	II	M	F		
67	26.850	4.0	L1	X	0.5		6.0						6.5	LR	---	---	---	---	---	G		
68	26.850	5.5	IL				1.6						1.6	LR	7.9	---	---	---	---	F		
69	27.086	4.5	OL				4.8		1.0		0.6		6.4	LR	---	3.1	BR	II	M	F		
70	27.086	9.5	L3	X	0.2		4.5	0.3	3.0		2.0		10.0	LR	---	---	---	---		P		FC-5 Raveling/worn
71	27.236	6.5	IR				1.4						1.4	LR	6.1	---	---	---	---	F		
72	27.236	3.5	R1	X	1.0		6.1						7.1	LR	---	---	---	---	---	G		
73	27.836	9.5	L3	X	0.8		2.3	1.0	2.8		2.2		9.1	LR	11.7	---	---	---	---	G		
74	27.836	5.5	L1		0.8		5.9						6.7	LR	13.3	---	---	---	---	G		
75	27.836	3.5	R1	X	1.0		5.9						6.9	LR	13.9	---	---	---	---	G		
76	27.836	9.5	R3	X	0.8		3.1	0.4			2.7		7.0	LR	13.1	---	---	---	---	G		
77	27.950	9.5	L3	X	1.1		8.6						9.7	LR	11.8	---	---	---	---	G		
78	27.950	3.5	L1	X	1.0		5.6						6.6	LR	13.4	---	---	---	---	G		
79	27.950	5.0	R1		0.9		5.7						6.6	LR	13.9	---	---	---	---	G		
80	27.950	9.0	R3	X	0.7		3.3	0.5	2.4		1.0		7.9	LR	13.6	---	---	---	---	G		
81	29.200	3.5	L1	X	0.7		5.7						6.4	LR	---	---	---	---	---	G		
82	29.200	6.0	IL				1.5						1.5	LR	6.3	---	---	---	---	F		
83	29.236	9.0	R3	X	0.7		3.4	0.2	4.3		1.9		10.5	LR	---	3.9	BR	III	S	F		Horizontal crack at 6.5"
84	29.236	6.5	OR				5.5		1.0		0.5		7.0	LR	8.0	2.6	ST	II	L	F		
85	29.336	6.0	OL				5.1		0.8		0.8		6.7	LR	---	---	---	---	---	F		
86	29.336	9.5	L3	X	1.1		3.5	0.4	4.2		1.8		11.0	LR	---	---	---	---	---	G		
87	29.336	4.0	IR				1.6						1.6	LR	6.9	---	---	---	---	F		
88	29.336	5.0	R1		1.0		7.0						8.0	LR	---	---	---	---	---	G		
89	29.686	3.5	L1	X	1.0		5.2						6.2	LR	12.8	---	---	---	---	F		
90	29.686	6.0	IL				1.5						1.5	LR	0.0	---	---	---	---	F		
91	29.786	7.0	OL				4.3		0.9		0.8		6.0	LR	---	1.8	SL	I	L	F		
92	29.786	10.0	L3	X	0.8		2.7	1.0	2.5		2.5		9.5	LR	11.6	3.0	BR	III	S	F		
93	29.886	9.0	R3	X	0.6		7.4						8.0	LR	11.7	---	---	---	---	G		
94	29.886	7.0	OR				7.0		0.8		0.6		8.4	LR	---	---	---	---	---	F		
95	30.100	6.0	IR				1.5						1.5	LR	---	---	---	---	---	F		
96	30.100	3.0	R1	X	0.8		5.9						6.7	LR	13.3	---	---	---	---	G		
97	30.900	3.0	L1	X	0.8		6.0						6.8	LR	---	---	---	---	---	G		
98	30.900	8.0	IL				1.3						1.3	LR	5.0	---	---	---	---	F		
99	30.900	10.0	R3	X	0.7	1.8	2.5		2.5		1.9		9.4	LR	---	2.9	BR	II	M	F		
100	30.900	5.5	OR				6.0		1.4				7.4	LR	6.3	5.0	ST	II	L	F		
101	31.250	5.5	OL				4.2		1.0		0.6		5.8	LR	5.7	---	---	---	---	F		Horizontal crack at 2.5"
102	31.250	4.0	L3	X	0.8		9.5						10.3	LR	---	4.0	BR	II	S	F		Horizontal crack at 4"

103	31.300	6.5	IR				1.4					1.4	LR	6.1	---	---	---	---	F			
104	31.300	3.0	R1	X	0.7		6.1					6.8	LR	---	---	---	---	G				
105	31.590	5.0	OL				5.0		1.0		0.5	6.5	LR	---	---	---	---	F				
106	31.590	10.0	L3	X	0.9		9.0	0.4			1.3	11.6	LR	---	4.6	SL	II	M	F			
107	32.250	10.0	L3	X	0.9		4.6	0.5	1.0		2.7	9.7	LR	12.6	---	---	---	G				
108	32.250	5.5	L1		0.8		6.0					6.8	LR	13.3	---	---	---	G				
109	32.250	6.0	R1		1.0		6.5					7.5	LR	14.8	---	---	---	G				
110	32.250	9.0	R3	X	1.0		8.8	0.2				10.0	LR	11.4	---	---	---	G				
111	32.400	9.0	L3		0.8		7.7					8.5	LR	12.6	6.0	BR	II	M	P			
112	32.400	3.5	L1	X	0.8		6.1					6.9	LR	13.4	---	---	---	G				
113	32.400	2.5	R1	X	0.7		5.9					6.6	LR	15.2	---	---	---	G				
114	32.400	9.5	R3	X	1.0		4.4		2.6		1.2	9.2	LR	13.4	---	---	---	G				
115	32.800	6.0	IR				1.7					1.7	LR	7.3	---	---	---	F				
116	32.800	3.5	R1	X	0.8		5.5					6.3	LR	---	---	---	---	G				
117	32.936	3.5	L1	X	1.0		6.0					7.0	LR	---	---	---	---	F				
118	32.936	5.5	IL				1.6					1.6	LR	6.4	---	---	---	F				
119	33.136	6.0	OL				4.2		0.9		0.7	5.8	LR	8.5	---	---	---	F				
120	33.136	10.0	L3	X	0.6		3.3	0.2	2.4		2.1	8.6	LR	---	---	---	---	F				
121	33.136	9.5	R3	X	1.0		3.8	0.2	2.8		2.0	9.8	LR	---	---	---	---	F				
122	33.136	7.0	OR				4.5		1.0		0.7	6.2	LR	8.1	---	---	---	F				
123	34.036	9.0	R3	X	0.8		7.2	0.5				8.5	LR	---	---	---	---	G				ARMI Layer Between Two Layers of Type S
124	34.036	6.5	OR				3.0		1.0		0.7	4.7	LR	---	---	---	---	G				
125	34.060	3.5	L1	X	0.8		6.5					7.3	LR	13.1	---	---	---	G				
126	34.060	7.0	OL				3.2		1.0		0.9	5.1	LR	---	---	---	---	F				
127	34.186	6.5	IR				7.2					7.2	LR	---	---	---	---	F				
128	34.186	3.5	R1	X	0.8		5.9					6.7	LR	14.3	---	---	---	G				
129	34.250	7.0	OL				3.0		0.9		0.9	4.8	LR	---	---	---	---	F				
130	34.250	9.5	L3	X	0.7		2.7	0.5	3.4		2.1	9.4	LR	12.1	---	---	---	G				
131	35.236	3.0	L1	X	0.8		5.9					6.7	LR	---	---	---	---	G				
132	35.236	4.5	IL				1.5					1.5	LR	4.5	---	---	---	F				
133	35.236	9.0	R3	X	0.9		6.0	0.3			2.0	9.2	LR	---	---	---	---	G				ARMI Layer Between Two Layers of Type S
134	35.236	6.5	OR				4.5		1.0		0.6	6.1	LR	8.2	---	---	---	F				
135	35.336	6.0	OL				4.8		1.1		0.8	6.7	LR	7.5	---	---	---	F				
136	35.336	8.0	L3		0.9		8.9					9.8	LR	---	---	---	---	G				
137	35.336	5.0	IR				1.4					1.4	LR	7.6	---	---	---	F				
138	35.336	3.0	R1	X	0.6		5.9					6.5	LR	---	---	---	---	G				
139	35.736	4.0	L1	X	0.6		6.0					6.6	LR	19.0	---	---	---	G				
140	35.736	5.5	IL				1.5					1.5	LR	---	---	---	---	F				
141	35.736	9.5	R3	X	0.8		3.2	0.2	4.3		2.0	10.5	LR	11.5	---	---	---	G				
142	35.736	6.0	OR				5.9		1.3		0.6	7.8	LR	---	---	---	---	F				Horizontal crack at 1.0"
143	36.100	7.0	OL				4.0		1.0		0.5	5.5	LR	---	---	---	---	F				
144	36.100	9.0	L3	X	0.7		2.9		3.2		2.0	8.8	LR	11.7	---	---	---	G				
145	36.200	6.0	IR				1.6					1.6	LR	---	---	---	---	F				
146	36.200	3.5	R1	X	0.8		6.5					7.3	LR	12.2	---	---	---	G				
147	36.650	5.5	OL				4.1		1.0		0.5	5.6	LR	8.8	2.4	BR	I	L	F			
148	36.650	9.0	L3	X	0.7		3.7	0.3	3.5		1.7	9.9	LR	---	---	---	---	G				
149	36.950	6.0	IR				1.5					1.5	LR	7.8	B	SL	II	L	F			
150	36.950	3.5	R1	X	0.7		6.4					7.1	LR	---	---	---	---	G				
151	37.186	3.0	L1	X	0.7		5.8					6.5	LR	---	---	---	---	G				
152	37.186	7.0	IL				1.4					1.4	LR	6.4	---	---	---	F				
153	37.297	5.5	R3		0.7		6.0		2.4		1.9	11.0	LR	---	---	---	---	G				Horizontal crack at 2"
154	37.297	7.0	OR				4.0		1.8		0.7	6.5	LR	7.5	1.7	BR	II	M	F			
155	37.686	6.5	OL				4.5		1.2		0.6	6.3	LR	---	1.5	BR	II	S	P			
156	37.686	9.5	L3	X	1.1		2.8	0.5	3.2		1.9	9.5	LR	11.6	---	---	---	G				
157	37.800	6.0	IR				1.8					1.8	LR	---	---	---	---	F				
158	37.800	3.0	R1	X	1.1		6.5					7.6	LR	12.4	---	---	---	G				
159	38.100	2.5	L1	X	0.7		6.9					7.6	LR	12.6	---	---	---	G				
160	38.100	5.5	IL				1.8					1.8	LR	---	---	---	---	F				
161	38.100	9.5	R3	X	0.7		8.8					9.5	LR	11.5	---	---	---	F				
162	38.100	6.5	OR	---			5.8		1.3		0.5	7.6	LR	---	1.5	BR	II	M	P			
163	528'	13.0	Ramp	X	0.9		2.6		1.5		2.1	7.1	LR	10.2	---	---	---	F				Ramp 024: I-75 NB to SR 326 from Gore
164	528'	3.0	OR	---	0.5		6.9					7.4	LR	7.6	---	---	---	F				Ramp 024: I-75 NB to SR 326 from Gore
165	1056'	13.0	Ramp	X	0.6		3.5					4.1	LR	17.4	---	---	---	G				Ramp 025: I-75 SB to SR 326 from Gore
166	1056'	1.0	OR	---	0.3		2.3					2.6	LR	4.9	---	---	---	F				Ramp 025: I-75 SB to SR 326 from Gore
167	750'	13.5	Ramp	X	0.7	1.8	2.8					5.3	LR	12.0	---	---	---	F				Ramp 027: CR 318 to I-75 SB from Gore
168	750'	1.0	OR	---	0.8	2.0	0.8					3.6	LR	11.9	---	---	---	F				Ramp 027: CR 318 to I-75 SB from Gore
169	750'	14.0	Ramp	X	0.5		1.3		2.6		2.1	6.5	LR	11.5	---	---	---	F				Ramp 028: I-75 NB to CR 318 from Gore
170	750'	1.5	OR	---	0.8		0.7					1.5	LR	11.3	---	---	---	F				Ramp 028: I-75 NB to CR 318 from Gore
171	750'	14.0	Ramp	X	0.6	2.5			2.4		1.9	7.4	LR	10.4	---	---	---	F				Ramp 029: I-75 SB to CR 318 from Gore
172	750'	1.5	OR		0.6		2.2					2.8	LR	11.5				F				Ramp 029: I 75 SB to CR 318 from Gore



## Supplemental Data to PECD

(GPS Coordinates for Each Locations Cored)

SR 93 FPN: 430643-1 County: Marion

Core #	GPS Coordinates	
1	N 29.218795	W -82.184295
2	N 29.218816	W -82.184286
3	N 29.220545	W -82.184520
4	N 29.220545	W -82.184520
5	N 29.222780	W -82.184626
6	N 29.222792	W -82.184626
7	N 29.226065	W -82.184854
8	N 29.226070	W -82.184824
9	N 29.232783	W -82.189144
10	N 29.232789	W -82.189148
11	N 29.233583	W -82.189261
12	N 29.233603	W -82.189230
13	N 29.235141	W -82.190096
14	N 29.235140	W -82.190032
15	N 29.241453	W -82.189876
16	N 29.241448	W -82.189878
17	N 29.256119	W -82.189834
18	N 29.256125	W -82.189834
19	N 29.255790	W -82.189808
20	N 29.255801	W -82.189807

Core #	GPS Coordinates	
21	N 29.252760	W -82.189666
22	N 29.252768	W -82.189667
23	N 29.252797	W -82.189637
24	N 29.252566	W -82.190031
25	N 29.252575	W -82.190029
26	N 29.265456	W -82.192720
27	N 29.265585	W -82.192733
28	N 29.265571	W -82.192497
29	N 29.266354	W -82.192737
30	N 29.268908	W -82.193889
31	N 29.267485	W -82.193205
32	N 29.268292	W -82.193399
33	N 29.275846	W -82.196424
34	N 29.275846	W -82.196425
35	N 29.278088	W -82.196968
36	N 29.278036	W -82.196907
37	N 29.279794	W -82.197953
38	N 29.279799	W -82.197953
39	N 29.282148	W -82.198541
40	N 29.282148	W -82.198541

## Supplemental Data to PECD

(GPS Coordinates for Each Locations Cored)

SR 93 FPN: 430643-1 County: Marion

Core #	GPS Coordinates	
41	N 29.218795	W -82.184295
42	N 29.218816	W -82.184286
43	N 29.220545	W -82.184520
44	N 29.220545	W -82.184520
45	N 29.222780	W -82.184626
46	N 29.222792	W -82.184626
47	N 29.226065	W -82.184854
48	N 29.226070	W -82.184824
49	N 29.232783	W -82.189144
50	N 29.232789	W -82.189148
51	N 29.233583	W -82.189261
52	N 29.233603	W -82.189230
53	N 29.235141	W -82.190096
54	N 29.235140	W -82.190032
55	N 29.241453	W -82.189876
56	N 29.241448	W -82.189878
57	N 29.256119	W -82.189834
58	N 29.256125	W -82.189834
59	N 29.255790	W -82.189808
60	N 29.255801	W -82.189807

Core #	GPS Coordinates	
61	N 29.252760	W -82.189666
62	N 29.252768	W -82.189667
63	N 29.252797	W -82.189637
64	N 29.252566	W -82.190031
65	N 29.252575	W -82.190029
66	N 29.265456	W -82.192720
67	N 29.265585	W -82.192733
68	N 29.265571	W -82.192497
69	N 29.266354	W -82.192737
70	N 29.268908	W -82.193889
71	N 29.267485	W -82.193205
72	N 29.268292	W -82.193399
73	N 29.275846	W -82.196424
74	N 29.275846	W -82.196425
75	N 29.278088	W -82.196968
76	N 29.278036	W -82.196907
77	N 29.279794	W -82.197953
78	N 29.279799	W -82.197953
79	N 29.282148	W -82.198541
80	N 29.282148	W -82.198541

## Supplemental Data to PECD

(GPS Coordinates for Each Locations Cored)

SR 93 FPN: 430643-1 County: Marion

Core #	GPS Coordinates	
81	N 29.218795	W -82.184295
82	N 29.218816	W -82.184286
83	N 29.220545	W -82.184520
84	N 29.220545	W -82.184520
85	N 29.222780	W -82.184626
86	N 29.222792	W -82.184626
87	N 29.226065	W -82.184854
88	N 29.226070	W -82.184824
89	N 29.232783	W -82.189144
90	N 29.232789	W -82.189148
91	N 29.233583	W -82.189261
92	N 29.233603	W -82.189230
93	N 29.235141	W -82.190096
94	N 29.235140	W -82.190032
95	N 29.241453	W -82.189876
96	N 29.241448	W -82.189878
97	N 29.256119	W -82.189834
98	N 29.256125	W -82.189834
99	N 29.255790	W -82.189808
100	N 29.255801	W -82.189807

Core #	GPS Coordinates	
101	N 29.252760	W -82.189666
102	N 29.252768	W -82.189667
103	N 29.252797	W -82.189637
104	N 29.252566	W -82.190031
105	N 29.252575	W -82.190029
106	N 29.265456	W -82.192720
107	N 29.265585	W -82.192733
108	N 29.265571	W -82.192497
109	N 29.266354	W -82.192737
110	N 29.268908	W -82.193889
111	N 29.267485	W -82.193205
112	N 29.268292	W -82.193399
113	N 29.275846	W -82.196424
114	N 29.275846	W -82.196425
115	N 29.278088	W -82.196968
116	N 29.278036	W -82.196907
117	N 29.279794	W -82.197953
118	N 29.279799	W -82.197953
119	N 29.282148	W -82.198541
120	N 29.282148	W -82.198541

## Supplemental Data to PECD

(GPS Coordinates for Each Locations Cored)

SR 93 FPN: 430643-1 County: Marion

Core #	GPS Coordinates	
121	N 29.218795	W -82.184295
122	N 29.218816	W -82.184286
123	N 29.220545	W -82.184520
124	N 29.220545	W -82.184520
125	N 29.222780	W -82.184626
126	N 29.222792	W -82.184626
127	N 29.226065	W -82.184854
128	N 29.226070	W -82.184824
129	N 29.232783	W -82.189144
130	N 29.232789	W -82.189148
131	N 29.233583	W -82.189261
132	N 29.233603	W -82.189230
133	N 29.235141	W -82.190096
134	N 29.235140	W -82.190032
135	N 29.241453	W -82.189876
136	N 29.241448	W -82.189878
137	N 29.256119	W -82.189834
138	N 29.256125	W -82.189834
139	N 29.255790	W -82.189808
140	N 29.255801	W -82.189807

Core #	GPS Coordinates	
141	N 29.252760	W -82.189666
142	N 29.252768	W -82.189667
143	N 29.252797	W -82.189637
144	N 29.252566	W -82.190031
145	N 29.252575	W -82.190029
146	N 29.265456	W -82.192720
147	N 29.265585	W -82.192733
148	N 29.265571	W -82.192497
149	N 29.266354	W -82.192737
150	N 29.268908	W -82.193889
151	N 29.267485	W -82.193205
152	N 29.268292	W -82.193399
153	N 29.275846	W -82.196424
154	N 29.275846	W -82.196425
155	N 29.278088	W -82.196968
156	N 29.278036	W -82.196907
157	N 29.279794	W -82.197953
158	N 29.279799	W -82.197953
159	N 29.282148	W -82.198541
160	N 29.282148	W -82.198541



