

State of Florida Department of Transportation
PAVEMENT EVALUATION AND CONDITION DATA SHEET

Project No.: 433655-1		Cored By: Elipsis Engineering and Consulting				Date: November 3, 2016				Page No.: 1 of 1												
County: Brevard		Highway Sect. No.: 70050				From: Just West of Hollywood Blvd				To: Just East of Hollywood Blvd												
Road No.: SR 500		Begin MP: 13.033				End MP: 13.035				Length: 0.002												
Core No.	MP	Distance from left edge of lane (ft)	Lane	Wheel Path	Pavement Layer (in.)					Core Length (in)	Base		Crack				Pavt Cond.	Rut Depth (in)	Cross Slope (%)	Comments		
					FC-2	FC-9.5	FC-12.5	Type SP	Type S		Type	Thickness (in)	Depth (in)	Type	Class	Extent						
1	12.993	2.5	RLTL-1	X		1.2		1.6	1.5		10.5	ABC	6.2	-	-	-	-	F		EB SR 500 to NB Evans Rd.		
2	13.056	8.0	R1			1.0		1.5	0.7		3.2	LR	8.6	-	-	-	-	F		EB SR 500		
3	13.057	3.0	LLTL	X		1.0		1.2	0.9		3.1	LR	9.8	-	-	-	-	F		WB SR 500 to SB Hollywood Blvd		
4	*	8.0	RRTL				1.7	2.1	0.7		11.6	ABC	7.1	-	-	-	-	G		NB Hollywood Blvd to EB SR 500 ; ~130' S of SR 500 Note: 2.9 inches of LR under ABC		
5	*	4.0	R2		0.4				1.3		1.7	LR	11.1	B	A1	III	S	P		NB Evans Rd ; ~243' N of SR 500		
6	*	8.0	L2		0.3				1.9		2.2	LR	9.8	B	Br	II	S	P		SB Evans Rd ; ~524' N of SR 500		
7	*	9.0	LRTL	X	0.2				1.5		1.7	LR	8.8	B	Br	III	S	P		SB Evans Rd to WB SR 500 ; ~185' N of SR 500		
8	*	2.5	L1	X			1.1	3.4	2.5		7.0	LR	16.5	-	-	-	-	F		SB Hollywood Blvd ; ~116' S of SR 500		

Remarks: Crack Depth of "B" indicates full depth crack to the base. EOP = Edge of Pavement * = Approximate Location, refer to Aerial View for a more accurate location
Crack Extent: L= Light; M= Moderate; S= Severe **Pavement Condition:** G= Good; F= Fair; P= Poor **Crack Types:** A= Alligator; B1= Block; Br= Branch
SL= Single Longitudinal; **ST=** Single Transverse; **R=** Reflective; **J=** Joint; **OGFC=** Open-Graded FC Stress Crack
Base Types: LR= Limerock; COQ= Coquina; SC= Soil Cement; ABC= Asphalt Base; SAHM= Sand Asphalt Hot Mix; NB= No Base