

State of Florida Department of Transportation
PAVEMENT EVALUATION AND CONDITION DATA SHEET

Project No.: 239203-4	Cored By: F. Shaw & P. Gatewood	Date: 2/5/01	Page No.: 1 of 13
County: Orange	Highway Sect. No: 75060	From: CR 425 (Dean Road)	To: East of Old Cheney Hwy.
Road No.: SR 50	Begin M.P.: 9.445	End M.P.: 14.645	Length: 5.200

Core No.	MP	Distance from left edge of lane (ft)	Lane	Wheel Path	Pavement Layer (in)										Crack				Pavt. Cond.	Rut Depth (in)	Cross Slope	Comments
					FC-6	FC-5	Type S	Type I	Type III	ST	Binder	Core Length (in)	Base Type	Base Thick (in)	Depth (in)	Type	Class	Extent				
2	9.509	6	R2		1.8		0.9	0.9		0.5		4.1	L/R	9.3	--	--	--	--	G			
4	9.795	3	R2	X	1.5		1.3	1.8	0.4	0.5		5.5	L/R	--	--	--	--	--	G			
9	10.203	9	R2	X	1.3		1.4	0.8	0.5	0.6		4.6	L/R	--	--	--	--	--	G			
11	10.500	6	R2		1.3		1.5	1.1				3.9	L/R	10.1	--	--	--	--	G			
13	10.806	9	R2	X	1.6		1.0	1.7				4.3	L/R	--	--	--	--	--	G			
17	11.155	3	R2	X	1.5		1.2	1.9				4.6	L/R	--	--	--	--	--	G			
21	11.510	6	R2		1.3		1.1	1.5		0.6		4.5	L/R	9.5	--	--	--	--	G			
24	11.814	9	R2	X		1.0	2.5					3.5	L/R	--	--	--	--	--	G			
30	12.201	3	R2	X		0.8	1.7	1.6				4.1	L/R	--	--	--	--	--	G			
35	12.501	6	R2			0.8	3.2					4.0	L/R	10.3	--	--	--	--	G			
37	12.827	9	R2	X		0.9	1.9	2.1	0.2	0.6		5.7	L/R	--	--	--	--	--	G			
41	13.231	9	R2	X		0.8	1.8	1.4	0.2	0.6		4.8	L/R	--	--	--	--	--	G			
44	13.501	3	R2	X		0.9	1.4	1.8	0.2	0.5		4.8	L/R	10.2	--	--	--	--	G			
45	13.786	6	R2			1.0	3.9		0.9	0.6		6.4	L/R	--	--	--	--	--	G			
49	14.201	3	R2	X		1.2	2.1	1.2	0.1	0.6		5.2	L/R	--	--	--	--	--	G			
51	14.421	9	R2	X		1.1	2.2	2.1	0.9	0.5		6.8	L/R	12.1	--	--	--	--	G			

Remarks: Mainline
Friction Course changes from FC-6 West of SR 434 to FC-5 East of SR 434

State of Florida Department of Transportation
PAVEMENT EVALUATION AND CONDITION DATA SHEET

Project No.: 239203-4	Cored By: F. Shaw & P. Gatewood	Date: 2/5/01	Page No.: 2 of 13
County: Orange	Highway Sect. No: 75060	From: CR 425 (Dean Road)	To: East of Old Cheney Hwy.
Road No.: SR 50	Begin M.P.: 9.445	End M.P.: 14.645	Length: 5.200

Core No.	MP	Distance from left edge of lane (ft)	Lane	Wheel Path	Pavement Layer (in)										Crack				Pavt. Cond.	Rut Depth (in)	Cross Slope	Comments	
					FC-6	FC-5	Type S	Type I	Type III	ST	Binder	Core Length (in)	Base Type	Base Thick (in)	Depth (in)	Type	Class	Extent					
53	14.642	3	R2	X	1.0		3.8		0.2	0.7		5.7	L/R	--	--	--	--	--	G				
94	9.498	6	R1		1.7		1.3	2.3	0.8	0.6		6.7	L/R	10.6	--	--	--	--	G				
92	9.530	9	R1	X	1.7		3.1					4.8	L/R	--	--	--	--	--	G				
98	9.912	9	R1	X	1.9		3.3					5.2	L/R	--	--	--	--	--	G				
101	10.280	3	R1	X	1.5		1.0	1.8	1.1	0.6		6.0	L/R	--	--	--	--	--	G				
104	10.586	6	R1		1.5		1.3	2.3	1.2	0.5		6.8	L/R	10.3	--	--	--	--	G				
107	10.885	9	R1	X	1.5		1.2	1.6	1.3	0.6		6.2	L/R	--	--	--	--	--	G				
111	11.289	3	R1	X	1.5		1.5	3.3	1.5	0.6		8.4	L/R	--	--	--	--	--	G				
114	11.602	6	R1		1.8		1.0	1.1	1.0	0.5		5.4	L/R	11.4	--	--	--	--	G				
118	11.902	9	R1	X		0.6	1.3	1.7	1.2	0.7		5.5	L/R	--	--	--	--	--	G				
121	12.303	3	R1	X		1.2	3.2	1.5	1.9	0.5		8.3	L/R	8.9	--	--	--	--	G				
123	12.603	6	R1			1.2	1.9	2.5				5.6	L/R	--	--	--	--	--	G				
124	12.902	9	R1	X		1.1	2.2	2.0	1.1	0.7		7.1	L/R	--	--	--	--	--	G				
127	13.324	3	R1	X		1.1	3.7	1.9	1.5	0.5		8.7	L/R	7.9	--	--	--	--	G				
130	13.634	3	R1	X		0.9	3.4	2.6	1.5	0.6		9.0	L/R	--	--	--	--	--	G				
132	13.891	9	R1	X		1.2	1.8	1.9	1.3	0.6		6.8	L/R	--	--	--	--	--	G				

Remarks: Mainline
Friction Course changes from FC-6 West of SR 434 to FC-5 East of SR 434

State of Florida Department of Transportation
PAVEMENT EVALUATION AND CONDITION DATA SHEET

Project No.: 239203-4				Cored By: F. Shaw & P. Gatewood				Date: 2/5/01				Page No.: 3 of 13											
County: Orange				Highway Sect. No: 75060				From: CR 425 (Dean Road)				To: East of Old Cheney Hwy.											
Road No.: SR 50				Begin M.P.: 9.445				End M.P.: 14.645				Length: 5.200											
Core No.	MP	Distance from left edge of lane (ft)	Lane	Wheel Path	Pavement Layer (in)										Crack				Pavt. Cond.	Rut Depth (in)	Cross Slope	Comments	
					FC-6	FC-5	Type S	Type I	Type III	ST	Binder	Core Length (in)	Base Type	Base Thick (in)	Depth (in)	Type	Class	Extent					
136	14.290	3	R1	X		0.9	3.5	3.7	1.6	0.6		10.3	L/R	7.9	--	--	--	--	G				
139	14.640	6	R1			1.2	2.0	3.1	1.4	0.5		8.2	L/R	--	--	--	--	--	G				
140	14.619	6	L1			0.9	4.4					5.3	L/R	11.7	--	--	--	--	G				
141	14.365	9	L1	X		1.0	2.3				2.0	5.3	L/R	--	--	--	--	--	G				
142	14.195	3	L1	X		0.7	3.4				1.0	5.1	L/R	--	--	--	--	--	G				
145	13.836	3	L1	X		0.8	3.2				1.1	5.1	L/R	12.1	--	--	--	--	G				
146	13.491	6	L1			1.1	2.0				1.5	4.6	L/R	--	--	--	--	--	G				
149	13.209	9	L1	X		1.0	3.7			0.7		5.4	L/R	--	--	--	--	--	G				
152	12.807	3	L1	X		0.9	4.0				1.9	6.8	L/R	10.9	--	--	--	--	G				
154	12.534	6	L1			1.0	2.0	1.7			0.6	5.3	L/R	--	--	--	--	--	G				
157	12.205	9	L1	X		1.0	3.6					4.6	L/R	--	--	--	--	--	G				
163	11.769	6	L1			0.7	1.2	3.1				5.0	L/R	10.1	--	--	--	--	G				
165	11.526	3	L1	X	1.5		1.4				2.0	4.9	L/R	--	--	--	--	--	G				
168	11.205	9	L1	X	1.7		1.2	0.9			1.2	5.0	L/R	--	--	--	--	--	G				
171	10.791	6	L1		1.6		1.3	1.2			0.7	4.8	L/R	11.5	--	--	--	--	G				
175	10.466	3	L1	X	1.7		1.5				0.9	4.1	L/R	--	--	--	--	--	G				

Remarks: Mainline
Friction Course changes from FC-6 West of SR 434 to FC-5 East of SR 434

State of Florida Department of Transportation
PAVEMENT EVALUATION AND CONDITION DATA SHEET

Project No.: 239203-4	Cored By: F. Shaw & P. Gatewood	Date: 2/5/01	Page No.: 4 of 13
County: Orange	Highway Sect. No: 75060	From: CR 425 (Dean Road)	To: East of Old Cheney Hwy.
Road No.: SR 50	Begin M.P.: 9.445	End M.P.: 14.645	Length: 5.200

Core No.	MP	Distance from left edge of lane (ft)	Lane	Wheel Path	Pavement Layer (in)										Crack				Pavl. Cond.	Ret Depth (in)	Cross Slope	Comments
					FC-6	FC-5	Type S	Type I	Type III	ST	Binder	Core Length (in)	Base Type	Base Thick (in)	Depth (in)	Type	Class	Extent				
178	10.179	6	L1		2.0		1.6	1.1				4.7	L/R	12.6	--	--	--	--	G			
181	9.798	3	L1	X	1.7		1.3	1.7				4.7	L/R	--	--	--	--	--	G			
185	9.743	6	L1		1.7		1.0	1.4				4.1	L/R	--	--	--	--	--	G			
54	14.629	3	L2	X	1.0		2.9				1.4	5.3	L/R	12.7	--	--	--	--	G			
55	14.304	6	L2		1.2		3.1					4.3	L/R	--	--	--	--	--	G			
56	13.899	9	L2	X	1.0		1.9				1.5	4.4	L/R	--	--	--	--	--	G			
60	13.603	6	L2		1.2		3.5					4.7	L/R	12.3	--	--	--	--	G			
62	13.299	3	L2	X	0.9		1.7	1.0			1.5	5.1	L/R	--	--	--	--	--	G			
63	12.925	9	L2	X	0.8		3.6					4.4	L/R	--	--	--	--	--	G			
67	12.602	6	L2		1.0		4.6					5.6	L/R	8.4	--	--	--	--	G			
68	12.312	3	L2	X	1.3		2.9				1.2	5.4	L/R	--	--	--	--	--	G			
72	11.954	9	L2	X	1.0		2.1				1.7	4.8	L/R	--	--	--	--	--	G			
79	11.909	9	L2	X		1.6	3.3					4.9	L/R	--	--	--	--	--	G			
76	11.621	6	L2			1.3	2.4				0.9	4.6	L/R	11.9	--	--	--	--	G			
78	11.297	3	L2	X		1.5	2.4				1.2	5.1	L/R	--	--	--	--	--	G			
83	10.602	6	L2			1.7	2.2					3.9	L/R	8.7	--	--	--	--	G			

Remarks: Mainline
Friction Course changes from FC-6 West of SR 434 to FC-5 East of SR 434

State of Florida Department of Transportation PAVEMENT EVALUATION AND CONDITION DATA SHEET

Project No.: 239203-4	Cored By: F. Shaw & P. Gatewood	Date: 2/5/01	Page No.: 5 of 13
County: Orange	Highway Sect. No: 75060	From: CR 425 (Dean Road)	To: East of Old Cheney Hwy.
Road No.: SR 50	Begin M.P.: 9.445	End M.P.: 14.645	Length: 5.200

Core No.	MP	Distance from left edge of lane (ft)	Lane	Wheel Path	Pavement Layer (in)										Crack				Pavt. Cond.	Rut Depth (in)	Cross Slope	Comments				
					FC-6	FC-5	Type S	Type I	Type III	ST	Binder	Core Length (in)	Base Type	Base Thick (in)	Depth (in)	Type	Class	Extent								
86	10.293	3	L2	X		1.5	1.3					1.6	4.4	L/R	--	--	--	--	--	G						
89	9.891	9	L2	X		2.0	3.4						5.4	L/R	--	--	--	--	--	G						
91	9.713	6	L2		2.1		2.4						4.5	L/R	10.2	--	--	--	--	G						

Remarks: Mainline
Friction Course changes from FC-6 West of SR 434 to FC-5 East of SR 434

State of Florida Department of Transportation
PAVEMENT EVALUATION AND CONDITION DATA SHEET

Project No.: 239203-4				Cored By: F. Shaw & P. Gatewood				Date: 2/5/01				Page No.: 6 of 13												
County: Orange				Highway Sect. No: 75060				From: CR 425 (Dean Road)				To: East of Old Cheney Hwy.												
Road No.: SR 50				Begin M.P.: 9.445				End M.P.: 14.645				Length: 5.200												
Core No.	MP	Distance from left edge of lane (ft)	Lane	Wheel Path	Pavement Layer (in)										Crack				Pavt. Cond.	Rut Depth (in)	Cross Slope	Comments		
					FC-6	FC-5	Type S	Type I	Type III	ST	Blnder	Core Length (in)	Base Type	Base Thick (in)	Depth (in)	Type	Class	Extent						
95	9.569	6	RLTL		1.8		4.7						13.7	ABC3	7.2	--	--	--	--	G				To Gator Tire
96	9.716	9	RLTL	X	1.6		5.4						12.7	ABC3	5.7	--	--	--	--	G				To U turns
97	9.900	3	RLTL	X	1.8		3.1						4.9	L/R	8.3	--	--	--	--	G				To Culver Rd.
99	10.015	6	RLTL		1.4		4.7						10.6	ABC3	4.5	--	--	--	--	G				To Vincent Rd.
100	10.148	9	RLTL	X	1.5		2.1						3.6	L/R	10.4	--	--	--	--	G				To Murdock Blvd.
102	10.280	9	RLTL	X	1.1		1.5						2.6	COQ	6.2	--	--	--	--	G				To Alamo Shopping Ctr.
103	10.380	3	RLTL	X	1.6		1.2						2.8	COQ	10.4	--	--	--	--	G				To Alamo Shopping Ctr.
105	10.602	6	RLTL		1.6		3.0						4.6	L/R	11.1	--	--	--	--	G				To Autozone
106	10.694	3	RLTL	X	1.5		6.0						13.2	ABC3	5.7	--	--	--	--	G				To Rouse Rd.
108	10.918	9	RLTL	X	1.2		3.5						4.7	L/R	11.5	--	--	--	--	G				To Pinewood Mobile Home Park
109	11.106	6	RLTL		1.4		3.1						4.5	L/R	12.5	--	--	--	--	G				To Rouse Lake Rd.
110	11.289	9	RLTL	X	1.2		6.1						10.8	ABC3	3.5	--	--	--	--	G				To U turns
112	11.435	3	RLTL	X	1.0		4.9						12.4	ABC3	6.5	--	--	--	--	G				To Hedlightz
113	11.561	6	RLTL		1.7		5.5						13.2	ABC3	6.0	--	--	--	--	G				To Pays Inn
116	11.676	3	RRLTL	X	1.3		1.5	1.7	1.2	0.6			6.3	L/R	11.4	--	--	--	--	G				To SR 434
162	11.816	3	LRLTL	X		0.9	6.2						13.1	ABC3	6.0	--	--	--	--	G				To SR 434

Remarks: Auxiliary Lanes
Friction Course changes from FC-6 West of SR 434 to FC-5 East of SR 434

State of Florida Department of Transportation
PAVEMENT EVALUATION AND CONDITION DATA SHEET

Project No.: 239203-4	Cored By: F. Shaw & P. Gatewood	Date: 2/5/01	Page No.: 7 of 13
County: Orange	Highway Sect. No: 75060	From: CR 425 (Dean Road)	To: East of Old Cheney Hwy.
Road No.: SR 50	Begin M.P.: 9.445	End M.P.: 14.645	Length: 5.200

Core No.	MP	Distance from left edge of lane (ft)	Lane	Wheel Path	Pavement Layer (in)										Crack				Pavt. Cond.	Rut Depth (in)	Cross Slope	Comments	
					FC-6	FC-5	Type S	Type I	Type III	ST	Blader	Core Length (in)	Base Type	Base Thk (in)	Depth (in)	Type	Class	Extent					
117	11.845	6	RLTL			0.4	6.7						13.3	ABC3	6.2	--	--	--	--	G			To Taco Bell
119	11.949	3	RLTL	X		1.0	1.5						2.5	L/R	16.3	--	--	--	--	G			To Sophie Blvd.
120	12.076	6	RLTL			1.0	3.7						4.7	L/R	14.8	--	--	--	--	G			To Big K
122	12.410	9	RLTL	X		0.8	3.0						3.8	L/R	13.2	--	--	--	--	G			To Michaels
125	12.953	9	RLTL	X		0.6	1.6	1.0				2.3	5.5	L/R	12.5	--	--	--	--	G			To Bonneville Dr.
126	12.213	6	RLTL			1.1	4.1						14.7	ABC3	9.5	--	--	--	--	G			To Lake Pickett Rd.
128*	13.501	3	RLTL	X			1.9						1.9	L/R	14.6	--	--	--	--	G			To U turns
131	13.754	9	RLTL	X		1.0	2.1						3.1	L/R	10.9	--	--	--	--	G			To Fairway C.C.
1	9.500	6	RRTL			1.6	1.3						2.9	L/R	5.2	--	--	--	--	G			Merge Lane from Dean Rd.
3	9.593	3	RRTL	X		1.5	1.9						3.4	L/R	12.7	--	--	--	--	G			To Park n Ride
5	9.814	9	RRTL	X		1.4	2.5						3.9	L/R	5.7	--	--	--	--	G			To Durango's
6	9.938	9	RRTL	X		1.4	1.3						2.7	L/R	11.4	--	--	--	--	G			To Culver Rd.
7	10.001	3	RRTL	X		1.6	1.7						3.3	L/R	13.0	--	--	--	--	G			To Reedy Plaza
8	10.086	9	RRTL	X		1.1	1.7						2.8	L/R	10.2	--	--	--	--	G			To Captain D's
12	10.694	6	RRTL			1.7	2.6						4.3	L/R	9.7	--	--	--	--	G			To Rouse Rd.
14	10.806	3	RRTL	X		1.2	1.5						2.7	L/R	15.4	--	--	--	--	G			To Krystals

Remarks: Auxiliary Lanes
Friction Course changes from FC-6 West of SR 434 to FC-5 East of SR 434
* No Friction Course completed currently

State of Florida Department of Transportation
PAVEMENT EVALUATION AND CONDITION DATA SHEET

Project No.: 239203-4					Cored By: F. Shaw & P. Gatewood					Date: 2/5/01					Page No.: 8 of 13									
County: Orange					Highway Sect. No.: 75060					From: CR 425 (Dean Road)					To: East of Old Cheney Hwy.									
Road No.: SR 50					Begin M.P.: 9.445					End M.P.: 14.645					Length: 5.200									
Core No.	MP	Distance from left edge of lane (ft)	Lane	Wheel Path	Pavement Layer (in)										Crack				Pavt. Cond.	Rat Depth (in)	Cross Slope	Comments		
					FC-6	FC-5	Type S	Type I	Type III	ST	Blader	Core Length (in)	Base Type	Base Thick (in)	Depth (in)	Type	Class	Extent						
15	10.922	9	RRTL	X	0.9		2.1						3.0	L/R	14.3	--	--	--	--	G				To Lake Berge Rd.
16	11.108	6	RRTL		1.7		2.7						4.4	L/R	13.4	--	--	--	--	G				To Wal-Mart
18	11.310	9	RRTL	X	1.2		1.8						3.0	L/R	9.7	--	--	--	--	G				To Car Wash
20	11.498	9	RRTL	X	1.6		1.6						3.2	L/R	9.9	--	--	--	--	G				To Big Lots
22	11.596	3	RRTL	X	1.2		1.4						2.6	L/R	11.4	--	--	--	--	G				To Albertsons
23	11.684	6	RRTL		1.5		1.1						2.6	L/R	12.1	--	--	--	--	G				To Alafaya Tr.
25	11.814	3	RRTL	X	1.2		1.8						3.0	L/R	13.4	--	--	--	--	G				To Tropi Grill
26	11.947	9	RRTL	X	0.7		1.6						2.3	L/R	14.2	--	--	--	--	G				To Sophie Blvd.
27	12.023	3	RRTL	X	1.3		3.2						13.9	ABC3	9.4	--	--	--	--	G				Merge Lane from Sophie Blvd.
28	12.100	6	RRTL		0.8		1.7						2.5	L/R	15.6	--	--	--	--	G				To Express Care
29	12.167	9	RRTL	X	0.6		2.9						3.5	L/R	11.7	--	--	--	--	G				To Cricket Club Apts.
31	12.235	6	RRTL		0.8		2.9						3.7	L/R	12.3	--	--	--	--	G				To Cricket Club Apts.
33	12.401	3	RRTL	X	0.7		2.9						3.6	L/R	11.4	--	--	--	--	G				To Diner
34	12.464	9	RRTL	X	0.9		2.9						3.8	L/R	14.2	--	--	--	--	G				To Woodbury Rd.
36	12.551	9	RRTL	X	1.1		3.0						4.1	L/R	11.2	--	--	--	--	G				To 408 West
38	12.887	9	RRTL	X	1.3		5.4						6.7	L/R	12.2	--	--	--	--	G				Merge Lane from 408

Remarks: Auxiliary Lanes
Friction Course changes from FC-6 West of SR 434 to FC-5 East of SR 434

State of Florida Department of Transportation
PAVEMENT EVALUATION AND CONDITION DATA SHEET

Project No.: 239203-4	Cored By: F. Shaw & P. Gatewood	Date: 2/5/01	Page No.: 9 of 13
County: Orange	Highway Sect. No: 75060	From: CR 425 (Dean Road)	To: East of Old Cheney Hwy.
Road No.: SR 50	Begin M.P.: 9.445	End M.P.: 14.645	Length: 5.200

Core No.	MP	Distance from left edge of lane (ft)	Lane	Wheel Path	Pavement Layer (in)										Crack				Pavt. Cond.	Rut Depth (in)	Cross Slope	Comments
					FC-6	FC-5	Type S	Type I	Type III	ST	Binder	Core Length (in)	Base Type	Base Thick (in)	Depth (in)	Type	Class	Extent				
39	12.980	6	RRTL		1.2		6.2					7.4	L/R	11.9	--	--	--	--	G			To Bonneville Dr.
40	13.102	9	RRTL	X	1.2		3.5					4.7	L/R	12.4	--	--	--	--	G			To Speedway Gas
42	13.231	3	RRTL	X	1.0		3.9					4.9	L/R	12.5	--	--	--	--	G			To Lake Pickett Rd.
46	13.786	6	RRTL		0.9		1.9					2.8	L/R	10.7	--	--	--	--	G			To Texaco
47	13.887	3	RRTL	X	0.7		1.6					2.3	L/R	12.6	--	--	--	--	G			To Pel St.
48	13.979	9	RRTL	X	1.0		1.6					2.6	L/R	12.5	--	--	--	--	G			To Plumbing Svc.
50	14.341	6	RRTL		1.1		3.9					13.0	ABC3	8.0	--	--	--	--	G			To Old Cheney Hwy
143	13.956	6	LLTL			1.1	2.3					3.4	SC	12.3	--	--	--	--	G			To Pel St
144	13.836	9	LLTL	X		1.0	1.8					2.8	L/R	12.6	--	--	--	--	G			To Texaco
147*	13.425	6	LLTL				2.7					2.7	L/R	11.8	--	--	--	--	G			To Walgreens
148	13.340	3	LLTL	X		0.9	4.6					5.5	L/R	13.6	--	--	--	--	G			To Lake Pickett Rd.
150	13.173	6	LLTL			0.9	4.1					5.0	L/R	12.4	--	--	--	--	G			To Racetrac Gas
151	13.017	9	LLTL	X		0.9	5.4					6.3	L/R	11.8	--	--	--	--	G			To Bonneville Dr.
153	12.565	3	LLTL	X		0.9	1.1	1.9				3.9	L/R	13.4	--	--	--	--	G			To Woodbury Rd.
155	12.467	9	LLTL	X		1.3	2.2					3.5	L/R	14.3	--	--	--	--	G			To Diner
156	12.325	6	LLTL			0.5	2.8					3.3	L/R	12.2	--	--	--	--	G			To Cricket Club Apts.

Remarks: Auxiliary Lanes
Friction Course changes from FC-6 West of SR 434 to FC-5 East of SR 434
* No Friction Course completed currently

State of Florida Department of Transportation
PAVEMENT EVALUATION AND CONDITION DATA SHEET

Project No.: 239203-4	Cored By: F. Shaw & P. Gatewood	Date: 2/5/01	Page No.: 10 of 13
County: Orange	Highway Sect. No: 75060	From: CR 425 (Dean Road)	To: East of Old Cheney Hwy.
Road No.: SR 50	Begin M.P.: 9.445	End M.P.: 14.645	Length: 5.200

Core No.	MP	Distance from left edge of lane (ft)	Lane	Wheel Path	Pavement Layer (in)										Crack				Pavt. Cond.	Rut Depth (in)	Cross Slope	Comments	
					FC-6	FC-5	Type S	Type I	Type III	ST	Binder	Core Length (in)	Base Type	Base Thick (in)	Depth (in)	Type	Class	Extent					
158	12.171	3	LLTL	X		1.3	1.5					2.8	L/R	14.2	--	--	--	--	G				To Car Wash
159	12.029	6	LLTL			1.0	2.3					3.3	L/R	5.4	--	--	--	--	G				To Sophie Blvd.
160	11.912	9	LLTL	X		1.2	2.0					3.2	L/R	12.6	--	--	--	--	G				To Olive Garden
161	11.816	9	LLLTL	X		1.1	8.1					13.9	ABC3	4.7	--	--	--	--	G				To SR 434
115	11.674	9	RLTL	X	1.7		5.5					13.0	ABC3	5.8	--	--	--	--	G				To SR 434
164	11.526	9	LLTL	X	1.0		10.7					11.7	L/R	6.7	--	--	--	--	G				To Big Lots
166	11.395	6	LLTL		1.4		6.4					13.3	ABC3	5.5	--	--	--	--	G				To Video Rental
167	11.255	3	LLTL	X	1.8		6.0					14.8	ABC3	7.0	--	--	--	--	G				To Wal-Mart
169	11.022	6	LLTL		1.5		1.7					3.2	L/R	13.4	--	--	--	--	G				To Hollywood Video
170	10.868	9	LLTL	X	1.2		2.2					3.4	SC	10.9	--	--	--	--	G				To Krystals
172	10.765	6	LLTL		1.8		1.2					3.0	L/R	11.3	--	--	--	--	G				To Rouse Rd.
173	10.664	3	LLTL	X	1.0		7.6					14.8	ABC3	6.2	--	--	--	--	G				To Park Manor
174	10.466	9	LLTL	X	1.7		5.0					14.5	ABC3	7.8	--	--	--	--	G				To Grayson Dr.
176	10.334	6	LLTL		1.3		3.2					9.9	ABC3	5.4	--	--	--	--	G				To Animal Hospital
177	10.241	3	LLTL	X	2.0		1.2				1.8	5.0	L/R	11.2	--	--	--	--	G				To Murdock Blvd.
179	10.082	9	LLTL	X	1.5		1.7					3.2	L/R	12.1	--	--	--	--	G				To Plaza

Remarks: Auxiliary Lanes
Friction Course changes from FC-6 West of SR 434 to FC-5 East of SR 434

State of Florida Department of Transportation
PAVEMENT EVALUATION AND CONDITION DATA SHEET

Project No.: 239203-4	Cored By: F. Shaw & P. Gatewood	Date: 2/5/01	Page No.: 11 of 13
County: Orange	Highway Sect. No.: 75060	From: CR 425 (Dean Road)	To: East of Old Cheney Hwy.
Road No.: SR 50	Begin M.P.: 9.445	End M.P.: 14.645	Length: 5.200

Core No.	MP	Distance from left edge of lane (ft)	Lane	Wheel Path	Pavement Layer (in)										Crack				Pavt. Cond.	Rat Depth (in)	Cross Slope	Comments
					FC-6	FC-5	Type S	Type I	Type III	ST	Binder	Core Length (in)	Base Type	Base Thick (in)	Depth (in)	Type	Class	Extent				
180	9.982	6	LLTL		2.0		1.8					13.0	ABC3	9.2	--	--	--	--	G			To Big 10 Tire
182	9.798	9	LLTL	X	1.4		6.9					14.3	ABC3	6.0	--	--	--	--	G			To Durangos
183	9.646	6	LLTL		1.5		6.6					13.9	ABC3	5.8	--	--	--	--	G			To Park n Ride
184	9.489	3	LLTL	X	1.7		1.7				1.1	4.5	L/R	12.3	--	--	--	--	G			To Dean Rd.
58	13.838	9	LRTL		1.1		1.5					2.6	L/R	7.3	--	--	--	--	G			To Fairway C.C.
59	13.691	3	LRTL	X	0.6		4.2					4.8	L/R	10.4	--	--	--	--	G			To Fricke Ave.
61	13.321	6	LRTL		0.8		1.8					2.6	L/R	9.9	--	--	--	--	G			To Lake Pickett Rd.
64	12.295	3	LRTL	X	0.8		4.2					11.0	ABC3	6.0	--	--	--	--	G			Merge from Bonneville Rd.
66	12.705	9	LRTL	X	1.7		1.2					2.9	L/R	12.3	--	--	--	--	G			To 408 West
69	12.163	6	LRTL		0.6		3.1					3.7	L/R	13.3	--	--	--	--	G			To Chilis
70	12.095	9	LRTL	X	0.7		2.0					2.7	L/R	12.9	--	--	--	--	G			To Steak n Shake
71	12.025	3	LRTL	X	1.4		2.0					3.4	L/R	10.8	--	--	--	--	G			To Sophie Blvd.
74	11.890	6	LRTL		0.5		3.0					3.5	L/R	11.2	--	--	--	--	G			To Dennys
75	11.795	9	LRTL	X	1.1		9.4					14.0	ABC3	3.5	--	--	--	--	G			To Alafaya Tr.
77	11.541	3	LRTL	X	1.6		1.9					3.5	L/R	12.9	--	--	--	--	G			To Hedlightz
81	10.772	6	LRTL		1.1		3.6					4.7	L/R	16.3	--	--	--	--	G			To Rouse Rd.

Remarks: Auxiliary Lanes
Friction Course changes from FC-6 West of SR 434 to FC-5 East of SR 434

State of Florida Department of Transportation
PAVEMENT EVALUATION AND CONDITION DATA SHEET

Project No.: 239203-4	Cored By: F. Shaw & P. Gatewood	Date: 2/5/01	Page No.: 12 of 13
County: Orange	Highway Sect. No: 75060	From: CR 425 (Dean Road)	To: East of Old Cheney Hwy.
Road No.: SR 50	Begin M.P.: 9.445	End M.P.: 14.645	Length: 5.200

Core No.	MP	Distance from left edge of lane (ft)	Lane	Wheel Path	Pavement Layer (in)										Crack				Pavt. Cond.	Rat Depth (in)	Cross Slope	Comments	
					FC-6	FC-5	Type S	Type I	Type III	ST	Binder	Core Length (in)	Base Type	Base Thick (in)	Depth (in)	Type	Class	Extent					
82	10.680	9	LRTL	X	0.9		3.7					4.6	L/R	15.8	--	--	--	--	G				To Autozone
84	10.476	3	LRTL	X	1.4		1.6					3.0	L/R	10.2	--	--	--	--	G				To Alamo Shopping Ctr.
85	10.390	6	LRTL		1.3		1.3					2.6	L/R	10.4	--	--	--	--	G				To Alamo Shopping Ctr.
87	10.255	9	LRTL	X	1.5		2.2					3.7	L/R	10.3	--	--	--	--	G				To Murdock Blvd.
88	10.133	6	LRTL		1.9		2.7					4.6	L/R	6.2	--	--	--	--	G				To McDonalds
93	9.492	9	LRTL	X	1.4		3.2					4.6	L/R	11.4	--	--	--	--	G				To Dean Rd.
129	13.643		MXO			1.3	1.0	0.5				2.2	5.0	L/R	13.9	--	--	--	--	G			
133	14.051		MXO			0.8	1.5					2.1	4.4	L/R	12.1	--	--	--	--	G			
134	14.162		MXO			1.1	1.4					2.1	4.6	L/R	11.9	--	--	--	--	G			
135	14.290		MXO			1.3	1.1					1.6	4.0	L/R	12.4	--	--	--	--	G			
137	14.400		MXO			1.5	0.9					1.5	3.9	L/R	12.6	--	--	--	--	G			
138	14.583		MXO			1.4	2.2					1.9	5.5	L/R	11.9	--	--	--	--	G			

Remarks: Auxiliary Lanes
Friction Course changes from FC-6 West of SR 434 to FC-5 East of SR 434

State of Florida Department of Transportation
PAVEMENT EVALUATION AND CONDITION DATA SHEET

Project No.: 239203-4	Cored By: F. Shaw & P. Gatewood	Date: 2/5/01	Page No.: 13 of 13
County: Orange	Highway Sect. No: 75060	From: CR 425 (Dean Road)	To: East of Old Cheney Hwy.
Road No.: SR 50	Begin M.P.: 9.445	End M.P.: 14.645	Length: 5.200

Core No.	MP	Distance from left edge of lane (ft)	Lane	Wheel Path	Pavement Layer (in)										Crack				Pavt. Cond.	Ret Depth (in)	Cross Slope	Comments			
					FC-6	FC-5	Type S	Type I	Type III	ST	Binder	Core Length (in)	Base Type	Base Thick (in)	Depth (in)	Type	Class	Extent							
10	10.203	1	OR		2.1		1.0						7.1	ABC3	4.0	--	--	--	--	G			5' Shoulder		
19	11.425	2	OR		1.3		1.1						7.0	ABC3	4.6	--	--	--	--	G			5' Shoulder		
32	12.304	2	OR			0.8	1.6						4.1	ABC3	1.7	--	--	--	--	G			5' Shoulder		
43	13.411	2	OR			0.8	2.1						4.0	ABC3	1.1	--	--	--	--	G			5' Shoulder		
52	14.421	2	OR			1.2	1.9						5.5	ABC3	2.4	--	--	--	--	G			5' Shoulder		
57	13.899	2	OL			1.2	2.8						4.0	L/R	5.5	--	--	--	--	G			5' Shoulder		
65	12.866	3	OL			0.7	1.3						2.0	L/R	10.5	--	--	--	--	G			12' Shoulder		
73	11.954	2	OL			0.8	2.5						3.3	L/R	9.7	--	--	--	--	G			5' Shoulder		
80	10.909	2	OL		1.6		2.9						7.5	ABC3	3.0	--	--	--	--	G			5' Shoulder		
90	9.891	2	OL		1.5		1.4						7.7	ABC3	4.8	--	--	--	--	G			5' Shoulder		

Remarks: Shoulders
 Friction Course changes from FC-6 West of SR 434 to FC-5 East of SR 434