

**State of Florida Department of Transportation**  
**PAVEMENT EVALUATION AND CONDITION DATA SHEET**

<b>Project No.:</b> 433648-1		<b>Cored By:</b> Ardaman				<b>Date:</b> 8/12/2013				<b>Page No.:</b> 1 of 1										
<b>County:</b> Orange		<b>Highway Sect. No.:</b> 75040				<b>From:</b> South of Lake Gatlin Road				<b>To:</b> North Of Holden Ave.										
<b>Road No.:</b> SR 527		<b>Begin MP:</b> 10.575				<b>End MP:</b> 10.850				<b>Length:</b> 0.275 Miles										
Core No.	MP	Distance from left edge of lane (ft.)	Lane	Wheel Path	Pavement Layers (in.)						Base		Crack				Pavt Cond.	Rut Depth (in)	Cross Slope (%)	Comments
					FC-6	FC-4	Type SP / Type S	Type I	Binder	Core Length (in)	Type	Thick-ness (in)	Depth (in)	Type	Class	Extent				
1	10.677	6.0	RRTL		1.8				3.0	4.8	LR	22.2	1.8	BR	I	L	F			To Gatlin Avenue
2	10.711	5.5	R2		1.3		1.0	0.7	2.0	5.0	LR	9.0	1.7	SL	I	L	F			
3	10.737	6.5	RRTL		1.5		1.6			11.5	ABC	8.4	0.3	SL	I	L	F			To Shopping Plaza
4	10.759	10.0	Ramp			0.4	1.1			10.0	ABC	8.5	---	---	---	---	F			To Shopping Plaza
5	10.791	4.5	R2		1.5		1.2		2.3	5.0	LR	9.3	B	BR	II	M	P			Split core at 3.00"
6	10.797	5.0	L2		1.4		0.8	0.6	2.0	4.8	LR	8.7	3.0	SL	I	L	F			Split core at 2.00"
7	10.742	2.0	OL		1.5		0.6	0.9	2.3	5.3	LR	8.5	---	---	---	---	F			
8	10.726	9.0	L2	X	1.5		1.5		1.6	4.6	LR	7.7	B	BR	I	M	F			
9	10.653	3.0	L2	X	1.5		1.3			2.8	LR	8.0	---	---	---	---	F			
10	10.665	3.5	R1	X	1.5		1.0		2.4	4.9	LR	9.1	---	---	---	---	F			
11	10.744	6.0	RLTL		1.0		2.1	1.0	2.1	6.2	LR	8.3	---	---	---	---	F			To Holden Avenue
12	10.681	3.0	L1	X	1.4		1.9		1.9	5.2	LR	9.3	5.0	SL	II	M	F			
13	10.644	4.5	LLTL		1.0		1.5			2.5	LR	8.5	---	---	---	---	F			To Lake Gatlin Road
14	10.632	11.0	R1			0.8	1.2		2.1	4.1	LR	8.9	B	BR	II	L	F			Lake Gatlin Road
15	10.699	7.5	R1				2.5			2.5	LR	9.8	B	BR	II	L	F			Gatlin Avenue
16	10.772	5.0	R1		1.2		1.3			12.0	ABC	9.5	---	---	---	---	F			Holden Avenue

**Remarks:** Crack Depth of "B" indicates full depth crack to the base. EOP = Edge of Pavement  
Crack Extent: L= Light; M= Moderate; S= Severe      Pavement Condition: G= Good; F= Fair; P= Poor      Crack Types: A= Alligator; BI= Block; Br= Branch  
SL= Single Longitudinal; ST= Single Transverse; R= Reflective; J= Joint; OGFC= Open-Graded FC Stress Crack  
Base Types: LR= Limerock; COQ= Coquina; SC= Soil Cement; ABC= Asphalt Base; SAHM= Sand Asphalt Hot Mix; NB= No Base