

State of Florida Department of Transportation
PAVEMENT EVALUATION AND CONDITION DATA SHEET

Project No.: 430682-1	Cored By: Ardaman	Date: 9/6/2013	Page No.: 1 of 1
County: Volusia	Highway Sect. No.: 79260	From: South of Silver Beach Ave.	To: SR 600 (US 92)
Road No.: SR 441	Begin MP: 4.750	End MP: 5.409	Length: 0.659 Miles

Core No.	MP	Distance from left edge of lane (ft.)	Lane	Wheel Path	Pavement Layers (in.)						Base		Crack				Pavt Cond.	Rut Depth (in)	Cross Slope (%)	Comments	
					FC-6	Type S	Type I	Type II w/ Shell	ST	Core Length (in)	Type	Thick-ness (in)	Depth (in)	Type	Class	Extent					
1	5.347	2.5	L1	X	1.7			0.6		2.3	COQ	11.3	B	BL	II	S	P				
2	5.091	9.0	L1	X	1.7			0.3		2.0	COQ	7.0	B	BL	III	S	P				
3	4.866	7.0	L1	---	1.1	0.5		0.4		2.0	COQ	7.8	B	BL	III	S	P				
4	4.805	8.0	LLTL	X	2.0				0.7	2.7	LR	9.6	---	---	---	---	F			To Silver Beach Ave.	
5	4.798	3.5	L1	X	0.8					0.8	LR	9.0	B	BR	II	M	P				
6	4.750	3.0	L2	X	1.5	0.3			2.6	4.4	LR	8.1	B	BR	II	M	P				
7	4.750	3.5	L1	X	0.8	1.5			2.0	4.3	LR	8.0	B	BR	II	M	P				
8	4.750	8.5	RLTL	X	1.5	0.5			1.0	3.0	LR	8.3	---	---	---	---	F			To Silver Beach Ave.	
9	4.750	4.0	R1	X	1.0	0.9				1.9	LR	8.1	---	---	---	---	F				
10	4.790	9.0	R1	X	1.7	3.3	2.0			7.0	LR	10.9	---	---	---	---	F				
11	4.843	5.0	R1	---	1.5			1.0		2.5	COQ	6.3	B	BR	III	S	P				
12	4.945	9.0	R1	X	1.0			1.3		2.3	COQ	6.2	B	BR	III	S	P				
13	5.227	3.0	R1	X	1.7		1.0	0.5		3.2	COQ	9.1	B	BR	III	S	P				
14	5.392	6.0	R1	---	1.2	1.7				2.9	COQ	8.7	B	ST	II	M	P				

Remarks: Crack Depth of "B" indicates full depth crack to the base. EOP = Edge of Pavement
Crack Extent: L= Light; M= Moderate; S= Severe Pavement Condition: G= Good; F= Fair; P= Poor Crack Types: A= Alligator; Bl= Block; Br= Branch
SL= Single Longitudinal; ST= Single Transverse; R= Reflective; J= Joint; OGFC= Open-Graded FC Stress Crack
Base Types: LR= Limerock; COQ= Coquina; SC= Soil Cement; ABC= Asphalt Base; SAHM= Sand Asphalt Hot Mix; NB= No Base