

State of Florida Department of Transportation
PAVEMENT EVALUATION AND CONDITION DATA SHEET

Project No.: 432441-1		Cored By: FDOT - TK, TD					Date: 3/4/2014					Page No.: 1 of 1									
County: Volusia		Highway Sect. No.: 79060					From: From US 17-Woodland Blvd.					To: Alabama Street									
Road No.: SR 600 (US 92)		Begin MP: 0.000					End MP: 0.147					Length: 0.147									
Core No.	MP	Distance from left edge of lane (ft)	Lane	Wheel Path	Pavement Layer (in.)							Base		Crack				Pavt Cond.	Rut Depth (in)	Cross Slope (%)	Comments
					FC-4	Type S	Type III	Type I	Binder		Core Length (in)	Type	Thick-ness (in)	Depth (in)	Type	Class	Extent				
1	0.145	5.0	LLTL			3.2					3.2	LR	8.1					F			Left Turn Lane to Alabama St.
2	0.148	6.0	LRTL		0.6	2.0					2.6	LR	18.4					P			Right Turn Lane to Shopping Plaza
3	0.057	6.0	LRTL		1.0						9.0	PCC	8.0					P			Right Turn Lane to US 17- North
4	0.057	1.5	OL			1.8					1.8	LR	4.7					P			Paved Shoulder
5	0.057	7.0	L2		1.3						9.5	PCC	8.2					P			WB Outside Travel Lane
6	0.033	6.5	L1		0.2	0.7	1.0	1.6			3.5	LR	13.9					F			WB Inside Travel Lane
7A	0.029	3.5	LLTL-2	X	0.8	0.3	0.9	1.7			3.7	LR	10.7	B	SL	II	M	P			Outside Dual Left TL to US-17 South Split Core
7B	0.029	3.5	LLTL-2	X	0.8	2.7					3.5	LR	10.7	B	SL	II	M	P			Outside Dual Left TL to US-17 South Split Core
8	0.024	6.0	LLTL-1		0.9	2.0					2.9	LR	12.9					F			Inside Dual Left TL to US-17 South
9	0.080	4.5	R1		0.9	1.6			2.0		4.5	LR	6.8	B	A	II	S	P			EB Inside Travel Lane
10	0.800	4.0	R2	X	0.9	1.9			1.7		4.5	LR	7.0	2.3	Bl	II	M	P			EB Outside Travel Lane
11	0.080	6.0	RRTL		1.2	2.2					3.4	LR	15.2					F			Right Turn Lane to Alabama St.
12	0.080	2.5	OR		1.0	2.1					3.1	LR	10.0					F			Paved Shoulder

Remarks: Crack Depth of "B" indicates full depth crack to the base. EOP = Edge of Pavement
Crack Extent: L= Light; M= Moderate; S= Severe Pavement Condition: G= Good; F= Fair; P= Poor Crack Types: A= Alligator; Bl= Block; Br= Branch
 SL= Single Longitudinal; ST= Single Transverse; R= Reflective; J= Joint; OGFC= Open-Graded FC Stress Crack
Base Types: LR= Limerock; COQ= Coquina; SC= Soil Cement; ABC= Asphalt Base; SAHM= Sand Asphalt Hot Mix; NB= No Base