

**State of Florida Department of Transportation
PAVEMENT EVALUATION AND CONDITION DATA SHEET**

Project No.: 441017-1	Cored By: D. Rapp / E. Bluemke (Terracon)	Date: 6/27/2019	Page No.: 1 of 2
County: Osceola	Highway Sect. No: 92010	From: Vine Street (US 192)	To: Old Dixie Highway (CR 527)
Road No.: SR 500 (US 441)	Begin MP: 11.916	End MP: 12.283	Length: 0.367

Core No.	MP	Distance from left edge of lane (ft.)	Lane	Wheel Path	Pavement Layer (in.)					Base			Crack				Pavt Cond.	Rut Depth (in.)	Cross Slope (%)	Comments
					FC-6	Type S	Binder			Core Length (in.)	Type	Thick-ness (in.)	Depth (in.)	Type	Class	Extent				
1	12.049	9.6	R2	x	1.9	2.2	2.3			6.4	LR	6.9	B	Br	III	S	P			Adjacent to multiple pavement patches
2	12.159	7.8	R2	x	1.4	0.2	1.9			3.5	LR	-	B	Br	III	S	P			
3	12.200	6.5	L2		1.0	0.8	1.6			3.4	LR	8.9	B	Br	III	M	P			
4	12.074	3.9	L2	x	1.0	0.5	1.4			2.9	LR	-	B	Br	III	M	P			
5	11.930	6.3	L2		0.9	0.6	1.7			3.2	LR	6.1	B	Br	III	M	P			
6	11.970	2.1	R1	x	1.9	0.9	1.3			4.1	LR	7.2	1.2	Br	II	L	P			Pavement Rippling, 2.1 inch crack from base up
7	12.156	2.0	R1	x	1.0	2.0	1.3			4.3	LR	-	B	Br	III	M	P			
8	12.259	6.3	L1		1.2	0.6	1.3			3.1	LR	6.9	-	-	-	-	F			
9	12.134	1.8	L1	x	1.2	0.9	1.2			3.3	LR	-	B	Br	III	M	P			Pavement Separation 1.5 inches
10	11.964	6.2	CTL		1.0	0.5	1.7			3.2	LR	-	B	SL	III	S	P			
11	12.135	6.0	CTL		1.1	0.4	1.4			2.9	LR	8.2	B	SL	III	S	P			

Remarks: Crack Depth of "B" indicates full depth crack to the base. EOP = Edge of Pavement
Crack Extent: L= Light; M= Moderate; S= Severe Pavement Condition: G= Good; F= Fair; P= Poor
Crack Types: A= Alligator; Bl= Block; Br= Branch; SL= Single Longitudinal; ST= Single Transverse; R= Reflective; J= Joint; OGFC= Open-Graded FC Stress Crack
Base Types: LR= Limerock; COQ= Coquina; SC= Soil Cement; ABC= Asphalt Base; SAHM= Sand Asphalt Hot Mix; SBRM= Sand Bituminous Road Mix; NB= No Base

**State of Florida Department of Transportation
PAVEMENT EVALUATION AND CONDITION DATA SHEET**

Project No.: 441017-1	Cored By: D. Rapp / E. Bluemke (Terracon)	Date: 6/27/2019	Page No.: 2 of 2
County: Osceola	Highway Sect. No: 92010	From: Vine Street (US 192)	To: Old Dixie Highway (CR 527)
Road No.: SR 500 (US 441)	Begin MP: 11.916	End MP: 12.283	Length: 0.367

Core No.	MP	Distance from left edge of lane (ft.)	Lane	Wheel Path	Pavement Layer (in.)					Base		Crack				Pavt Cond.	Rut Depth (in.)	Cross Slope (%)	Comments
					FC-6	Type SP	Type S	Binder			Core Length (in.)	Type	Thick-ness (in.)	Depth (in.)	Type				
D-1	12.110	6.5	L2							7.1	LR								Box Culvert - Extension
D-2	12.110	5.5	L1							2.3	PCC								Bridge # 920007
D-3	12.110	5.8	R1							2.2	PCC								Bridge # 920007
D-4	12.110	6.2	R2							9.8	LR								Box Culvert - Extension
These are hand drill for asphalt overlay thickness. Thickness reported is considered to be approximate (+/-)																			

Remarks: Crack Depth of "B" indicates full depth crack to the base. EOP = Edge of Pavement
Crack Extent: L= Light; M= Moderate; S= Severe Pavement Condition: G= Good; F= Fair; P= Poor
Crack Types: A= Alligator; Bl= Block; Br= Branch; SL= Single Longitudinal; ST= Single Transverse; R= Reflective; J= Joint; OGFC= Open-Graded FC Stress Crack
Base Types: LR= Limerock; COQ= Coquina; SC= Soil Cement; ABC= Asphalt Base; SAHM= Sand Asphalt Hot Mix; SBRM= Sand Bituminous Road Mix; NB= No Base