

02/21/23

FLORIDA DEPARTMENT OF TRANSPORTATION
PAVEMENT CORING REPORTING

PCRPJ03
PCRO003

PAVEMENT EVALUATION CORING AND CONDITION DATA
INPUT DATA REPORT

MANDIST	FINPROJ	TYPSECT	MESSAGE
06	437053-3-52-01	01	THE CONTROL CARD IS CORRECT

02/21/23

FLORIDA DEPARTMENT OF TRANSPORTATION
PAVEMENT CORING REPORTING

PCRPJ03
PCRO103

PAVEMENT EVALUATION CORING AND CONDITION DATA

FIN PROJ: 437053-3-52-01	NAME:	CORED BY: GEOSOL INC.
TYP SECT: 01	FROM:	DATE: 2017-09-14
	TO:	LANES: @ FEET
FA PROJ:	BEG MP: 10.89	SHOULDER TYPE
COUNTY: MIAMI-DADE	END MP: 11.16 LENGTH: .27	INSIDE:
SR NUMBER: SR 9A	PROJECT MEASUREMENT: ENGLISH	OUTSIDE:
MEDIAN:		CURB & GUTTER: NO
CURBED: NO		

PAVEMENT EVALUATION CORING AND CONDITION DATA

COMMENTS

SEQ

1 SUBGRADE MATERIALS CONSISTS OF FINE TO MEDIUM SAND
2 WITH TRACE OF LIMEROCK FRAGMENT (A-3), EXCEPT FOR
3 CORE 13 (C-13) WHICH HAD BASE AND SUBGRADE
4 MATERIALS COSISTING OF FINE TO MEDIUM SAND WITH
5 LITTLE LIMEROCK FRAGMENTS (A-1-B). CORES CONSIST
6 OF CONCRETE PAVEMENT WITH THICKNESS RANGING FROM
7 8.3 TO 9.5 INCHES, EXCEPT FOR CORE 13 (C-13) WHICH
8 SB I-95 ON-RAMP FROM NW 151ST STREET WHICH
9 CONSISTED OF ASPHALT PAVEMENT WITH A THICKNESS OF
10 2.5 INCHES.
11 THE MILLING RECOMMENDATION IS TO MILL 1.5" AND
12 REPAVE WITH 1.5" FC 12.5 FOR THE NW 151 STREET
13 RAMP.
14 CORES 17 TO 26 CONSISTED OF ASPHALT PAVEMENT
15 THE MILLING RECOMMENDATION FOR SIDE STREETS IS
16 TO MILL 1.25" AND REPLACE WITH FC 9.5.

CODE DESCRIPTIONS

CRACK TYPE TYPE DESCRIPTION
=====

A ALLIGATORING IN WHEELPATH

B BLOCK CRACKING

C COMBINATION OF TYPES

CRACK EXTNT EXTENT DESCRIPTION
=====

L LIGHT

M MEDIUM

S SEVERE

CRACK CLASS CLASS DESCRIPTION
=====

IB UNKNOWN

II UNKNOWN

III UNKNOWN

CODE DESCRIPTIONS

SURFACE LAYER CODE =====	DESCRIPTION =====
ARMI	ASPHALT RUBBER MEMBRANE INTERL
BIND	ASPHALT BINDER COURSE
BRCK	BRICK PAVERS
CONC	PORTLAND CEMENT CONCRETE
CRL	CRACK RELIEF LAYER
FAB	PAVEMENT OVERLAY FABRIC
FC	FRICTION COURSE
FC1	FRICTION COURSE 1
FC2	FRICTION COURSE 2
FC3	FRICTION COURSE 3
FC4	FRICTION COURSE 4
FC5	FRICTION COURSE 5
FC5B	FRICTION COURSE 5 BONDED
FC6	FRICTION COURSE 6
F12M	FRIC. COURSE 12.5 MODIFIED
F125	FRICTION COURSE 12.5
F95	FRICTION COURSE 9.5
F95M	FRIC. COURSE 9.5 MODIFIED
S	TYPE S ASPHALTIC CONCRETE
SAHM	SAND ASPHALT HOT MIX
SP1C	9.5 SUPERPAVE COARSE GRADED
SP1F	9.5 SUPERPAVE FINE GRADED
SP2C	12.5 SUPERPAVE COARSE GRADED
SP2F	12.5 SUPERPAVE FINE GRADED
SP3C	19.0 SUPERPAVE COARSE GRADED
SP3F	19.0 SUPERPAVE FINE GRADED
ST	SURFACE TREATMENT
S1	TYPE S-I ASPHALTIC CONCRETE
S2	TYPE S-II ASPHALTIC CONCRETE
S3	TYPE S-III ASPHALTIC CONCRETE
T1	TYPE I ASPHALTIC CONCRETE
T2	TYPE II ASPHALTIC CONCRETE
T3	TYPE III ASPHALTIC CONCRETE
UNIM	UNIMPROVED SURFACE
UNKW	UNKNOWN
WC	WEARING COURSE
WC1	WEARING COURSE 1
WC2	WEARING COURSE 2
WC3	WEARING COURSE 3
WC4	WEARING COURSE 4
WC5	WEARING COURSE 5
WC6	WEARING COURSE 6
WC7	WEARING COURSE 7
WC8	WEARING COURSE 8