PCRPJ03 PCRO003

PAVEMENT EVALUATION CORING AND CONDITION DATA INPUT DATA REPORT

MANDIST	FINPROJ	TYPSECT	MESSAGE
06	443896-1-52-01	01	THE CONTROL CARD IS CORRECT

PCRPJ03 PCR0103

PAVEMENT EVALUATION CORING AND CONDITION DATA

FIN PROJ:	443896-1-52-01	NAME :		CORED BY: HRES	
TYP SECT:	01	FROM:		DATE: 2019-01-21	
		TO:		LANES: @ FEET	
FA PROJ:	D623007B	DEC ND:	0.0		
COUNTY:	MIAMI-DADE	BEG MP:	.00	SHOULDER TYPE	
SR NUMBER:	SR 9A	END MP:	.03 LENGTH: .03	INSIDE:	
		PROJECT M	EASUREMENT: ENGLISH	OUTSIDE:	
MEDIAN:	No			CURB & GUTTER: NO	
CURBED:	NO				

PCRPJ03 PCR0203

PAVEMENT EVALUATION CORING AND CONDITION DATA

CORE	MILE			W					CORE								
NO.	POST	VFY	LN	Ρ	TOP		- PAVEMENT	LAYER	 LNGTH	BASE	SUB	DEPTH	TYP	CLSS	EXT	CND	COMMENTS
				-					 								
					FC2	S1	BIND			LR	ST40						
1	.000	Ν	L1	Y	.50	1.30	.50		2.30	12.0	12.0	2.30				P	195 RAMP AT RICKENBACKE
2	.000	Ν	L2	Y	.70	2.40			3.10	12.0	12.0	1.90				P	195 RAMP AT RICKENBACKE
3	.000	Ν	R2	Y	.60	1.30	2.00		3.90	12.0	12.0	3.90				P	SW 25 ROAD EB
4	.000	Ν	R2	Y	.30	1.70	2.00		4.00	12.0	12.0	4.00				P	SW 25 ROAD EB
	.000																

PCRPJ03 PCR0303

PAVEMENT EVALUATION CORING AND CONDITION DATA

COMMENTS

SEQ

- - 1 BASE AND SUBBASE ARE LIMEROCK.
 - 2 THE MILLING RECOMMENDATION IS TO MILL 2" AND
 - 3 REPLACE WITH 2" FC 12.5 AT ALL RAMPS AND 25TH RD.
 - 4 AN CONTINGENCY ITEM MAY BE NEEDED DUE TO HEAVY
 - 5 CRACKING ON 25TH ROAD (OVERBUILD)

	FRVEMENT CORING REFORTING
	CODE DESCRIPTIONS
	TYPE DESCRIPTION
А	ALLIGATORING IN WHEELPATH
В	BLOCK CRACKING
С	COMBINATION OF TYPES
	EXTENT DESCRIPTION
L	LIGHT
М	MEDIUM
S	SEVERE
	CLASS DESCRIPTION
IB	UNKNOWN
II	UNKNOWN

III

UNKNOWN

CODE DESCRIPTIONS

SURFACE LAYER	
CODE	DESCRIPTION
====	
ARMI	ASPHALT RUBBER MEMBRANE INTERL
BIND	ASPHALT BINDER COURSE
BRCK	BRICK PAVERS
CONC	PORTLAND CEMENT CONCRETE
CRL	CRACK RELIEF LAYER
FAB	PAVEMENT OVERLAY FABRIC
FC	FRICTION COURSE
FC1	FRICTION COURSE 1
FC2	FRICTION COURSE 2
FC3	FRICTION COURSE 3
FC4	FRICTION COURSE 4
FC5	FRICTION COURSE 5
FC5B	FRICTION COURSE 5 BONDED
FC6	FRICTION COURSE 6
F12M	FRIC. COURSE 12.5 MODIFIED
F125	FRICTION COURSE 12.5
F95	FRICTION COURSE 9.5
F95M	FRIC. COURSE 9.5 MODIFIED
S	TYPE S ASPHALTIC CONCRETE
SAHM	SAND ASPHALT HOT MIX
SP1C	9.5 SUPERPAVE COARSE GRADED
SP1F	9.5 SUPERPAVE FINE GRADED
SP2C	12.5 SUPERPAVE COARSE GRADED
SP2F	12.5 SUPERPAVE FINE GRADED
SP3C	19.0 SUPERPAVE COARSE GRADED
SP3F	19.0 SUPERPAVE FINE GRADED
ST	SURFACE TREATMENT
S1	TYPE S-I ASPHALTIC CONCRETE
S2	TYPE S-II ASPHALTIC CONCRETE
S3	TYPE S-III ASPHALTIC CONCRETE
T1	TYPE I ASPHALTIC CONCRETE
T2	TYPE II ASPHALTIC CONCRETE
T3	TYPE III ASPHALTIC CONCRETE
UNIM	UNIMPROVED SURFACE
UNKW	UNKNOWN
WC	WEARING COURSE
WC1 WC2	WEARING COURSE 1 WEARING COURSE 2
WC2 WC3	
	WEARING COURSE 3 WEARING COURSE 4
WC4 WC5	WEARING COURSE 4 WEARING COURSE 5
	WEARING COURSE 5 WEARING COURSE 6
WC6 WC7	WEARING COURSE 6 WEARING COURSE 7
WC7	WEARING COURSE 7 WEARING COURSE 8
WC8	WEAKING COURSE 8