PAVEMENT EVALUATION CORING AND CONDITION DATA INPUT DATA REPORT

MANDIST	FINPROJ	TYPSECT	MESSAGE
06	445989-1-52-01	01	THE CONTROL CARD IS CORRECT

MEDIAN:

FLORIDA DEPARTMENT OF TRANSPORTATION PAVEMENT CORING REPORTING

PAVEMENT EVALUATION CORING AND CONDITION DATA

END MP: 7.06 LENGTH: 1.99

FIN PROJ: 445989-1-52-01 NAME: CORED BY: OSCAR CORREA TERRACON

TYP SECT: 01 FROM: DATE: 2020-04-20

BEG MP: 5.06

TO: LANES: @ FEET

FA PROJ: D623008B

COUNTY: MIAMI-DADE SHOULDER TYPE

SR NUMBER: SR 9336 INSIDE:

PROJECT MEASUREMENT: ENGLISH OUTSIDE:

CURB & GUTTER: NO

CURBED: NO

PAVEMENT EVALUATION CORING AND CONDITION DATA

CORE	MILE	W		CORE	CRACK PMT	
NO.	POST	VFY LN PTOP	PAVEMENT LAYER	LNGTH BASE SUB DEP	TH TYP CLSS EXT CND	COMMENTS
		FC5	S1 BIND	LR		
1	.000	N L1 Y 1.10	3.70 1.00	5.80 18.0	F	25.4193 -80.5014
2	.000	N R1 Y 1.00	4.60	5.60 18.0	F	25.4290 -80.5014
3	.000	N L1 Y 1.10	4.30 1.00	6.40 12.0	F	25.4388 -80.5015
4	.000	N R1 Y 1.30	4.30 1.00	6.60 24.0	F	25.4471 -8035016
	.000					

FLORIDA DEPARTMENT OF TRANSPORTATION PAVEMENT CORING REPORTING

PAVEMENT EVALUATION CORING AND CONDITION DATA

COMMENTS

SEQ 	
1	SUBGRADE IS LT BROWN LIMEROCK WITH SAND
2	SUBGRADE IS LT BROWN LIMEROCK WITH SAND
3	SUBGRADE IS LT BROWN LIMESTONE
4	SUBGRADE IS LT BROWN LIMESTONE
5	THE MILLING AND PAVING RECOMMENDATION IS
6	MILL 1.5" AND RESURFACE WITH 1.5" OF FC 12.5

FLORIDA DEPARTMENT OF TRANSPORTATION PAVEMENT CORING REPORTING

CODE DESCRIPTIONS

	CODE DESCRIPTIONS
	TYPE DESCRIPTION
A	ALLIGATORING IN WHEELPATH
В	BLOCK CRACKING
С	COMBINATION OF TYPES
	EXTENT DESCRIPTION
L	LIGHT
М	MEDIUM
S	SEVERE
	CLASS DESCRIPTION

UNKNOWN

UNKNOWN

ΙI

III

CODE DESCRIPTIONS

SURFACE LAYER CODE ====	DESCRIPTION
ARMI BIND BRCK CONC CRL FAB FC FC1 FC2	ASPHALT RUBBER MEMBRANE INTERI ASPHALT BINDER COURSE BRICK PAVERS PORTLAND CEMENT CONCRETE CRACK RELIEF LAYER PAVEMENT OVERLAY FABRIC FRICTION COURSE FRICTION COURSE 1 FRICTION COURSE 2
FC3 FC4 FC5 FC5B FC6 F12M F125 F95	FRICTION COURSE 3 FRICTION COURSE 4 FRICTION COURSE 5 FRICTION COURSE 5 BONDED FRICTION COURSE 6 FRIC. COURSE 12.5 MODIFIED FRICTION COURSE 12.5 FRICTION COURSE 9.5 FRIC. COURSE 9.5 MODIFIED
S SAHM SP1C SP1F SP2C SP2F SP3C SP3C SP3F ST	TYPE S ASPHALTIC CONCRETE SAND ASPHALT HOT MIX 9.5 SUPERPAVE COARSE GRADED 9.5 SUPERPAVE FINE GRADED 12.5 SUPERPAVE COARSE GRADED 12.5 SUPERPAVE FINE GRADED 19.0 SUPERPAVE COARSE GRADED 19.0 SUPERPAVE FINE GRADED SURFACE TREATMENT TYPE S-I ASPHALTIC CONCRETE
S2 S3 T1 T2 T3 UNIM UNKW WC	TYPE S-II ASPHALTIC CONCRETE TYPE S-III ASPHALTIC CONCRETE TYPE I ASPHALTIC CONCRETE TYPE II ASPHALTIC CONCRETE TYPE III ASPHALTIC CONCRETE UNIMPROVED SURFACE UNKNOWN WEARING COURSE
WC1 WC2 WC3 WC4 WC5 WC6 WC7 WC8	WEARING COURSE 1 WEARING COURSE 2 WEARING COURSE 3 WEARING COURSE 4 WEARING COURSE 5 WEARING COURSE 6 WEARING COURSE 7 WEARING COURSE 8