PAVEMENT EVALUATION CORING AND CONDITION DATA INPUT DATA REPORT

MANDIST	FINPROJ	TYPSECT	MESSAGE
06	443940-1-52-01	01	THE CONTROL CARD IS CORRECT

FLORIDA DEPARTMENT OF TRANSPORTATION PAVEMENT CORING REPORTING

PAVEMENT EVALUATION CORING AND CONDITION DATA

FIN PROJ: 443940-1-52-01 NAME: CORED BY: HRES

TYP SECT: 01 FROM: DATE: 2018-11-29

BEG MP: 9.67

TO: LANES: @ FEET

FA PROJ:

MEDIAN:

COUNTY: MIAMI-DADE SHOULDER TYPE

END MP: 10.00 LENGTH: .33

SR NUMBER: SR 9 INSIDE:

PROJECT MEASUREMENT: ENGLISH OUTSIDE:

CURB & GUTTER: NO

CURBED: NO

PAVEMENT EVALUATION CORING AND CONDITION DATA

CORE NO.	MILE POST	VFY	LN	W P	TOP		PAVEMENT	LAYER	 CORE LNGTH	BASE			-			_	CROSS SLOPE	COMMENTS	
				_					 					 					
					S1	BIND				LR	ST40								
1	.000	N	R2	Y	5.30	1.00			6.30	12.0	12.0	1.30			F			SR9 NB	
2	.000	N	L1	Y	6.90				6.90			2.00			F			SR9 SB	
3	.000	N	L1	Y	7.00	1.00			8.00	12.0	12.0				G			SR9 SB	
4	.000	N	R3	Y	4.90	1.00			5.90	12.0	12.0	1.50			F			SR9 NB	
5	.000	N	L2	Y	5.10	1.50			6.60	12.0	12.0	6.60			F			SR9 SB	
	.000																		

FLORIDA DEPARTMENT OF TRANSPORTATION PAVEMENT CORING REPORTING

PAVEMENT EVALUATION CORING AND CONDITION DATA

COMMENTS

SEQ 	
1	BASE IS LIMEROCK. SUBBASE IS FINE SAND. NO BASE OR
2	SUBBASE SAMPLES WERE OBTAINED DUE TO THE PRESENCE
3	OF CONCRETE UNDER THE ASPHALT CORE C-2
4	THE MILLING RECOMMENDAITON IS TO MILL 1.5" AND
5	ספסואפי שויים פכ 10 5

FLORIDA DEPARTMENT OF TRANSPORTATION PAVEMENT CORING REPORTING

	CODE DESCRIPTIONS
CRACK TYPE	TYPE DESCRIPTION
А	ALLIGATORING IN WHEELPATH
В	BLOCK CRACKING
С	COMBINATION OF TYPES
CRACK EXTNT	EXTENT DESCRIPTION
L	LIGHT

M MEDIUM

S SEVERE

CRACK CLASS CLASS DESCRIPTION

IB UNKNOWN

II UNKNOWN

III UNKNOWN

CODE DESCRIPTIONS

SURFACE LAYER CODE ====	DESCRIPTION
ARMI BIND BRCK CONC CRL FAB FC FC1 FC2 FC3 FC4	ASPHALT RUBBER MEMBRANE INTERL ASPHALT BINDER COURSE BRICK PAVERS PORTLAND CEMENT CONCRETE CRACK RELIEF LAYER PAVEMENT OVERLAY FABRIC FRICTION COURSE FRICTION COURSE 1 FRICTION COURSE 2 FRICTION COURSE 3 FRICTION COURSE 4
FC5 FC5B FC6 F12M F125 F95 F95M S SAHM SP1C	FRICTION COURSE 5 FRICTION COURSE 5 BONDED FRICTION COURSE 6 FRIC. COURSE 12.5 MODIFIED FRICTION COURSE 9.5 FRICTION COURSE 9.5 FRIC. COURSE 9.5 MODIFIED TYPE S ASPHALTIC CONCRETE SAND ASPHALT HOT MIX 9.5 SUPERPAVE COARSE GRADED
SP1F SP2C SP2F SP3C SP3F ST S1 S2 S3	9.5 SUPERPAVE FINE GRADED 12.5 SUPERPAVE COARSE GRADED 12.5 SUPERPAVE FINE GRADED 19.0 SUPERPAVE COARSE GRADED 19.0 SUPERPAVE FINE GRADED SURFACE TREATMENT TYPE S-I ASPHALTIC CONCRETE TYPE S-III ASPHALTIC CONCRETE TYPE S-III ASPHALTIC CONCRETE
T1 T2 T3 UNIM UNKW WC WC1 WC2 WC3 WC4 WC5 WC6	TYPE I ASPHALTIC CONCRETE TYPE II ASPHALTIC CONCRETE TYPE III ASPHALTIC CONCRETE UNIMPROVED SURFACE UNKNOWN WEARING COURSE WEARING COURSE 1 WEARING COURSE 2 WEARING COURSE 3 WEARING COURSE 4 WEARING COURSE 5 WEARING COURSE 5 WEARING COURSE 6
WC7 WC8	WEARING COURSE 7 WEARING COURSE 8