PCRPJ03 PCRO003

PAVEMENT EVALUATION CORING AND CONDITION DATA INPUT DATA REPORT

MANDIST	FINPROJ	TYPSECT	MESSAGE
06	451033-1-52-01	01	THE CONTROL CARD IS CORRECT

PCRPJ03 PCR0103

PAVEMENT EVALUATION CORING AND CONDITION DATA

FIN PROJ:	451033-1-52-01	NAME :	NW 72ND AVE	CORED BY:	TERRACON
TYP SECT:	01	FROM:	AT SR-948 / NW 36TH	DATE:	2024-03-13
		TO:		LANES:	3 @ FEET
FA PROJ:			2.02		
COUNTY:	MIAMI-DADE	BEG MP:	3.23	SHOULDEF	R TYPE
SR NUMBER:	SR 948	END MP:	3.49 LENGTH: .26	INSIDE:	
MEDIAN.		PROJECT	MEASUREMENT: ENGLISH	OUTSIDE:	
MEDIAN: CURBED:	NO		(CURB & GUTTER:	NO

PCRPJ03 PCR0203

PAVEMENT EVALUATION CORING AND CONDITION DATA

CORE NO.	MILE POST	VFY	V LN P	I PTOP		- PAV	EMENT	LAYER		CORE LNGTH	BASE		-	CK CLSS E		COMMENTS
				F125	S1	S1	S1	S1	S1		LR	STAB				
1	3.320	Ν	L1 У	1.10	1.30	1.80	1.20	1.70	7.20	14.30	12.0	12.0			F	SG: LT BROWN SAND
2	3.401	N	LЗ Υ	1.00	1.20	1.50	1.80	1.40	6.60	13.50	12.0	12.0			F	SG: LT BROWN SAND W/ LR
	.000															

PCRPJ03 PCRO303

PAVEMENT EVALUATION CORING AND CONDITION DATA

COMMENTS

SEQ

- ____ ____
 - 1 MILLING RECOMMENDATIONS: MILL 1.50 INCHES AND
 - 2 REPAVE WITH 1.50 INCHES FC-12.5 (FRICTION COURSE).

CODE DESCRIPTIONS

CRACK TYPE	TYPE DESCRIPTION
===========	

- A ALLIGATORING IN WHEELPATH
- B BLOCK CRACKING
- C COMBINATION OF TYPES

CRACK EXTNT EXTENT DESCRIPTION

- L LIGHT
- M MEDIUM

S SEVERE

CRACK CLASS CLASS DESCRIPTION

- IB UNKNOWN
- II UNKNOWN
- III UNKNOWN

CODE DESCRIPTIONS

SURFACE LAYER	
CODE	DESCRIPTION
====	
ARMI	ASPHALT RUBBER MEMBRANE INTERL
BIND	ASPHALT BINDER COURSE
BRCK	BRICK PAVERS
CONC	PORTLAND CEMENT CONCRETE
CRL	CRACK RELIEF LAYER
FAB	PAVEMENT OVERLAY FABRIC
FC	FRICTION COURSE
FC1	FRICTION COURSE 1
FC2	FRICTION COURSE 2
FC3	FRICTION COURSE 3
FC4	FRICTION COURSE 4
FC5	FRICTION COURSE 5
FC5B	FRICTION COURSE 5 BONDED
FC6	FRICTION COURSE 6
F12M	FRIC. COURSE 12.5 MODIFIED
F125	FRICTION COURSE 12.5
F95	FRICTION COURSE 9.5
F95M	FRIC. COURSE 9.5 MODIFIED
S	TYPE S ASPHALTIC CONCRETE
SAHM	SAND ASPHALT HOT MIX
SP1C	9.5 SUPERPAVE COARSE GRADED
SP1F	9.5 SUPERPAVE FINE GRADED
SP2C	12.5 SUPERPAVE COARSE GRADED
SP2F	12.5 SUPERPAVE FINE GRADED
SP3C	19.0 SUPERPAVE COARSE GRADED
SP3F	19.0 SUPERPAVE FINE GRADED
ST	SURFACE TREATMENT
S1	TYPE S-I ASPHALTIC CONCRETE
S2	TYPE S-II ASPHALTIC CONCRETE
S3	TYPE S-III ASPHALTIC CONCRETE
T1 T2	TYPE I ASPHALTIC CONCRETE TYPE II ASPHALTIC CONCRETE
12 T3	TYPE III ASPHALTIC CONCRETE
UNIM	UNIMPROVED SURFACE
UNKW	UNKNOWN
WC	WEARING COURSE
WC1	WEARING COURSE 1
WC1 WC2	WEARING COURSE 1 WEARING COURSE 2
WC2 WC3	WEARING COURSE 2 WEARING COURSE 3
WC4	WEARING COURSE 3
WC5	WEARING COURSE 5
WC6	WEARING COURSE 6
WC7	WEARING COURSE 7
WC8	WEARING COURSE 8
100	