

STATE OF FLORIDA DEPARTMENT OF TRANSPORTATION

PAVEMENT EVALUATION CORING AND CONDITION DATA

Cored By: TEST LAB, INC

Coring Completion Date: 12/30/2024

Typical Section: OWENSBORO\_RD

W.P.I. No.:			Name: SR 35 / SR 700 / US 98 / US 301			Lanes: 4 to 6 Lane Urban Principal Arterial Roadway		
Fin. Proj. ID: 451236-1			From: N. of Long Ave			Shoulder Type and Condition:		
F.A. Project No.:		Roadway ID: 14050001	To: S. of US 98			Inside: NONE		
County: PASCO	SR No.: 35 / 700	Beg MP: 0.000	End MP: 0.399	Length: 0.399	Outside: NONE			
Overall Pavement Condition (from DMO field review): Fair			Median Curbed (Y/N): N	Paved:	Lawn:	Other:	Curb & Gutter (Y/N): N	

14050001-All Cores

CORE NO.	MILE POST <sup>2</sup>	LANE TYPE	LANE	WP (Y/N)	PAVEMENT LAYER (IN.)										TOTAL ASPHALT THICKNESS (IN.)	BASE				STABILIZED SUBGRADE <sup>3</sup>	CRACK				PAVEMENT CONDITION	COMMENTS
					FC5	FC12.5	SP12.5	S								LR						DEPTH (IN.)	TYPE	CLASS		
155	0.041	ML	L1	N	1.0		1.2	1.5						3.7	8.3					3.7	B	III	S	P	Owensboro Rd.	
156	0.066	ML	R1	N			1.0							1.0	6.0					1.0	B	II	S	P	Owensboro Rd.	
157	0.104	ML	L1	Y		1.2								1.2	6.8									P	Owensboro Rd. Block cracking.	
158	0.145	ML	R1	Y			1.2							1.2	6.8				11.0	1.2	B	III	S	P	Owensboro Rd.	
159	0.238	ML	L1	N				1.0						1.0	11.0				9.5	1.0	A	IB	L	P	Owensboro Rd. Raveling.	
160	0.248	ML	R1	Y				0.9						0.9	6.1					0.9	A	II	L	P	Owensboro Rd. Raveling.	
161	0.300	ML	R1	Y				1.0						1.0	6.0					1.0	B	IB	L	P	Owensboro Rd.; One-way Rd. Raveling.	
162	0.371	ML	R1	Y				0.9						0.9	7.1					0.9	A	II	M	P	Owensboro Rd.; One-way Rd. Raveling.	
AVERAGE					1.00	1.20	1.13	1.06						1.36	7.26				10.25	1.39						
MAX					1.00	1.20	1.20	1.50						3.70	11.00				11.00	3.70						
MIN					1.00	1.20	1.00	0.90						0.90	6.00				9.50	0.90						
LAYER COEF.					0.00	0.25	0.25	0.25							0.18				0.08							

- Notes:
1. The data presented on this table is specific only at the locations cored at the time of the investigation. Should questions arise regarding the pavement composition, it is incumbent upon those raising the question to perform additional exploration as necessary.

2. Mile posts are approximate based on field recorded measurements using a Distance Measuring Instrument (DMI) or a GPS unit.

3. Stabilization thickness was checked on 10% of the coring locations. For pavement design, assume 12 inches of thickness for stabilization.

4. The cross slope is approximate and measured in the center of the lane.

5. A blank cell indicates measurement was not recorded.

6. A value of "UNK" indicates material was encountered but the total thickness was not determined.

Lane Designations - Decreasing MP	Lane Designations - Increasing MP	Lane Type		Crack Type	Crack Rating	Extent	Pavement Condition
OL/IL - Outside/Inside Shoulder	OR/IR - Outside/Inside Shoulder	ML - Mainline	S - Shoulder	A - Alligator	Class IB - Hairline cracks that are ≤ 1/8 inch wide	L - Light	G - Good
L1 - 1st Lane Left of Centerline	R1 - 1st Lane Right of Centerline	TL - Turn Lane	SS - Side Street	B - Block	Class II - Cracks > than 1/8 inch and ≤ 1/4 inch	M - Moderate	F - Fair
LL/LR - Left/Right Turn Lane	RL/RR - Left/Right Turn Lane	CO - Crossover	BR - Bridge Approach/Departure	C - Combination	Class III - Cracks > 1/4 inch	S - Severe	P - Poor