

STATE OF FLORIDA DEPARTMENT OF TRANSPORTATION  
**PAVEMENT EVALUATION CORING AND CONDITION DATA**

Cored By: Madrid Engineering Group

Coring Completion Date: 1/18/2022

Typical Section: \_\_\_\_\_

W.P.I. No.:	Name: SR 592 (I-375)	Lanes: 6
Fin. Proj. ID: 445865-1	From: I-275	Shoulder Type and Condition: PAVED, GOOD
F.A. Project No.:	Roadway ID: 15002000	To: SR 595 / 4th Ave. North
County: Pinellas	SR No.: 592	Inside: 15.0' paved with warn
Overall Pavement Condition (from DMO field review): Fair	Beg MP: 0.000	End MP: 1.220
	Median Curbed (Y/N): N	Length: 1.220
	Paved	Other: Barrier
	Lawn	Outside: 8' paved with warn
		Curb & Gutter (Y/N): Y

All Cores																													
CORE NO.	MILE POST <sup>2</sup>	LANE TYPE	LANE	WP (Y/N)	PAVEMENT LAYER (IN.)										TOTAL ASPHALT THICKNESS (IN.)	BASE				STABILIZED SUBGRADE <sup>3</sup>	CRACK				PAVEMENT CONDITION	RUT DEPTH - LWP (IN.)	RUT DEPTH - RWP (IN.)	CROSS SLOPE (%) <sup>4</sup>	COMMENTS
					CONC	FC12.5	S									SCM 300	ABC-1				DEPTH (IN.)	TYPE	CLASS	EXTENT					
1	0.505	BR	R3	N	10.2										10.2	8.5					10.2	C	II	M	F				
2	0.570	ML	R3	N	9.1										9.1	7.0									F				
3	0.571	S	OR	N		1.4									1.4		4.6			12.0					F				
9	0.872	BR	L3	N	8.0										8.0	5.5					8.0	C	II	M	P				
10	0.745	ML	L3	N	9.5										9.5	7.5					9.5	C	III	S	P				
11	0.744	S	OL	N		1.5	0.4								1.9		5.0			6.0					F				
12	0.505	BR	L3	N	9.6										9.6	6.0									F				
18	0.050	ML	R2	N	9.0										9.0	7.5									F				
19	0.053	S	OR	N		1.6									1.6		3.4			16.0	1.6	C	III	S	P				BASE CRACK
20	0.095	ML	R2	N	9.4										9.4	8.0					9.4	C	II	M	F				
21	0.536	ML	R2	N	8.8										8.8	7.5									F				
22	0.746	S	OR	N	8.6										8.6	8.0					8.6	C	III	S	P				
23	0.824	ML	R1	N	8.8										8.8	7.0					8.8	C	II	M	F				
24	0.888	BR	R2	N	9.2										9.2	8.0					9.2	C	III	S	P				
25	1.064	BR	R2	Y	9.4										9.4	7.5					9.4	C	II	M	F				
26	1.118	ML	R2	N	8.4										8.4	8.0									F				
27	1.119	S	OR	N		1.5	5.1								6.6	7.0									F				
28	1.147	ML	L2	N	9.8										9.8	7.0									F				
29	1.146	S	OL	N		1.9									1.9		3.8			2.0	1.9	C	II	M	F				BASE CRACK
30	1.064	BR	L2	Y	9.0										9.0	8.0					9.0	C	IB	L	F				
31	0.806	ML	L1	N	8.9										8.9	8.0					8.9	C	III	S	P				
32	0.532	ML	L2	N	9.4										9.4	7.5									F				
34	0.023	ML	R1	N	8.9										8.9	7.0									F				
35	0.023	S	IR	N		1.3									1.3		5.0			14.0	1.3	C	III	S	P				BASE CRACK
36	0.660	ML	R1	N	9.1										9.1	7.5									F				
38	0.661	S	IR	N	8.9										8.9	7.0									F				
39	0.865	S	IR	N	9.1										9.1	6.5									F				
40	1.156	ML	R1	N	8.7										8.7	8.0									F				
41	1.157	S	IR	N		1.4	5.1								6.5	6.5									F				BASE IS SCM WITH 2" STONE ON TOP
42	1.110	ML	L1	N	9.1										9.1	7.5					9.1	C	III	S	P				
43	1.110	S	IL	N		1.7									1.7		5.0			8.0					F				
44	0.586	ML	L1	N	9.0										9.0	6.0									F				

